

# Use of residual materials for synthesis of lightweight granulates by thermal treatment process

Ndue Kanari, Frédéric Diot, Christophe Gauthier, Jacques Yvon

## ▶ To cite this version:

Ndue Kanari, Frédéric Diot, Christophe Gauthier, Jacques Yvon. Use of residual materials for synthesis of lightweight granulates by thermal treatment process. Applied Clay Science, 2016, 123, pp.259-271. 10.1016/j.clay.2015.12.027. hal-01452246

# HAL Id: hal-01452246 https://hal.univ-lorraine.fr/hal-01452246

Submitted on 5 May 2017

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



1		
-		

3

4

5

8 9

# treatment process N. Kanari, F. Diot, C. Gauthier and J. Yvon

Université de Lorraine, UMR 7359 CNRS, CREGU, GeoRessources Laboratory, 2 rue du Doyen
 Roubault, TSA 70605, Vandoeuvre-lès-Nancy Cedex, F-54518, France.

Use of residual materials for synthesis of lightweight granulates by thermal

#### Abstract

10 The general scope of this paper is to explore the formulation and the production, by 11 thermochemical transformations, of expanded lightweight granulates incorporating residual 12 materials as kaolinitic waste, sewage sludge, schist fines and wasted glass. The possible 13 application fields are light concretes, road engineering, water treatment and hydroponic 14 agriculture. The benefits can be multiple: creation of new resources from wastes; preservation of 15 primary resources; humid zones on the river banks and the natural course of rivers; management 16 of hazardous residual materials.

Tests on the thermal treatment and the thermochemical expansion were conducted in horizontal 17 experimental set-up including a static electrical furnace. Raw material mixtures and treatment 18 products were examined by visible microscopy, scanning electron microscopy-energy dispersive 19 spectroscopy (SEM-EDS), X-ray diffraction (XRD) and infrared spectroscopy (IR) in order to 20 understand the thermal behaviors of the chosen samples. Data analysis of the experimental results 21 showed the possibility of obtaining the expanded granulates at temperatures lower than or equal 22 to 1100°C for a firing time of a few minutes. The optimal temperature for their synthesis is a 23 function of fluxes content and decreased significantly with increase of the wasted glass amount. 24 Obtained granulates have a density lower than unity and they have good mechanical strength 25 fulfilling the conditions for their use as building materials. 26

Sewage sludge, wasted glass as well as incinerator ashes can be used as alternative materials, among other industrial solid wastes, in the formulation of lightweight clay and schist based granulates. Results of this work try to meet the principles of sustainable mining and decreased pressure on the environment.

31

32 Keywords: Residual materials, kaolinitic waste 'KW', sewage sludge, lightweight granulates.

#### 34 **1. Introduction**

Using natural lightweight materials for the construction purpose is known since Roman times. 35 Pumice and scoria, the oldest of these materials, are of volcanic origin and can be used after 36 simple mechanical operations (Chandra and Berntsson, 2002). But, their occurrence is related to 37 the eruption actions of volcanos, therefore their abundance has a heterogeneous geographical 38 distribution. Nowadays, there is a great interest for the use of the natural materials and/or 39 aggregates that undergo thermal expansion under controlled conditions. The perlite and some 40 lamellar minerals i.e. vermiculite, clay, schist, shale, slate are the most identified raw materials 41 used for the thermal synthesis of the lightweight aggregates. An excessive exploitation of these 42 non-renewable natural resources will lead to their depletion in the future. In addition, the 43 reserves in granulates of developed countries become lower and lower and their exploitation is 44 severely regulated due to environmental constraint concerning the water flow management and 45 the protection of humid zones. In this context, attempts were made to replace, at some extents, 46 the natural materials by residual substances. However, these solid wastes and by-products have 47 to accomplish the principles of the expansion process based upon two phenomena: (i) the 48 formation of a continuous plastic phase, and (ii) the presence of volatile matter under certain 49 pressure trapped inside this phase creating bubbles that generate the expansion. This plastic 50 phase is formed when the materials are heated and transformed into a softened and/or partially 51 liquid state. Depending on the physical properties of materials, the softening temperatures varied 52 widely reaching, in some cases, more than 1500°C. Most of the common chemical substances 53 54 able to generate gases undergo this phenomenon at temperatures lower than 1000°C. Note as examples: the combustion and/or pyrolysis of organic matter; the release of bonded/chemical 55 water; the decomposition of sulphates, hydrated phosphates, carbonates; the oxidation of 56 57 sulphides, etc. Hence, a large difference between the softening temperature and the gasification

temperature mostly leads to sintering rather than expansion. This is due to gas leakage after thatthe continuous fluid phase is formed.

As could be expected, the elemental composition of materials undergoing thermal expansion are 60 composed of the most abundant elements of the earth crust, i.e. O. Si, Al, Fe, Ca, Na, K, Mg 61 representing the rock-forming elements with SiO<sub>2</sub> as the main constituent. Therefore, they are 62 generated during mining, mineral processing and other pre-treatment process of raw materials, 63 metallurgical extraction of valuable metals, chemical purification and metals refining as well as 64 at the end-of-life products. Sterile residues, harbor sediments, tailings, slags, sludges, ashes, 65 dusts, wasted glass are the most common and generic names of them. Addition and incorporation 66 of two or more residual substances in the formulation of materials to be thermally expanded is 67 often recommended allowing mixtures satisfying the necessary and sufficient conditions for the 68 expansion as mentioned above. One may underline that it is important to decrease the soften 69 temperature of the materials to be expanded. One possibility to achieve that in a given system is 70 to add materials containing so called "fluxes". They are well known in extractive metallurgy 71 72 during slag formation as well as in the glass industry. A typical example is illustrated in Fig. 1 representing the phase equilibrium diagram for Na-Si-O system (Levin et al., 1964). It contains 73 three binary compounds: the orthosilicate  $(2Na_2OSiO_2)$ , the metasilicate  $(Na_2OSiO_2)$ , and the 74 disilicate (Na<sub>2</sub>O<sub>2</sub>SiO<sub>2</sub>). The two last compounds melt congruently at about 1090°C and 875°C, 75 respectively. However, the most important part of this diagram is to contain more than 70% SiO<sub>2</sub> 76 corresponding to the composition of the most common glasses. An eutectic (Na<sub>2</sub>O SiO<sub>2</sub>-SiO<sub>2</sub>) 77 occurs at about 74% SiO<sub>2</sub> and 793°C (Fig. 1) resulting in an important decrease of melting point 78 of the mixture. For this raison, it is suggested to add wasted glass in the formulation of the 79 lightweight materials. Phase diagrams of three (Na<sub>2</sub>O-Al<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub>) and other oxides are also 80 available in the literature describing equilibrium phase composition and their evolution with 81 temperature. 82

As overviewed recently (Zhang, 2013; Monteiro and Vieira, 2014) extensive works were
devoted to the incorporation of wastes in fired clay ceramics.

Many investigations were devoted to the use of various coproducts, residues and wastes for 85 incorporating in the lightweight materials. In a recent work (Ouina et al., 2014), the air pollution 86 control residues from municipal solid waste incineration is used at low extent (< 10%) to 87 substitute clay for the preparation of lightweight aggregates. A study of González-Corrochano et 88 al. (2014) reports the synthesis of lightweight aggregates at 1150°C using mining and industrial 89 waste as raw materials. The manufacture of the lightweight aggregates by incorporating fly ashes 90 and reaction ashes with reservoir sediments at 1150-1200°C is investigated by Chen et al. 91 (2010). Recycling of harbour sediment via lightweight materials is considered as an appropriate 92 route thanks to its proper chemical composition and particle size distribution (Wei et al., 2008). 93 The authors concluded that leaching levels of trace metals including Pb, Hg, As, Cd, Cu, and Cr 94 from all lightweight aggregate samples are less than regulatory limits. Stabilization of heavy 95 metals in the lightweight materials is also demonstrated by Xu et al. (2013). 96

In this optic, the objective of this study is to investigate the synthesis of the lightweight granulates starting from only wastes and by-products such as kaolinitic waste, sewage sludge, schist fines, and wasted glass. As the first step of the investigation, much attention was paid to the thermal behaviour of these materials and to their mineralogical evolution as a function of the temperature between 150°C and 1200°C. Thereafter, the binary and ternary prepared mixtures were subjected to the thermal expansion by firing between 1000°C and 1200°C.

103

#### 104 **2. Materials and methods**

105 Multiple samples coming from the industrial exploitation of kaolinitic and schist deposits, 106 wastewater treatment plants as well as from end-of-life glass materials were collected for this 107 investigation. They were used in powder form for the individual thermal treatment. General

morphological aspects of the initial samples examined by SEM as well as their composition, 108 expressed as simple oxides for main elements, are grouped in Fig. 2. The kaolinitic waste 'KW' 109 sample (Fig. 2a) has a broad particle size with a  $d_{90}$  equal to 183 µm and it is used in bulk state 110 111 without further grinding or sizing process. The sample has high contents of silica and alumina as well as the potassium oxide which will promote the decrease of the softening and/or melting 112 point of the system. The sewage sludge 'SS' sample (Fig. 2b) possesses a complex composition 113 which is linked to their process generation. Besides silica and alumina, this sample contains 114 appreciable amounts of calcium, phosphorus, iron and magnesium compounds. Five major 115 elements constituting the schist fines 'SF' sample (Fig. 2c) are silicon, aluminium, iron, 116 117 potassium and magnesium. Finally, the composition of the wasted glass 'WG' sample (Fig. 2d) reflects its origin being a soda-lime-silica glass originating from the recycling of the glass 118 containers. 119

The binary and ternary formulations at various proportions of the above mentioned materials were prepared and the composition of some typical mixtures (M1 through M4) is given in Table 1. To prepare the mixtures, definite proportions of KW, SS, SF and WG (Table 1) were thoroughly mixed and homogenized. Thereafter, the obtained products are blended with water to form a pasty material which is rolled by hand as granulates of centimetric size.

Raw materials and the prepared granulates were dried in an oven at 60°C for evaporating the free 125 126 water before thermal treatment and different analysis tests. Thermal experimental trials were conducted in horizontal set-ups including a system of static tubular furnaces able to reach 127 1600°C. For the thermal treatment tests, the sample is introduced directly into the furnace 128 already preheated at desired temperature and when the dwell time is reached, the sample is 129 removed from the furnace and cooled down to room temperature. Air was used as flow gas and it 130 131 also assured the combustion of the organic matter contained in the mixtures. The outlet gases were cooled at room temperature leading to the condensation of the vapor phase and the recovery 132 of a solid condensate mixed with the soot. Initial raw materials and solid products obtained from 133

raw material mixtures and thermally expanded granulates were examined by visible microscopy,
scanning electron microscopy-energy dispersive spectroscopy (SEM-EDS), X-ray diffraction
(XRD), and infrared (DRIFTS) spectroscopy (IR). Solid condensates were subjected to SEMEDS analysis.

SEM examinations were performed by using a HITACHI S-4800 device equipped with an EDS
elemental analysis microprobe. SEM imaging and chemical microanalysis were realized at
accelerating voltage of 15 kV. The samples were carbon covered prior to analysis.

141 XRD was performed on powdered samples using a Bruker D8 Advance device, (Co K $\alpha$ 1 142 radiation,  $\lambda = 1.789$  Å), under 35 kV and 45 mA operating conditions. The acquisition of 143 diffraction patterns was performed between 3° and 64° (2 $\theta$ ) range at step scan 0.034° with 3 s 144 per step. The XRD-patterns were analysed thanks to the DIFFRAC.EVA software and PDF-2 145 release 2011 database.

Diffuse reflectance infrared Fourier transform spectroscopy (DRIFTS) was performed using a Bruker IFS 55 spectrometer. The infrared spectra were collected between 600 and 4000 cm<sup>-1</sup> wavenumber range with a 2 cm<sup>-1</sup> resolution. Most infrared spectra were interpreted using previously reported data (Farmer, 1979).

150

1	5	1
	5	T

Table 1. Composition of several prepared mixtures (wt.%).

Mixtures	Kaolinitic waste 'KW'	Sewage sludge 'SS'	Schist fines 'SF'	Wasted glass 'WG'
M1		25	75	
M2		20	60	20
M3	40	20		40
M4	50	20		30

152

#### 154 **3. Results and discussion**

#### 155 **3.1 Isothermal treatment of initial samples**

The thermal treatment of the individual samples was carried out under isothermal conditions 156 from 150°C to 1200°C for 30 minutes and the obtained data are plotted in Fig. 3. The evolution 157 of the mass loss (ML%) versus temperature during the treatment of the kaolinitic waste sample is 158 drawn in Fig. 3a. The curve shape suggests that at least two phenomena can be distinguished at 159 temperature lower and higher than 700°C. By assuming that there is still kaolinite in the KW 160 sample and after reviewing works related to the thermal behavior of the kaolinite clay, one may 161 emphasis that the ML% up to 700°C can be attributed to the dehydroxylation of kaolinite. 162 Moreover, as the relative mass of water in pure kaolinite [Al<sub>2</sub>Si<sub>2</sub>O<sub>5</sub>(OH)<sub>4</sub>, i.e. Al<sub>2</sub>O<sub>3</sub>·2SiO<sub>2</sub>·2H<sub>2</sub>O] 163 is 13.96%, one may suggest that the kaolinite content in the KW sample is around 10%. 164 Volatilization of the micas structural water contained in KW can be responsible for the ML 165 observed at higher temperature. Nevertheless, the ML% curve is an apparent reflection of the 166 sample thermal behavior due to the broad size fractions of the KW sample used for the 167 experimental tests and to the intrinsic transformation kinetics. 168

Data compilation for the sewage sludge treatment between 150°C and 1150°C is drawn in 169 Fig. 3b. As could be expected, such materials are very complex in composition including organic 170 matter, clavs, carbonates, phosphates, sulphates, quartz, etc. Further, SS sample is constituted of 171 intrinsic fine particles (several um) leading to an increased activity compared with KW sample. 172 However, the ML curve shape for the SS treatment reflects two significant steps of ML%. One 173 may speculate that dehydration, combustion/decomposition of organic matter and clays 174 dehydroxylation are produced at temperatures lower than 550°C. Whilst the metal carbonate 175 decomposition (most probably CaCO<sub>3</sub>) occurs at temperatures higher than 700°C. Note that the 176 final ML% of the sample at 1100°C is more than 9 times higher than that of KW sample. 177

The shape of the thermal treatment curve of the schist fines sample plotted in Fig. 3c indicated a continuous mass loss up to about 800°C with a value close to 4.5% ML. As expected, the ML of the wasted glass sample (Fig. 3c) is low with an average value of about 0.4% in the whole temperature range studied. These preliminary assumptions for the thermal behaviors of these samples are developed and discussed during interpretation of some XRD, IR and SEM-EDS results which are exposed below.

184

#### 185 **3.2** Characterization of the thermal treatment products

#### 186 *3.2.1 Kaolinitic waste*

The results of the XRD measurements of the initial kaolinitic sample and the obtained residues at 187 different treatment temperatures (from 300°C to 1200°C) are displayed in Fig. 4. Whilst, the IR 188 (DRIFTS) results are summarized in Fig. 5. XRD analysis shows the presence of micas 189  $\{Al_2[AlSi_3O_{10}(OH,F)_2K]$ -muscovite;  $Al_{(2-x)}(Mg,Fe)_xSi_3Al)(K,H_3O)_x(O_{10}[(OH)_2,(H_2O)]$ -illite} as 190 191 well as kaolinite  $[Al_2Si_2O_5(OH)_4]$  as major crystallized phases in the KW raw sample (Fig. 4a). Other major phases revealed by XRD consisted of quartz ( $\alpha$ -SiO<sub>2</sub>), alkali feldspar (KAlSi<sub>3</sub>O<sub>8</sub>) 192 and schorl [NaFe<sup>2+</sup><sub>3</sub>Al<sub>6</sub>(BO<sub>3</sub>)<sub>3</sub>Si<sub>6</sub>O<sub>18</sub>(OH)<sub>4</sub>], note that this mineral contains borate ions and acts 193 as a flux. SEM-EDS analysis of the non-treated kaolinitic waste confirms the occurrence of the 194 above mentioned phases in selected sample particles. Titanium, tin, tantalum, niobium and iron 195 oxides were also revealed by SEM-EDS analysis. It should be noted that their phase content is 196 low to be detected by usual XRD analysis. The thermal treatment of the KW resulted into the 197 decrease of the peaks intensity of kaolinite with an increase of the temperature; in addition, 198 typical peaks of kaolinite disappeared for the temperature higher than 600°C. Higher 199 temperatures (approaching 1000°C) are required for breakage-down of muscovite/illite (micas) 200 structure (Fig. 4b). The characteristic peaks of the schorl phase are no more detected beyond 201 900°C. Note that schorl appeared as a minor phase even in the initial KW sample. Products 202 obtained at temperatures exceeding 900°C are mostly composed of feldspar and quartz. 203

As shown by Fig. 5, the IR spectrum of KW raw sample exhibits the bands near the three characteristic bands at 3696, 3652 and 3620 cm<sup>-1</sup> that can be attributed to [Al-O-H] stretching of disordered kaolinite. More precisely, the last band is characteristic of inner hydroxyls, while the two first ones are assigned to vibrations of external hydroxyls. The bands close to 3620 cm<sup>-1</sup> could also be assigned to the hydroxyl vibrations in the muscovite and illite and they overlap due to the similarities of Al-OH bond of these two minerals.

As presented in Fig. 5, the IR spectra of the KW treated at various temperatures can be classified in three groups depending on the temperature: (i) from 300°C to 600°C; (ii) between 700°C and 900°C and (iii) 1000°C-1200°C. By combining the results of ML versus temperature (Fig. 3a) with XRD (Fig. 4) and IR and results, one may conclude that quasi-full dehydroxylation of kaolinite contained in the KW is achieved at about 600°C for 30 minutes. Similar findings were reported early (Gasparini et al., 2013).

216

#### 217 3.2.2 Sewage sludge

Results of the above mentioned analysis upon the initial sewage sludge sample confirms the multiphase nature of this material. Figs. 6 and 7 represent, respectively, the XRD and IR analysis results of the products generated during heating of the sewage sludge. The mineral composition of the initial SS sample represents a mixture of micas, kaolinite, feldspar, anhydrite (CaSO<sub>4</sub>), quartz and calcite. Besides the characteristic bands ascribed to kaolinite, muscovite/illite, carbonate and quartz prevailed in the raw sample, the IR measurement confirms the presence of the organic matter (Fig. 7a).

Gathering the data displayed in Figs 3b, 6 and 7 allowed the explication of the SS thermal behaviors. The thermal treatment under 300°C led to destabilization/destruction of organic matter as indicated by the absence of the absorbance bands at 2820-2959 cm<sup>-1</sup> attributed to diverse C-H stretching (Fig. 7). The dehydroxylation of the silico-aluminates is shifted towards low temperatures compared with kaolinitic waste. This is probably due to the fine particle size of
sewage sludge as well as the exothermic nature of the reaction of organic matter with oxygen.
The plateau of the mass loss observed during treatment of the sample at around 550°C (Fig. 3b)
confirms an almost full reaction of hydrocarbons with oxygen and a complete removal of the
structural kaolinite water at temperatures lower than or equal to 500°C.

Decomposition of carbonates (CaCO<sub>3</sub> according to XRD, Fig. 6b) generating carbon dioxide is the major occurred transformation. The doublet band at 2340-2349 cm<sup>-1</sup> (Fig. 7b) is assigned to gaseous CO<sub>2</sub>. One may speculate that the evolved CO<sub>2</sub> is trapped in the soften glass creating closed micropores. This hypothesis is confirmed by the fact that the product obtained at 1150°C is free of CO<sub>2</sub> as it is fully melted leading to the carbon dioxide escape. Further, the remove of the CO<sub>2</sub>, involved and trapped in the porous SS product at medium temperature, may provoke the ML% observed at temperatures higher than 950°C.

These deduced observations show that the decomposition of carbonates guarantees one of the 241 necessary conditions for the thermal expansion of the materials. While, the presence of 242 phosphorous and potassium compounds (confirmed by SEM-EDS results) resulting in the 243 apparition of the liquid phase at relatively low temperatures which may be converted into 244 amorphous glass during cooling. The XRD patterns at high temperatures (Fig. 6b) showed neo-245 formed phases difficult to be identified (e.g. d = 5.18 Å) and some other ones belonging 246 probably to pyroxene group. However, the quartz, anhydrite and feldspar remain the major 247 crystallized phases of the sewage sludge sample treated at temperatures higher than 800°C. 248

249

#### 250 *3.2.3 Schist fines*

A schist fines sample was also subjected to thermal treatment under air atmosphere up to 1200°C. As in the previous cases, the elemental and mineralogical evolution as a function of the temperature was followed by above-mentioned analysis methods. Many of the obtained results are summarized in Figs. 8 and 9. According to the XRD patterns traced in Fig. 8a, the crystalline phases of the raw SF sample are chlorite, muscovite/illite (micas), kaolinite as well as feldspar and quartz. As indicated in Fig. 9a, the exhibited bands around 3559 and 3417 cm<sup>-1</sup> can be attributed to (AlFe)O-OH and (MgAl)O-OH stretching, respectively, of fired kaolinite and chlorite with a general formula  $[Mg_{(6-x-y)} Al_x Fe_y Si_{(4-x)} Al_xO_{10}(OH)_8]$ . Further, the absorption spectra of the OH region presented the overlapping of an absorption band at around 3622 cm<sup>-1</sup> by muscovite and illite.

Heating the SF sample leads to the dehydroxylation of kaolinite at T < 650 °C. The structure of 261 the hydroxide sheet of the present chlorite seems to be stable up to 775°C where the total 262 volatilisation of its structural is achieved. Peak intensity of the muscovite/illite phase decreased 263 with temperature and the peak signal of these compounds is absent in the diffractogram obtained 264 at T > 950°C. Further heating (especially at 1200°C) provokes the formation of partial liquid 265 phase converted into glass during sample quenching in air. Besides quartz, the characteristic 266 peaks of the spinel-like structure of the neo-formed hercynite (FeAl<sub>2</sub>O<sub>4</sub>) were revealed by XRD 267 in the schist product heated at 1200°C. 268

269

#### 270 *3.2.4 Wasted glass*

As already shown in Fig. 3c, the powdered wasted glass sample is heated at different temperatures for 30 minutes. Reminder that the sample was brought directly in the heated zone of the furnace and after reaching the fixed dwelling time, the sample is cooled in air to room temperature.

It was quite interesting to follow the mineralogical and morphological evolution of the WG thermal treatment products at various temperatures. The XRD patterns are grouped in Fig. 10. The initial WG diffractogram exhibits a broad diffraction band near to 27° (2θ) indicating the XRD amorphous nature of the waste glass sample. The well-defined reflection at 3.24 Å

probably corresponds to a crystallized organic material since it disappears at low temperature. As 279 shown by Fig. 10, the crystallization of WG started from temperatures higher than 600°C. This 280 phenomenon, known as glass devitrification, occurs beyond the glass transition temperature 281 282 which oscillates between 520°C and 600°C for the classical soda-lime-silica glasses. The first phase to be crystallized seems to be the quartz which remains predominant phase up to 900°C. 283 Typical peaks of plagioclase (series of solid solution between albite-NaAlSi<sub>3</sub>O<sub>8</sub> and anorthite-284 CaAl<sub>2</sub>Si<sub>2</sub>O<sub>8</sub> end-members) and wollastonite (CaSiO<sub>3</sub>) appeared in the diffractograms of samples 285 heated at temperature higher than 800°C. These components become the main crystallized 286 phases at 1000°C which is evaluated to be lesser than the liquidus temperature of the used soda-287 288 lime-silica glass, while the main phase of the WG treated at 1050°C is quartz. Further heating, at 1100°C, led to a product slightly crystallised with low intensity peaks of quartz. 289

Several WG thermal treatment samples were subjected to SEM/EDS examination. The cross 290 sections of the fired samples at 850°C and 950°C are given in Fig. 11. A bright star-like shaped 291 phase into the glassy matrix appeared in the SEM micrograph of the sample obtained at 850°C 292 293 (Fig. 11a). The morphology of the neo-formed crystalline phase is affected by the temperature and as shown in Fig. 11b, the needle-like crystals are abundant for the WG treated at 950°C. The 294 higher magnification of the SEM images gathered with the EDS results for both the samples are 295 displayed in Fig. 12. The oxides contents of two kinds of crystals seem to roughly confirm the 296 chemical composition of wollastonite. Other results acquired by SEM-EDS analysis indicate the 297 presence of neo-formed and well-developed particles having the typical composition of 298 plagioclase (Fig. 13a) and quartz (Fig. 13b). 299

Similar findings have been described in the literature during glass devitrification and glassceramic synthesis. Teixeira et al. (2014) reported the wollastonite formation during the production of the glass-ceramic material at temperatures lower than 900°C. Another investigation (Yoon et al., 2013) revealed that the most appropriate temperature to produce

wollastonite glass-ceramics containing acicular type crystalline phase with good mechanical
property was between 1000°C and 1050°C.

306 One may note that the nature, the amount and the shape of the crystalline phases are related 307 especially to the composition of starting materials, crystallization temperature and time, heating 308 and cooling rates as well as the presence of nucleation agents.

309

#### 310 **3.3 Thermal expansion of granulates**

The above mentioned results gave general information about the elemental and mineralogical 311 transformation occurring during the thermal treatment of the selected waste samples. They 312 permit to establish an experimental procedure for the production of lightweight granulates 313 starting by these waste materials. Various mixtures based on the binary and ternary formulations 314 315 were tested for thermal expansion purpose. Some preliminary results of the work performed are described previously (Kanari et al., 2010). A comparison view of green granulates and those 316 thermally treated under different conditions for the previously formulated mixtures (Table 1) is 317 shown in Fig. 14. The bloating temperatures ranged from 1050°C and 1100°C for the firing 318 times at 10 and 15 minutes. A substantial difference between green and expanded granulates is 319 320 obvious whichever mixture is used for the thermal expansion. Further, the cross-section of the expanded granulates shows mostly two distinct zones i.e. the shell and the core of granulates. 321 Their macro-morphology roughly demonstrates the principle of the thermal expansion 322 mechanism linked to the formation of a sealed coat (the dense outside layer) trapping gases 323 leading to the pore formation (gas-filled porous inner zone) during firing. 324

A typical microstructure of the obtained lightweight granulates is given in Fig. 15a. Various size pores (black zones) of rounded shape are obvious from the image. They are mostly enveloped by a vitreous matrix composed of Si, Ca, Al, K, Na oxides. However, the EDS spectra revealed the presence of some heavy metal bearing compounds in the expanded granulates. For instance, the

bright spots of Fig. 15a are typically composed of copper and iron sulfides (Fig. 15b) originating from the sewage sludge. Other heavy metals (Cr, Zn) are stabilized in the spinel phase of the expanded granulates (Kanari et al., 2010). Nevertheless, the SEM-EDS analysis of the obtained condensates showed the presence of Zn and Pb compounds indicating their partial volatilization during bloating process.

The aforementioned expanded mixtures were examined by XRD analysis and the obtained 334 diffractograms displayed in Fig. 16 are of particular interest. Besides guartz, feldspar and 335 anhydrite, they show the presence of the wollastonite phase in all expanded mixtures containing 336 wasted glass (M2, M3, M4) although the expansion temperature is between 1050°C and 1100°C. 337 Reminder that during the thermal treatment of wasted glass alone (section 3.2.4), the 338 wollastonite was not detected at temperatures higher than 1000°C. One may speculate that in the 339 case of the granulate expansion, the wollastonite nucleation is promoted by the presence of inert 340 phases, such as TiO<sub>2</sub>, known as nucleating agent during glass-ceramic synthesis. Note that the 341 titanium oxide is present in the starting materials (KW, SS and SF). Examination of the 342 343 lightweight granulates (M3 expanded at 1050°C) by SEM-EDS indicated the growth of whiskers-like shape (Fig. 17a) with a rough chemical composition (Fig. 17b) corresponding to 344 wollastonite embedded in a glassy matrix (Fig. 17c). It should be noted that the presence of such 345 compounds will improve the flexural strength of the expanded granulates. 346

347 The decrease of the expansion temperature is a function of the wasted glass amount in the granulate formulation. The soda-lime-silica glass acts as a flux for the granulates by lowering 348 their softening temperature (see Fig. 1). As shown before, experimental tests using mixture 349 designed as M3 (40% KW + 20% SS + 40% WG) showed a good thermal expansion of the 350 formulated granulates at 1050°C, which is 50°C lower than that employed for the expansion of 351 M4 (50% KW + 20% SS + 30% WG). Preliminary examination of several physical properties of 352 the obtained lightweight granulates showed that expanded M3 product had an apparent density of 353  $0.69 \text{ g/cm}^3$  and it is characterized by the water absorption coefficient of 14.8%. The granulates 354

obtained during thermal expansion of M1 at 1100°C have a real density close to unity and a compressive strength of 4.9 MPa which is comparable with those obtained for natural granulates based on schist, allowing their use as building materials. More detailed data related to the obtained lightweight granulates will be developed in the forthcoming studies.

359

## 360 **4. Conclusions**

361 Thermal treatments of individual wasted materials as well as the thermal expansion of theirs362 mixtures allow the following conclusions:

- The main phases of the kaolinitic waste are: micas, feldspar, kaolinite, schorl and quartz. Thermal treatment of the samples showed the dehydration/decomposition of the kaolin at temperatures lower than 650°C, whilst, the muscovite and other sheet silicates are broken down at around 1000°C resulting in quartz and refractory feldspar as well crystallized phases at 1200°C.
- 368
   2. At least two steps are observed during thermal treatment of the sewage sludge in air.
   369 The decomposition and/or combustion of the organic matter as well as the clay
   370 dehydroxylation occurred at temperatures lower than 650°C. The calcite decomposition
   371 into CaO proceeds at higher temperatures involving carbon dioxide.
- 372 3. Complete dehydroxylation of the chlorite contained in the schist sample is achieved at
  373 temperatures lower than or equal to 775°C. The thermal behaviors of other schist phases
  374 (kaolinite, muscovite, illite, feldspar) are similar to those observed for the kaolinitic
  375 waste.
- 4. The thermal treatment of the wasted glass led to the partial glass devitrification at
  temperatures higher than 700°C. Quartz, plagioclase and wollastonite are identified as
  the main neo-formed crystalline phases. The wollastonite needle-like structure is

considered as a suitable candidate for improving the strength of the fired product.

- 5. Results of the thermal expansion showed the possibility to manufacture the lightweight granulates at temperatures between 1050°C and 1100°C by using only residual materials. It may be stated that the optimal expansion temperature depends on the glass and sewage sludge contents of the prepared mixtures.
- 384
  6. The resulting granulates are lightweight and they have a good mechanical strength
  385 meeting the conditions for their use as building materials. Other application fields are
  386 road engineering, water treatment and hydroponic agriculture.

This study investigates the possibility of using a wide spectrum of secondary raw materials for synthesizing lightweight granulates by thermochemical transformation. Results so far indicate the potential to achieve sustainable mining and processing as well as resource efficiency principles of maximizing yields.

391

#### 392 Acknowledgements

The present work was performed in the frame of the European Union contract (n° 310645) 'Sustainable Technologies for Calcined Industrial Minerals' (STOICISM), part of the European seventh framework programme for research (FP7). Another part was supported by the French National Research Agency 'ANR' Project-EXPANTHERM, through contract n° ANR-06-ECOT-010. A last part was supported by Bourgogne innovation 'Prestation Technologique de Réseau: Préparation par voie thermique de matériaux expansés légers destinés aux murs végétalisés', n° PTRCRB1111-059. The authors thank these institutions for financial supports.

400

#### 401 **References**

402 Chandra, S., Berntsson, L., 2002. Lightweight Aggregate Concrete, Noyes Publications, New
403 York, USA.

- Chen, H.J., Wang, S.H., Tang, C.W., 2010. Reuse of incineration fly ashes and reaction ashes for
  manufacturing lightweight aggregate. Construct. Build. Mater. 24, 46-55.
- Farmer, V.C., 1979. Infrared spectroscopy, in: van Olphen, H., Fripiat, J.J. (Eds.), Data
  Handbook for Clay Materials and other Non-metallic Minerals. Pergamon Press, Oxford,
  285-337.
- 409 Gasparini, E., Tarantino, S. C., Ghigna, P., Riccardi, M., P., Cedillo-González, E. I., Siligardi, C.,
- Zema, M., 2013. Thermal dehydroxylation of kaolinite under isothermal conditions. Appl.
  Clay Sci. 80-81, 417-425.
- González-Corrochano, B., Alonso-Azcárate, J., Rodas, M., 2014. Effect of prefiring and firing
  dwell times on the properties of artificial lightweight aggregates. Construct. Build. Mater.
  52, 91-101.
- Kanari, N., Banse, J., Joussemet, R., Diot, F., Allain, E., Yvon, J., Faure, F.X., Sevèque, J.L.,
  Chambard, J.P., 2010. Synthesis of thermal expanded lightweight granulates incorporating
  wastes as raw materials. Proceedings of the XVIII<sup>th</sup> International scientific and professionnal
  meeting "Ecological Truth" EcoIst'10. 1-4 June 2010, Apatin, Serbia, Edited by Zoran S.
  Markovic, pp. 458-465.
- Levin, E.M., Robbins, C.R., McMurdie, H.F., 1964. Phase Diagrams for Ceramists, Vol. 1,
  American Ceramic Society, Columbus, OH, p. 94.
- Monteiro, S.N., Vieira, C.M.F., 2014. On the production of fired clay bricks from waste
  materials: A critical update. Constr. Build. Mater. 68, 599-610.
- Quina, M.J., Almeida, M.A., Santos, R., Bordado, J.M., Quinta-Ferreira, R.M., 2014.
  Compatibility analysis of municipal solid waste incineration residues and clay for producing
  lightweight aggregates. Appl. Clay Sci. 102, 71-80.
- 427 Teixeira, S.R., Magalhães, R.S., Arenales, A., Souza, A.E., Romero, M., Rincón, J.M., 2014.
  428 Valorization of sugarcane bagasse ash: Producing glass-ceramic materials. J. Environ.
  429 Manage. 134, 15-19.

- Wei, Y-L, Yang, J-C, Lin, Y-Y, Chuang, S-Y, Wang, H.P., 2008. Recycling of harbor sediment
  as lightweight aggregate. Mar. Pollut. Bull. 57, 867-872.
- Xu, G., Liu, M., Li, G, 2013. Stabilization of heavy metals in lightweight aggregate made from
  sewage sludge and river sediment. J. Hazard. Mater. 260, 74-81.
- 434 Yoon, S.D., Lee, J.U., Lee, J.H., Yun, Y.H., Yoon, W.J., 2013. Characterization of wollastonite
- glass-ceramics made from waste glass and coal fly ash. J. Mater. Sci. Technol. 29(2) 149-153.
- Zhang, L., 2013. Production of bricks from waste materials a review. Constr. Build. Mater. 47,
  643-655.
- 439

# 440 FIGURE CAPTIONS

441	Fig.	1	:	Phase diagram for Na <sub>2</sub> O-SiO <sub>2</sub> system, adapted from Levin et al. (1964).
442 443	Fig.	2	:	Fig. 2. Morphological aspects of the initial samples and their oxide contents for: (a) kaolinitic waste; (b) sewage sludge; (c) schist fines; (d) wasted glass.
444 445 446	Fig.	3	:	Evolution of sample mass loss as a function of temperature for: (a) kaolinitic waste; (b) sewage sludge; (c) schist fines and wasted glass during their isothermal treatment at 30 minutes.
447 448	Fig.	4	:	XRD diagrams of the solid products issued from the thermal treatment of the kaolinitic waste sample up to 600°C ( <i>a</i> ) and from 700°C to 1200°C ( <i>b</i> ).
449 450	Fig.	5	:	IR spectra (DRIFTS) of the solid products issued from the thermal treatment of the kaolinitic waste sample at different temperatures.
451 452	Fig.	6	:	XRD diagrams of the solid products issued from the thermal treatment of the sewage sludge sample up to 650°C ( <i>a</i> ) and from 750°C to 1150°C ( <i>b</i> ).
453 454	Fig.	7	:	IR spectra (DRIFTS) of the solid products issued from the thermal treatment of the sewage sludge sample up to 550°C ( <i>a</i> ) and from 650°C to 1150°C ( <i>b</i> ).
455 456	Fig.	8	:	XRD diffractograms of the solid products issued from the thermal treatment of the schist sample between 200°C and 650°C ( <i>a</i> ) and from 750°C to 1200°C ( <i>b</i> ).
457 458	Fig.	9	:	IR spectra (DRIFTS) of the solid products issued from the thermal treatment of the schist sample up to 650°C ( <i>a</i> ) and from 750°C to 1200°C ( <i>b</i> ).
459 460	Fig.	10	:	XRD diffractograms of the solid products issued from the thermal treatment of the wasted glass sample between 400°C and 1100°C.
461	Fig.	11	:	Cross section of the wasted glass sample heated at 850°C (a) and 950°C (b).
462 463	Fig.	12	:	SEM-EDS results of the wollastonite like crystals obtained during thermal treatment of the wasted glass sample at 850°C ( <i>a</i> ) and 950°C ( <i>b</i> ).
464 465	Fig.	13	:	SEM-EDS results of plagioclase (a) and quartz (b) particles obtained during thermal treatment of the wasted glass sample at 850°C.
466	Fig.	14	:	Photographs of green and expanded granulates for M1 (a), M2 (b), M3 (c) and M4 (d).
467	Fig.	15	:	SEM image of the expanded M3 at 1050°C (a) and elemental composition of bright spots (b).
468	Fig.	16	:	XRD diffractograms of the thermally expanded granulates.
469 470	Fig.	17	:	SEM-EDS results of the M3 expanded at 1050°C displaying: (a) morphologic aspects; (b) elemental composition of the 'whiskers'; (c) elemental composition of the matrix.
471				



Fig. 1. Phase diagram for Na<sub>2</sub>O-SiO<sub>2</sub> system, adapted from Levin et al. (1964).



Fig. 2. Morphological aspects of the initial samples and their oxide contents for: (a) kaolinitic
waste; (b) sewage sludge; (c) schist fines; (d) wasted glass.





### Fig. 3.

Evolution of sample mass loss as a function of temperature for: (a) kaolinitic waste; (b) sewage sludge; (c) schist fines and wasted glass during their isothermal treatment at 30 minutes.



Fig. 4. XRD diagrams of the solid products issued from the thermal treatment of the kaolinitic waste sample up to 600°C (*a*) and from 700°C to 1200°C (*b*).



Fig. 5. IR spectra (DRIFTS) of the solid products issued from the thermal treatment of the kaolinitic waste sample at different temperatures.



- 5/5





Fig. 7. IR spectra (DRIFTS) of the solid products issued from the thermal treatment of the sewage sludge sample up to 550°C (*a*) and from 650°C to 1150°C (*b*).



Fig. 8. XRD diffractograms of the solid products issued from the thermal treatment of the schist sample between 200°C and 650°C (*a*) and from 750°C to 1200°C (*b*).





Fig. 10. XRD diffractograms of the solid products issued from the thermal treatment of the wasted glass sample between 400°C and 1100°C.















Fig. 16. XRD diffractograms of the thermally expanded granulates.







## Fig. 17.

SEM-EDS results of the M3 expanded at 1050°C displaying: (*a*) morphologic aspects; (*b*) elemental composition of the 'whiskers'; (*c*) elemental composition of the matrix.