



HAL
open science

Coarsening Kinetic of Aluminium-Scandium and Aluminium-Zirconium-Scandium Precipitates

J. Boisse, N. Lecoq, Helena Zapolsky, Renaud Patte

► **To cite this version:**

J. Boisse, N. Lecoq, Helena Zapolsky, Renaud Patte. Coarsening Kinetic of Aluminium-Scandium and Aluminium-Zirconium-Scandium Precipitates. 11th International Conference on Aluminium Alloys (ICAA'11), Sep 2008, Aachen, Germany. hal-01486150

HAL Id: hal-01486150

<https://hal.univ-lorraine.fr/hal-01486150v1>

Submitted on 9 Mar 2017

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

ICAA'11, Aachen, September 2008

Aluminium Alloys : Their Physical and Mechanical Properties

Edited by J. Hirsch, B. Skrotzki and G. Gottstein

Wiley-VCH GmbH & Co. KgaA, 2008

Coarsening Kinetic of Aluminium-Scandium and Aluminium-Zirconium-Scandium Precipitates

N. Lecoq(Sp), J. Boisse, R. Patte and H. Zapolsky

GPM, UMR 6634 CNRS, University of Rouen, Avenue de l'Université, BP 12, 76801 Saint-Etienne du Rouvray (France)

1 Introduction

Al-Sc-based alloys exhibit a unique combination of high strength and plasticity, corrosion resistance and weldability [1-4]. Mechanical properties of these alloys depend on their microstructure and their phase composition, so its knowledge provides an opportunity to improve material properties by thermal treatment. The addition of Sc to aluminium is a very effective mean to form small ordered L_{12} precipitates which increase the tensile strength and inhibit recrystallisation.. Recently it was demonstrated that these precipitates remain coherent up to sizes of. 40 nm in diameter [1]. To further improve the properties of Al-Sc alloys, the effects of ternary additions to Al-Sc alloys have been investigated [5]. Previous studies have shown that addition of Zr in Al-Sc alloys improve the stability these systems to coarsening [20-21]. It was determined that Zr segregates to the α -Al/Al₃Sc heterophase interface and acts as a barrier for the diffusion of Sc across the interface, which leads to a lowering of the coarsening rate [22-23] as compared to binary Al-Sc alloys. Harada and Dunand [7] shown that zirconium addition reduces the lattice parameter of Al₃Sc and concomitantly the interface free and elastic strain energies.

The purpose of this work is to study the microstructural evolution in binary Al-Sc and in ternary Al-Sc-Zr alloys. Phase field approach based on the Cahn-Hilliard and Ginzburg-Landau equations [12-18] has been used. It is shown that L_{12} particles have a heterogeneous structure with the Al₃Sc core surrounded by a Zr-rich shell .

2 Model description

2.1 Phase field model.

Phase field model has been extensively used for microstructure simulation studies because of its ability to reproduce complicated microstructures without any *a priori* assumptions

ICAA'11, Aachen, September 2008

Aluminium Alloys : Their Physical and Mechanical Properties

Edited by J. Hirsch, B. Skrotzki and G. Gottstein

Wiley-VCH GmbH & Co. KgaA, 2008

[12-14]. We consider a model for two-phase system, in which parent phase has a disordered fcc structure and the precipitates have the four variants ordered L1₂ structure. In this case the kinetic equations that describe the temporal evolution of the composition variable $c(\mathbf{r}, t)$ and the long range order parameters $\eta(\mathbf{r}, t)$ are:

$$\frac{\partial c(\mathbf{r}, t)}{\partial t} = \nabla M(\mathbf{r}, t) \nabla \left(\frac{\partial F}{\partial c(\mathbf{r}, t)} \right) + \xi \quad (1a)$$

$$\frac{\partial \eta_i(\mathbf{r}, t)}{\partial t} = -L \frac{\partial F}{\partial \eta_i(\mathbf{r}, t)} + \zeta_i \quad i=1, 2, 3 \quad (1b)$$

where L and M are kinetic coefficients, F is a total non-equilibrium free energy functional, ξ and ζ are the Langevin's noise terms describing the compositional and structural thermal fluctuations, respectively.

The total free energy of the system consists of the bulk free energy, the interfacial energy and the elastic energy E_{el} . Assuming an isotropic interfacial energy, the chemical energy F_{ch} in the diffuse-interface description can be written as:

$$F_{ch} = \int_V (f(c, \eta_j) + \frac{\alpha}{2} (\nabla c)^2 + \frac{\beta}{2} \sum_{j=1}^3 (\nabla \eta_j)^2) dV \quad (2)$$

where α and β are gradient energy coefficients, f is the local free energy density which can be expressed in Landau polynomial form; in the case of ternary systems it take the following form :

$$f(c_a, c_b, \eta_1, \eta_2, \eta_3) = \frac{1}{2} A_1 (c_a + c_b - c_1)^2 + \frac{1}{2} A_2 (c_2 - c_a - c_b) \sum_{p=1}^3 \eta_p^2 + \frac{1}{3} A_3 \eta_1 \eta_2 \eta_3 + \frac{1}{4} A_4 \sum_{p=1}^3 \eta_p^4 + \frac{1}{4} A_5 (\eta_1^2 \eta_2^2 + \eta_1^2 \eta_3^2 + \eta_2^2 \eta_3^2) \quad (4)$$

where c_a and c_b are the composition variables of scandium and zirconium atoms, c_1 et c_2 are constants with values close to the equilibrium compositions of the matrix and precipitates, respectively and A_i s are constants for the given temperature. The coefficients and constants were chosen such that the free energy curve provides a qualitative description of the thermodynamics of the Al-Sc and Al-Sc-Zr system at 375°C, with the constraint that for the disorder-order phase transition to be first ordered, A_3 must be non-zero.

Khachatryan's model [13] is used for the description of elastic energy arising from the lattice misfit, with a homogeneous modulus approximation. In our calculations we assumed that the lattice parameter a_γ and a_α of the disordered and ordered phases, respectively, has a linear dependence on solute composition (Vegard's law).

The kinetic coefficient M in equation (1a) corresponds to the chemical mobility of elements in alloys. In many cases, for simplicity, the chemical mobility is assumed to be constant and is calculated on the average concentrations in the system. But in facts, M is related to the atomic motilities β_{Sc} and β_{Al} of each system's elements and is defined in the lattice refer-

ICAA'11, Aachen, September 2008

Aluminium Alloys : Their Physical and Mechanical Properties

Edited by J. Hirsch, B. Skrotzki and G. Gottstein

Wiley-VCH GmbH & Co. KgaA, 2008

ence frame as a composition and temperature-dependent function. In the case of an Al-Sc binary alloy the chemical mobility can be expressed by the following equation:

$$M = c_{Sc}(1 - c_{Sc})[(1 - c_{Sc})\beta_{Sc} + c_{Sc}\beta_{Al}] \quad (5)$$

where c_{Sc} is the mole fraction of Sc. The atomic mobility β_i of species i can be written as:

$$\beta_i = D_i \exp(-Q_i / RT) \quad (6)$$

where R is the gas constant, D_i and Q_i are diffusion factor and diffusion activation energy of species i in the disordered phase. These two constants can be generally obtained from atomic mobility databases.

There is not enough experimental databases for atomic mobilities for ternary Al-Sc-Zr system, this is why in our simulation we chose constant mobility for Zr and Sc atoms for ternary alloys. However, we took into account that at 375°C Zr diffuse 100 times slowly than Sc atoms in Al.

In addition, in our model, we also integrated the concentration dependence of misfit between two coexisting phases.

3 Numerical simulations and results.

Simulations were performed by numerically solving the four nonlinear equations (1a) and (1b), one for each field variable, using the semi-implicit Fourier-Spectral method [18]. In 3D computer simulations, 128^3 discrete grid points are used and periodic boundary conditions are applied. The initial state was a homogeneous solution with small composition fluctuations around the average composition. The Langevin's noises were introduced during the beginning of each simulation to ensure the nucleation of small precipitates. Particles with a radius greater than the critical nucleation radius can then grow. Approximately one thousand particles were formed during the nucleation stage. The precipitate microstructure and coarsening kinetics were then extracted from the simulation results, which were averaged over five simulation runs with different initial randomized Langevin's noises.

The parameter ε_0 used in the elastic energy term may be estimated from the γ/γ' lattice misfit,

$$\frac{a_{\gamma'} - a_{\gamma}}{a_{\gamma}} \approx 0.0098$$

and a_{γ} at 375°C [10]. If Vegard's law for the misfit is assumed, at this temperature $c_{\gamma} = 0.0001$ and $c_{\gamma'} = 0.25$, the estimation for ε_0 gives 0.039.

To determine the influence of the volume fractions of Al_3Sc precipitates on the coarsening rate and on the microstructure, three alloys with different volume fraction of the $L1_2$ phase, 0.35, 0.39 and 0.42, were studied. Therefore, for each alloy, two kinds of simulations were performed : with and without concentration dependent atomic mobilities.

Figure 1 show the morphological evolution of $L1_2$ ordered precipitates. We can conclude that including the concentration dependence mobility doesn't induce large influence on the morphology of microstructure in Al-Sc binary alloys. However, our statistical analyze of

ICAA'11, Aachen, September 2008

Aluminium Alloys : Their Physical and Mechanical Properties

Edited by J. Hirsch, B. Skrotzki and G. Gottstein

Wiley-VCH GmbH & Co. KgaA, 2008

temporal evolution for the mean radius of precipitates indicates differences between these two simulations.




Figure 1: Temporal microstructural evolution for Al-Sc alloys during coarsening for different reduced time t with : (a-c) constant atomic mobility ; (d-f) concentration dependent atomic mobility. The coherent ordered Al_3Sc precipitates are shown in white, the matrix is transparent.




Figure 2: $\langle R \rangle^3$ versus reduced time step for different concentrations and for constant and concentration dependent atomic mobilities. Solid lines are linear fits of the data from the simulations.

ICAA'11, Aachen, September 2008

Aluminium Alloys : Their Physical and Mechanical Properties

Edited by J. Hirsch, B. Skrotzki and G. Gottstein

Wiley-VCH GmbH & Co. KgaA, 2008

We find that the cubic growth law provides reasonably good fits in all cases. It is apparent in figure 2 that the slope of the curves, i.e. the value of the coarsening rate constant K , increases with increasing volume fraction which is also in good agreement with experimental data. This behavior was predicted in the modified LSW theory proposed by Ma and Ardell [16]. But, we observe that coarsening rate in the case of simulations with concentration dependent mobility is smaller than with constant mobility for each volume fraction. It can be understood by the fact that during growth and coarsening of precipitates, atomic mobility decreases with the decrease of Sc atomic concentration in the matrix.

Dealing with the Al-Sc-Zr alloys, it was demonstrated that the ordered Al_3Sc particles appear firstly and exhibit a cuboidal shape which is result of the minimization of strain energy (figure 3). The Zr atoms diffuse slowly and precipitate on the interface between matrix and Al_3Sc particles. The main effect is due to the strain energy and not on the diffusion velocities of the components.

Figure 4 is shown the influence of misfit dependent of concentration. On the later case, precipitates are smaller, zirconium forms shells around the Sc rich cores to minimize the strain energy and blocks the coarsening of Al_3Sc precipitates.




Figure 3. Microstructural evolution from 3D simulation at reduced time $t^*=10000$, showing the heterogeneous structure of γ' precipitates in a γ (transparent) disordered matrix. Left : Iso-concentration of Al_3Sc (yellow); Right : Zr rich-shell (blue) surrounding the previous Al_3Sc precipitates.

ICAA'11, Aachen, September 2008

Aluminium Alloys : Their Physical and Mechanical Properties

Edited by J. Hirsch, B. Skrotzki and G. Gottstein

Wiley-VCH GmbH & Co. KgaA, 2008




Figure 4. Microstructural evolution from 3D simulation at reduced time $t^*=10000$, showing the heterogeneous structure of γ' precipitates in a γ (transparent) disordered matrix. Left : without the misfit dependent of concentration; Right : misfit depends on concentration.

The precipitation of $Al_3(Sc,Zr)$ particles has been successfully studied by means of transmission electron microscopy [24] and 3D atom probe analysis [20-24]. It has been shown that ordered precipitates contain a Sc-rich core and a Zr enriched outer shell. These works confirm the hypothesis of an intense initial precipitation of Al_3Sc nuclei, favored by the fast Sc-diffusion rate, followed by later Zr segregation. Our simulation results are in very good agreements with these experimental data.

5 Conclusion.

Our simulation show that phase field model can successfully reproduce the microstructural evolution in binary and ternary system. The concentration dependence of atomic mobility and misfit was integrated in our calculations. It was shown that elastic interaction is responsible to heterogeneous structure of $L1_2$ precipitates in Al-Sc-Zr alloys.

Acknowledgements

The simulations were performed at the CRIHAN center under project 2006007.

ICAA'11, Aachen, September 2008

Aluminium Alloys : Their Physical and Mechanical Properties

Edited by J. Hirsch, B. Skrotzki and G. Gottstein

Wiley-VCH GmbH & Co. KgaA, 2008

5 References

- [1] E.A. Marquis and D.N. Seidman *Acta Mater.* **2001**, 49, 1909-1919.
- [2] D.N. Seidman, E.A. Marquis, D.C. Dunand, *Acta Mater.* **2002**, 50, 4021–4035.
- [3] E.A. Marquis, D.N. Seidman, D.C. Dunand, *Acta Mater.* **2003**, 51, 4751–4760.
- [4] C. Sigli, *Mater Forum*, **2004**, 28, 1353-1358.
- [5] Royset J., Ryum N., Bettella D., Tocco A., Jia Z., Solberg J.K., Reiso O., *Materials Science and Engineering*: **2008**, 483-484, 14th International Conference on the Strength of Materials, 175-178.
- [6] Toporova L.S., Kamardinkin A.N., Kindzhibalo V.V., Tyvanchuk A.T., 1990 *Phys Met Metal*, **70**, 106.
- [7] Harada Y. And Dunand D.C., **2002. Mater. Sci. Eng. A** **329-331**, 686-695.
- [8] Fujikawa S.I., Sugaya M., Takei H. and Hirano K.I. *J Less-common Met* 1979; **63**:87.
- [9] Hirano K.I and Fujikawa S.I. *J. Nucl Mater* 1978;**69-70**:564.
- [10] Marquis E.A. and Seidman D.N. *Acta Mater* 2001; **49**:1909.
- [11] Hyland R.W. *Metall Trans A* 1992; **23 A**:1947.
- [12] Wang Y., Banerjee D., Su C.C.; Khachaturyan A.G., *Acta Mater.*, **1998**, 46, 2983-3001.
- [13] Khachaturyan A.G., *Theory of structural transformations in solids. (John Wiley, New York)* **1983**.
- [14] L. Q. Chen and A. G. Khachaturyan, *Acta Metal. Mat*, 1991. **39**(11): p. 2533-2551.
- [15] L. Q. Chen, *Annual Review of Materials Research*, **2002. 32**: p. 113-140
- [16] J. Boisse, N. Lecoq, R. Patte and H. Zapolsky, *Acta. Mat.* **2007.55**, n18, 6151-6158.
- [17] Vaithyanathan V., Chen L.Q., *Acta Mater.*, **2002**, 50, 4061-4073.
- [18] Chen L.Q., Shen J., *J. Comp. Phys. Comm.*, **1998**, 108-147.
- [19] Ma Y. and Ardell A.J. *Acta Materialia*, **2007**, 55, Issue 13, 4419-4427
- [20] Fuller C.B., Seidman D.N. and Dunand D.C. *Acta Mater.*, **2003**. 51, 4803-4814.
- [21] Forbord B., Lefebvre W., Danoix F., Hallem H., Marthinsen K., *Scripta Materialia*, **2004**. 51, 333-337.
- [22] Fuller C.B., Murray J.L., and Seidman D.N., *Acta Mater.* **2005**. 53:5401.
- [23] Fuller C.B., and Seidman D.N., *Acta Mater.* **2005**; 53:5415.
- [24] Tolley A., Radmilovic V. and Dahmen U., *Scripta Materialia* **2005**, 52, Issue 7, 621-625.