

FTIR spectroscopy and X-ray powder diffraction characterization of microcrystalline cellulose obtained from alfa fibers

D. Trache, K. Khimeche, A. Donnot, R. Benelmir

► **To cite this version:**

D. Trache, K. Khimeche, A. Donnot, R. Benelmir. FTIR spectroscopy and X-ray powder diffraction characterization of microcrystalline cellulose obtained from alfa fibers. 39th Edition of the Joint European Days on Equilibrium between Phases, Mar 2013, Nancy, France. pp.1023 - 1023, 10.1051/mate-conf/20130301023 . hal-01609047

HAL Id: hal-01609047

<https://hal.univ-lorraine.fr/hal-01609047>

Submitted on 3 Oct 2017

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

FTIR spectroscopy and X-ray powder diffraction characterization of microcrystalline cellulose obtained from alfa fibers

D. Trache¹, K. Khimeche¹, A. Donnot², and R. Benelmir²

¹Chimie appliquée, Ecole Militaire Polytechnique E.M.P., B.P 17 Bordj-El-Bahri, Alger, Algérie

²LERMAB, Faculté des Sciences et Techniques, Université de Lorraine, 54506 Vandœuvre-les-Nancy, France

Abstract. Many cereal straws have been used as raw materials for the preparation of microcrystalline cellulose (MCC). These raw materials were gradually replaced with wood products; nevertheless about 10% of the world overall pulp production is obtained from non-wood raw material. The main interest in pulp made from straw is that it provides excellent fibres for different industries with special properties, and that it is the major available source of fibrous raw material in some geographical areas.

The aim of the present work was to characterize microcrystalline cellulose prepared from alfa fibers using the hydrolysis process. The products obtained are characterized with FTIR spectroscopy and X-ray powder diffraction.

As a result, FTIR spectroscopy is an appropriate technique for studying changes occurred by any chemical treatment. The spectrum of alfa grass stems shows the presence of lignin and hemicelluloses. However, the cellulose spectrum indicates that the extraction of lignin and hemicellulose was effective. The X-ray analysis indicates that the microcrystalline cellulose is more crystalline than the source material.

1 Introduction

Stipa tenacissima L. (esparto grass or alfa grass) is a perennial tussock grass widely distributed in semi-arid ecosystems of the southern and western Mediterranean basin, mainly in the Maghreb. It occupies in North Africa about 7 million ha and it belongs to the graminacées family and grows to a height of about 1 m [1-3].

At present, cellulose is the most abundant polymer available worldwide and a representative renewable resource. Microcrystalline cellulose has been used for many years in different industries like cosmetics, plastics, food, pharmaceuticals, etc. MCC is obtained in industrial scale from wood and cotton cellulose using dilute mineral acids [4].

In the present work, the MCC was prepared from esparto grass. The characterisations were done using FTIR spectroscopy and X-ray diffraction.

2 Experimental

Alfa grass fibres were collected from the Saïda area, in Algeria. The extraction of cellulose from Alfa grass was occurred using the method given elsewhere [5]. Microcrystalline cellulose was prepared using cellulose sample obtained from esparto grass by hydrochloric acid hydrolysis [6].

3 Results and discussion

FTIR spectroscopy is an appropriate technique for studying changes occurred by any chemical treatment. The spectrum of alfa grass stems shows the presence of lignin and hemicelluloses. However, the cellulose spectrum indicates that the extraction of lignin and hemicellulose was efficient. In addition, the spectra of extracted cellulose and the prepared microcrystalline cellulose samples are identical to that of commercial one. In these spectra, all characteristic absorption peaks of cellulose are present.

The X-ray analysis indicates that the microcrystalline cellulose is more crystalline than the source material. The increase in the crystallite sizes for the prepared cellulose particles might be associated with a reduction in the corresponding amorphous region. If the amorphous domains of cellulose are attacked during the hydrolysis treatment, chain scission and peeling reactions can occur, which reduce the total amount of amorphous region and therefore increase the crystallite sizes of microcrystalline cellulose particles. Consequently, crystallinity indexes increased with increasing crystallite sizes because the crystallites surface corresponding to amorphous region decreased.




Figure 1. FTIR spectra of alfa grass fibres and cellulose microcrystalline derived from it.




Figure 2. X-ray diffraction patterns of prepared cellulose microcrystalline.

References

1. A. Bessadok, S. Marais, F. Gouanve, L. Colasse, I. Zimmerlin, S. Roudesli, M. Metayer, *Compo. Sci. Technol.* **67** 685 (2007)
2. P. García-Fayos, M. Gasque, *Acta Oecol.* **30** 276 (2006)
3. H. Nadji, P.N. Diouf, A. Benaboura, Y. Bedard, B. Riedl, T. Stevanovic, *Bioresour. Technol.* **100** 3585 (2009)
4. A.M. Adel, H.Z. Abd El-Wahab, A.A. Ibrahim, M.T. Al-Shemy, *Bioresour. Technol.* **101** 4446 (2010)
5. E.M. Maafi, F. Malek, L. Tighzert, P. Dony, *Journal of Polymer Environment* **18** 638 (2010)
6. M. Hanna, G. Blby, V. Miladinove, US Patent 6,228,213 (2001)