Twinning in chalcostibite revisited

Massimo Nespolo

► To cite this version:

Massimo Nespolo. Twinning in chalcostibite revisited. European Journal of Mineralogy, 2018, 30 (5), pp.967-973. 10.1127/ejm/2018/0030-2764 . hal-01917230

HAL Id: hal-01917230

<https://hal.univ-lorraine.fr/hal-01917230>

Submitted on 9 Nov 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

1 **Twinning in chalcostibite revisited**

2 Massimo NESPOLO

3 Université de Lorraine, CNRS, CRM2, Nancy, France.

4 Corresponding author, email massimo.nespolo@univ-lorraine.fr

5 ORCID [0000-0003-2530-5399](https://orcid.org/0000-0003-2530-5399)

6 **Abstract:** Twinning in chalcostibite has been reported to occur on the (104) plane with respect to
7 the standard setting *Pnma* of the space group. However, different axial settings have been used for
8 this mineral, and in the literature an axial ratio which corresponds to the *Pnam* setting is often
9 reported. Unfortunately, the same indexing of the twin plane, (104), is incorrectly used for both
10 settings; this has led to an incorrect reticular analysis of the twin, which could have been an
11 example of diperiodic twin, an alleged category which has no known examples to date. In this
12 article, we trace back the origin of the inconsistent indexing, we present a revised reticular analysis
13 which puts back this twin in the category of triperiodic twins, and we discuss the atomic structure at
14 the composition plane, showing that a small adjustment of the metal-sulphur coordination is
15 required to accommodate the change in orientation occurring when the twin forms.

16 **Key-words:** chalcostibite; crystallographic orbits; twinning.

17 **1 Introduction**

18 In our review of hybrid twins in non-silicate minerals (Nespolo and Ferraris, 2009) we have shown
19 that almost all non-Friedelian twins, *i.e.* twins with a twin index beyond the empirical limit of 6, are
20 hybrid twins whose effective twin index is within or close to this limit. One remarkable exception
21 remained however, which seemed to escape the reticular theory of twinning (Friedel, 1926), even in
22 its last extension as theory of hybrid twins (Nespolo & Ferraris, 2005): (104) twin in chalcostibite
23 CuSbS₂. In our analysis, we found two concurrent sublattices with twin indices 29 and 25, leading
24 to an effective twin index of 14.5, far too large to explain this twin on the basis of the reticular

theory . Chalcostibite (104) could therefore be the first example of diperiodic twin, an alleged category introduced as intermediate between the usual triperiodic twins and the exceptional case of monoperiodic twins discovered in Zinnwald twin of quartz (Friedel, 1933).

While working on the relation between diperiodic twins, of which to the best of our knowledge there are no confirmed representatives to date, and plesiotwins, a type of oriented crystal association based on a large coincidence site lattice (Nespolo *et al.*, 1999), we have traced back the history of that (104) twin in chalcostibite and realized that, due to a variety of axial settings adopted by different authors, at a certain point an error in the indexing occurred in the literature, which remains in reference textbooks. In this article, we give a brief historical perspective of this twin, show that once the twin plane is correctly indexed the twin is still hybrid but with a much lower effective twin index (5.5 instead of 14.5), and explain its occurrence on the basis of pseudo-eigensymmetry of the crystallographic orbits occupied by Cu and Sb, which is the basis of a satisfactory structural restoration across the twin plane.

2 Axial setting of chalcostibite and the problem of indexing the twin and composition plane

Chalcostibite (named by Glocker, 1847, p. 32) is a sulfosalt also reported under different names: *kupferantimonglanz* (Zincken, 1835); *rosite* (Huot, 1841, p. 197); *wolfsbergite*, from the type locality (Wolfsberg, Germany: Nicol, 1849, p. 484); *guejarite*, from Guejar in Spain (Cumenge, 1879).

Chalcostibite crystallizes in a space group of type *Pnma* (No. 62); both the point group (*mmm*) and the type of unit cell (*oP*) are invariant under any permutation of the basis vectors. Such a permutation does result in different settings of the space group (a recent detailed treatment is available in Nespolo and Aroyo, 2016), but the structural information was not available in the old mineralogical literature. Before the discovery of X-ray diffraction, the unit cell was estimated from

an axial ratio obtained by indexing the developed faces, and expressed in the form of a ratio $a:b:c$, usually normalized with respect to b taken as the longest parameter; however, different orientations resulted in different indexing of the faces. In case of orthorhombic crystals, the presence of symmetry operations of the same order (binary rotations or mirror reflections) along the three basis vectors made the indexing particularly disputable. As a result, different axial ratios were often adopted by various authors. In the case of chalcostibite, the following ratios were reported:

- Friedel (1879): 0.7841:1:0.8220
- Groth (1889): 0.5231:1:0.6395
- Laspeyres (1891): 0.527598:1:0.618584
- Penfield and Frenzel (1897, 1898): 0.5312:1:0.63955 (from their own measurements); 0.5283:1:0.6364 (from measurement of Laspeyres, 1891); 0.5242:1:0.6377 (from measurement of Friedel, 1879, and re-indexing forms $\{730\}$ and $\{370\}$ as $\{320\}$ and $\{230\}$ respectively)
- Goldschmidt (1923): 0.8026:1:0.6275
- Ungemach (1923): 0.6275:1:2.4082
- Palache *et al.* (1952): 0.4153:1:0.2606

The ratios reported by Groth, by Laspeyres, and by Penfield and Frenzel (GLP in the following, for short) were essentially the same. The transformations are the following¹: Friedel to GLP: $\mathbf{c}, 2\mathbf{a}, \mathbf{b}$; Friedel to Palache: $3\mathbf{c}, 6\mathbf{b}, -2\mathbf{a}$; GLP to Palache: $3\mathbf{a}, 6\mathbf{c}, -\mathbf{b}$; Goldschmidt to Palache: $\mathbf{b}, 3\mathbf{a}, -\mathbf{c}$; Ungemach to Palache: $\mathbf{b}, \mathbf{c}, \mathbf{a}$.

Cell parameters obtained from X-ray diffraction were published by Hofmann (1933), for the standard setting $Pnma$ of the space group, namely $a = 6.12$, $b = 3.89$, $c = 14.51$ Å, corresponding to the ratio 1.5899:1:3.8254, *i.e.* 0.4156:0.2614:1, very close to Palache apart from the exchange of $\mathbf{b}$

¹ Some of the transformations given by Palache *et al.* (1952) correspond to a change to left-handed reference. In these cases, we have modified a sign to obtain a right-handed setting.

72 and **c** basis vectors. Cell parameters from X-ray diffraction were also reported by Cervelle *et al.*
73 (1979) as $a = 6.026$, $b = 14.510$, $c = 3.800$ Å, without any indication of the space group; they
74 however clearly correspond to the *Pnam* setting and a ratio 0.4153:1:0.2619, very close to the ratio
75 of Palache. The transformation from Hofmann to Palache is **a,c,-b** and from Palache to Hofmann is
76 **a,-c,b**. Finally, the transformation from GLP to Hoffman is **3a,b,6c**. In other words, the *orientation*
77 of the basis vectors chosen in GLP is consistent with the cell parameters for the standard setting of
78 the space group, although the ratios differ.

79 Twinning in chalcostibite was reported by Spencer (1896) based on axial ratio of Groth (1889), as
80 occurring on the (102) plane. The same twin was also listed by Hintze (1904, page 992), who used
81 Penfield's axial ratio. The twin plane is reported to coincide with the composition plane and, with
82 respect to the cell parameters obtained from the X-ray diffraction data, it becomes (104) in the
83 *Pnma* setting or (140) in the *Pnam* setting, after removing common factors remaining by adopting
84 the transformation. Palache *et al.* (1952) adopted basis vectors which correspond to the *Pnam*
85 setting of the space group; accordingly, the twin plane should have been indicated as (140).
86 Unfortunately, the Miller indices of the twin plane were taken directly from Hofmann (1933); in
87 other words, Palache *et al.* (1952) gave the axial ratio corresponding to the *Pnam* setting of the
88 space group, but the Miller indices corresponding to the *Pnma* setting. This error was replicated in a
89 few texts and databases where the twin is mentioned, for example mindat.org (entry No. 983 for
90 chalcostibite).

91 In our survey (Nespolo and Ferraris, 2009), based on the data reported by Palache *et al.* (1952),
92 assuming that the indexing was consistent with the axial ratio, we exchanged the *k* and *l* indices
93 when computing the twin lattice. The very large effective twin index was the result of the incorrect
94 indexing of the twin plane in Palache *et al.* (1952). After discovering this error, we repeated the
95 calculations and we report the correct results here.

3 Reticular analysis of the (104) twin in chalcostibite

As we have shown in the previous section, the twin and composition plane reported by Hintze (1904) has Miller indices (140) in the *Pnam* setting reported by Palache *et al.*, and (104) in the standard *Pnma* setting. On the basis of the cell parameters reported by Razmara *et al.* (1997) for *Pnma*, namely $a = 6.0160(1)$, $b = 3.7968(6)$, $c = 14.499(3)$ Å, two concurrent sublattices are based on the twin plane, with quasi-perpendicular directions [302] (index 11, obliquity 0.83°) and [403] (index 8, obliquity 2.12°), which lead to an effective twin index $n_E = 5.5$, as shown in Fig. 1 (calculations performed with the software *geminography*: Nespolo and Ferraris, 2006). This result shows that (104) twin in chalcostibite is a normal, triperiodic hybrid twin; the large effective twin index reported in our 2009 survey was the result of the error in the indexing of the twin plane in Palache *et al.* (1952). The possibility of a diperiodic twin is therefore negated.

4 Structural analysis of the (104) twin in chalcostibite

Fig. 2 shows the structure of chalcostibite along the **b** axis (black: Cu; grey: Sb; white: S) in the cation-centred description. Cu has a slightly distorted tetrahedral coordination with Cu-S bond lengths 2.2717, 2×2.3157 and 2.3163 Å, whereas Sb has a more irregular coordination, in the shape of a highly distorted tetragonal pyramid, with five bond distances at 2.4489, 2×2.5895 and 2×3.1288 Å; the two longer distances barely contribute to the coordination of Sb. Indeed, the Effective Coordination Number (ECN: Hoppe, 1979) for Cu and Sb is 3.99 for four Cu-S bonds and 3.36 for five Sb-S bonds, showing that the coordination for Sb is much more distorted than for Cu and is more realistically described as 3+2. In the anion-centred description (Fig. 3), one S (S1) is coordinated by two Cu, both at 2.3157 Å, and three Sb, at 2.4489 and 2×3.1288 Å; again, the two longer distances S-Sb are borderline bond contacts. The other S (S2) is coordinated by two Cu at 2.2717 and 2.3163 Å, and two Sb, both at 2×2.5895 Å (computations performed with the software

119 CHARDI2015: Nespolo and Guillot, 2016). The structure of minerals is commonly described as
 120 based on cation-centred polyhedra, but the importance of the alternative interpretation as anion-
 121 centred polyhedra has been repeatedly emphasized (see, e.g., Krivovichev *et al.*, 2013; Beck, 2014;
 122 Eon and Nespolo, 2015). As it was already pointed out by Hofmann (1933), both types of metal
 123 atoms are very close to the (104) plane (Fig. 4); their position should therefore not be largely
 124 affected by twinning. These atoms are located at the corners of the coordination polyhedra in the
 125 anion-centred description of the structure, which makes the visual comparison of the changes in
 126 coordination due to twinning easier. The anion-centred description is therefore privileged below; the
 127 cation-centred description leads to the same conclusions and is briefly presented in the discussion.
 128 Hofmann (1933) did not provide any quantitative estimation of the perturbation the structure
 129 undergoes at the formation of the twin. To obtain such a quantitative measure, we need to analyse
 130 the pseudo-eigensymmetry of the crystallographic orbits, to find whether it contains an operation
 131 whose linear part coincides with the twin operation. The approach has been described in details in
 132 our previous articles, where the reader can find all the details; here we give just a brief summary.
 133 The same approach has allowed us to explain the formation of twins in a number of minerals,
 134 namely melilite (Marzouki *et al.* 2014a), staurolite (Marzouki *et al.* 2014b), aragonite (Marzouki *et*
 135 *al.*, 2015), marcasite (Nespolo and Souvignier, 2015a), cassiterite and rutile (Nespolo and
 136 Souvignier, 2015b), forsterite (Azevedo and Nespolo, 2017) and the Carlsbad twin in orthoclase
 137 (Nespolo and Souvignier, 2017).
 138 The unit cell of the twin lattice is defined by the (104) plane and the [302] direction quasi-
 139 perpendicular to it. Because the twin is hybrid, more than one direction quasi-perpendicular to the
 140 (104) plane could be chosen, each corresponding to a different sublattice: in this case, [302]
 141 (obliquity 0.83°) and [403] (obliquity 2.12°). The former direction is chosen to describe the
 142 structure of chalcostibite in the setting of the twin, because of the lower obliquity, which allows a

143 more precise estimation of the pseudo-symmetry.

144 The two shortest directions in the (104) plane are $[40\bar{1}]$ and $[010]$, which, together with $[302]$,
145 constitute the columns of the transformation matrix from the basis vectors $(\mathbf{abc})_I$ of the untwinned
146 chalcostibite to those of the twin $(\mathbf{abc})_T$ (I = individual, T = twin):

$$(\mathbf{a} \quad \mathbf{b} \quad \mathbf{c})_I \begin{pmatrix} 4 & 0 & 3 \\ 0 & 1 & 0 \\ \bar{1} & 0 & 2 \end{pmatrix} = (\mathbf{a} \quad \mathbf{b} \quad \mathbf{c})_T$$

147 *i.e.* $\mathbf{a}_T \mathbf{b}_T \mathbf{c}_T = 4\mathbf{a}_I \mathbf{c}_I, \mathbf{b}_I, 3\mathbf{a}_I + 2\mathbf{c}_I$. The cell parameters of the twin lattice are $a_T = 28.094$, $b_T = 3.797$, c_T
148 $= 34.156$ Å, $\beta_T = 89.17^\circ$; the unit cell of the twin lattice is primitive, monoclinic but pseudo-
149 orthorhombic, with a deviation of β which corresponds precisely to the obliquity and is eleven times
150 larger than the unit cell of the individual (this correspond to the index of the first sublattice); it
151 contains $16 \times 11 = 176$ atoms. The highest subgroup of *Pnma* compatible with this lattice is
152 obtained as $\mathcal{H} = \mathcal{G}_1 \cap \mathcal{G}_2$ where $\mathcal{G}_1$ and $\mathcal{G}_2$ are the space groups of the two individuals, both of type
153 *Pnma*, in the respective orientations. In our case, $\mathcal{H}$ is of type $P2_1/m$. The fractional coordinates of
154 chalcostibite in the asymmetric unit of *Pnma* are given in Table 1. The Wyckoff splitting scheme to
155 the setting of the twin lattice is very simple: $4c \rightarrow 22 \times 2e$. Table 2 [Note that Table 2 is deposited,
156 not printed, and freely available as Supplementary Material linked to this article on the GSW
157 website of the journal: <http://eurjmin.geoscienceworld.org/>] gives the 88 atoms in the asymmetric
158 unit of $P2_1/m$. Crystallographic orbits having a (pseudo)-eigensymmetry containing a mirror or
159 glide plane perpendicular to the $\mathbf{c}$ vector of the twin lattice are (quasi)-restored by the corresponding
160 operation. In the cell of the twin lattice, there are 11 positions for the (001) plane passing on or
161 close to the metal atoms, about 3.1 Å apart. The eigensymmetry analysis can be performed about
162 any of these positions: we take the one about $z = 0.5$. The position of the metal atoms about $z = 0.5$
163 are pseudosymmetric with respect to two orthorhombic minimal (index 2) supergroups of $P2_1/m$:

164 *Pmmn* (No. 59), with the basis vector in common with the individual, and *Pbmm*, which
 165 corresponds to *Pmma* (No. 51) expressed in a non-standard setting obtained with basis vector
 166 transformation **c,a,b**. Table 3 gives the fractional atomic coordinates of the four independent metal
 167 atoms (the other four are obtained by applying an inversion), as well as the corresponding fractional
 168 atomic coordinates obtained by applying an *n*-glide reflection (for *Pmmn* pseudo-eigensymmetry)
 169 and a mirror reflection (for *Pbmm* pseudo-eigensymmetry), both about $z = 0.5$. The Sb atoms are
 170 restored by this operation within, respectively, 0.2625 Å and 0.2732 Å, the Cu atoms within 0.3849
 171 Å and 0.3825 Å. This means that if a change of orientation occurs during the crystal growth at $z =$
 172 0.5 (with respect to the unit cell of the twin lattice), only a small adjustment of the metal atoms is
 173 necessary to overcome this perturbation. The two candidate restoration operations corresponding to
 174 the two pseudo-eigensymmetries do not lead, however, to the same coordination environment on the
 175 two sides of the twin plane. The situation is shown in Fig. 5, where the region around $z = 0.5$ is
 176 shown for the untwinned crystal (bottom), the twinned model in *Pmmn* (middle), and the twinned
 177 model in *Pbmm* (top). The position of the metal atoms on the twin plan being slightly different in
 178 the two individuals, they are shown as split, almost overlapped atoms in the twinned models in Fig.
 179 5. The coordination polyhedra share edges on the twin plane in the *Pmmn* model, as in the
 180 untwinned crystal, whereas they share faces in the *Pbmm* model. Twinning by reflection on (104)
 181 requires therefore a small adjustment of the metal atoms to produce a local structure at the boundary
 182 which is close to that of the untwinned crystal if the restoration operation is an *n*-glide; if instead the
 183 restoration operation is a mirror reflection, the coordination that results highly modified, an event
 184 which would make the twin less likely to occur.
 185 Now, exactly the same conclusion can be drawn for the eleven positions of the twin plan every
 186 $\sim 3.1\text{\AA}$. This means that during the crystal growth, twinning on (104) can be accommodated every
 187 $\sim 3.1\text{\AA}$, making this twinning a relatively high probability event.

188 **5 Discussion**

189 Fig 6 is obtained from the *Pmmn* twin model by taking the arithmetic average of the fractional
190 coordinates of the metal atoms almost overlapped in the Fig. 5 (middle). The coordination
191 polyhedra are essentially the same as those occurring in the untwinned mineral, but the S-metal
192 distances are in some cases severely affected, resulting in some polyhedra of unphysically small
193 size, with some S-metal distances as short as 1.6 Å. Clearly, the structural adjustment has to extend
194 further from the composition plane in order for the S-metal distances to approach their normal
195 values. From the energetic viewpoint, it is certainly more favourable if the strain occurring at the
196 composition plane is absorbed through smaller deformations on a slightly wider region than a single
197 larger deformation at the composition plane.

198 Fig. 7 is the cation-centred description of the structure of chalcostibite analogous to Fig. 5. The
199 coordination polyhedra at the twin plane for the *Pmmn* model are essentially the same as those in
200 the untwinned crystal, with the exception of one Cu site; here, one S has moved closer and another
201 one farther from Cu, leading to a triangular instead of tetrahedral coordination. The structural
202 adjustment close to the twin plane mentioned above would easily restore the normal coordination of
203 this Cu atom. In the *Pbmm* model, instead, the coordination at the twin plane is so heavily affected
204 that it would require extensive rearrangements to get closer to the normal coordination in the bulk
205 of the crystal. The *Pmmn* model is definitely more sound than the *Pbmm* model and the restoration
206 operation for this twin is an *n*-glide perpendicular to the *c* axis of the twin lattice.

207 The determination of the extent and extension of the structural adjustment around the twin plane
208 would require a high-resolution transmission electron microscopy study of (104) twin in
209 chalcostibite, which, to the best of our knowledge, has never been performed. With this study, we
210 hope to draw the attention of electron microscopists on the interest to perform such an investigation.

211 **Acknowledgments.** We thank Prof. Dominik Schaniel (CRM2, Université de Lorraine) for help
 212 with the German literature. Critical remarks from two anonymous reviewers and the Associate
 213 Editor are thankfully acknowledged.

214 **References**

- 215 Azevedo, S., Nespolo, M. (2017): Twinning in olivine group revisited. *Eur. J. Mineral.* **29**, 213-226.
 216 Beck, H. P. (2014): The co-ordination number rule and the rule of hardness, powerful tools to
 217 rationalize inorganic structures. *Z. Kristallogr.* **229**, 473–488.
 218 Cervelle, B.D., Cesbron, F.P., Sichère, M.-C. (1979). La chalcostibite et la dadsonite de Saint-Pons,
 219 Alpes de Haute Provence, France. *Can. Mineral.* **17**, 601-605.
 220 Cumenge, M.E. (1879). Note sur une nouvelle espèce minérale découverte dans le district de
 221 Guejar, Sierra-Nevada (Andalousie). *Bull. soc. min.* **2**, 201-203.
 222 Eon, J.G. and Nespolo, M. (2015): Charge distribution as a tool to investigate structural details. III.
 223 Extension to description in terms of anion-centred polyhedra. *Acta Crystallogr.* **B71**, 34-47.
 224 Friedel, C. (1879): Sur le forme cristalline de la Guejarite. *Bull.soc. Minér.* **2**, 203-204.
 225 Friedel, G. (1933): Sur un nouveau type de macles. *Bull. Soc. franç Minér.* **56**, 262-274.
 226 Glocker, E.F. von (1847): *Generum et Specierum Mineralium Secundum Ordines Naturales*
 227 *digestorum Synopsis*, Halle: E. Anton, 348 pp.
 228 Goldschmidt, V. M. (1923). *Atlas der Krystallformen*, **9**, 91. Heidelberg: Winter.
 229 Groth, P. H. v. (1889): Tabellarische Übersicht der Mineralien nach ihren krystallographisch-
 230 chemischen Beziehungen. 3rd edition, Braunschweig: F. Vieweg. X+167 pp.
 231 Hintze, C. (1904): Handbuch der Mineralogie. Erster Band. Leipzig, Verlag von Veit & Comp.
 232 VI+1208 pp.
 233 Hofmann, W. (1933): Strukturelle und morphologische Zusammenhänge bei Erzen vom Formeltyp
 234 ABC₂. *Z. Kristallogr.* **84**, 177-203.
 235 Hoppe, R. (1979): Effective coordination numbers (ECoN) and mean fictive ionic radii (MEFIR).
 236 *Z. Kristallogr.* **150**, 23-52.
 237 Huot, J.J.N. (1841). *Nouveau manuel complet de minéralogie, ou tableau de toutes les substances*
 238 *minérales*. Vol. I. Paris, La librairie encyclopédique de Roret, 402 pp.
 239 Krivovichev, S.V., Mentré O., Siidra, O.I., Colmont, M. and Filatov, S. K. (2013): Anion-Centered
 240 Tetrahedra in Inorganic Compounds. *Chem. Rev.* **113**, 6459-6535.
 241 Laspeyres, H. (1891): Mittheilungen aus dem mineralogischen Museum der Universität Bonn. Iv.
 242 Theil. *Z. Kristallogr.* **19**, 417-436.
 243 Marzouki, M.-A., Souvignier, B. & Nespolo, M. (2014a): Analysis of the structural continuity in
 244 twinned crystals in terms of pseudo-eigensymmetry of crystallographic orbits. *IUCrJ*, **1**, 39-
 245 48.
 246 —, —, — (2014b): The staurolite enigma solved. *Acta Crystallogr.*, **A70**, 348-353.
 247 —, —, — (2015): Twinning of aragonite – the crystallographic orbit and sectional layer group
 248 approach. *Acta Crystallogr.*, **A71**, 195-202.
 249 Momma, K., Izumi, F. (2011): VESTA 3 for three-dimensional visualization of crystal, volumetric
 250 and morphology data. *J. Appl. Crystallogr.*, **44**, 1272-1276.
 251 Nespolo, Ma., Aroyo, M.I. (2016): The crystallographic chameleon: when space groups change
 252 skin. *Acta Crystallogr.* **A72**, 523-538.
 253 Nespolo, M., Ferraris, G. (2005): Hybrid twinning - A cooperative type of oriented crystal
 254 association. *Z. Kristallogr.* **220**, 317-323.
 255 —, — (2006): The derivation of twin laws in non-merohedric twins - Application to the analysis of
 256 hybrid twins. *Acta Crystallogr.* **A62**, 336-349.

- , — (2009): A survey of hybrid twins in non-silicate minerals. *Eur. J. Mineral.* **21**, 673-690.
- Nespolo, M., Ferraris, G., Takeda, H., Takéuchi, Y. (1999): Plesiotwinning: oriented crystal associations based on a large coincidence-site lattice. *Z. Kristallogr.*, **214**, 378-382.
- Nespolo, M., Guillot, B (2016): CHARDI2015: Charge Distribution analysis of non-molecular structures. *J. Appl. Crystallogr.*, **49**, 317-321.
- Nespolo, M., Souvignier B (2015a): Application of the crystallographic orbit analysis to the study of twinned crystals. The example of marcasite. *Cryst. Res. Techn.*, **50**, 442-450.
- , — (2015b): Structural rationale for the occurrence of the elbow twins in cassiterite and rutile. *J. Mineral. Petrol. Sci.*, **110**, 157-165.
- , — (2017): Structural analysis of twins in feldspars. I. Carlsbad twinning. *Eur. J. Mineral.* **29**, in press (10.1127/ejm/2017/0029-2678).
- Nicol, J. (1849): *Manual of Mineralogy*. Edinburgh : A. and C. Black, xxiv + 576 pp.
- Palache, C., Berman, H., Frondel, C. (1952): *The system of mineralogy of James Dana and Edward Salisbury Dana*, Vol. I, 7th ed., third printing, Wiley, New York and Chapman, London.
- Penfield, S.L., Frenzel, A. (1897): Identity of Chalcostibite (Wolfsbergite) and Gruejarite, and on Chalcostibite from Huanchaca, Bolivia. *Am. J. Sci.* **4**, 27-35.
- Penfield, S.L., Frenzel, A. (1898): Ueber die Identität des Chalkostibit (Wolfsbergit) mit Guejarit und über Chalkostibit von Huanchaca, Bolivia. *Z. Kristallogr.* **28**, 598-609.
- Razmara, M.F., Henderson, C.M.B., Patrick, R.A.D. (1997): The crystal chemistry of the solid solution series between chalcostibite (CuSbS₂) and emplectite (CuBiS₂). *Mineral. Mag.*, **61**, 79-88.
- Spencer, L.J. (1896): Zinckenite and Wolfsbergite (Chalcostibite) from Wofsborg in the Harz ; and the Zinckenite Group. *Miner. Mag.* **11**, 188-191.
- Ungemach, M. H. (1923): VIII. Sur les formes cristallines de notation compliquée. *Z. Kristallogr.* **58**, 150-171.
- Zincken, C. (1835): Ueber den Kupfer-Antimonglanz, eine neue Mineralgattung. Aus einem Schreiben an den Prof. H. Rose in Berlin. *Poggen. Ann. Phys. Chemie* **35**: 357-361.

FIGURE CAPTIONS

Figure 1. The lattice of chalcostibite projected along the [010] direction. drawn in scale according to the cell parameters reported by Razmara *et al.* (1997). Four-pointed and five-pointed black stars indicate lattice nodes belonging to the [302]/(104) and [403]/(104) sublattice respectively; nodes on the (104) plane are common the two two sublattice and indicated by black circle; white circles stand for lattice nodes not belonging to either of the sublattices. The unit cell based on the [302]/(104) pair of lattice elements has multiplicity 11 and contains one lattice node for each sublattice, so that the effective twin index is $11/2 = 5.5$.

Figure 2. The structure of chalcostibite observed down the **b** axis in the cation-centred description. Cu atoms occupy a distorted tetrahedron whereas Sb atoms are at the centre of a face of a distorted square pyramid (this and the following figures are drawn with VESTA: Momma and Izumi, 2011).

Figure 3. The structure of chalcostibite observed down the **b** axis in the anion-centred description. The two crystallographically independent S atoms have different coordination: a 2Cu+3Sb distorted square pyramid and a 2Cu+2Sb distorted tetrahedron.

Figure 4. The ball-and-stick description of the structure of chalcostibite, with the (104) plane drawn in grey at the position $z = 0.5$. Metal atoms are positioned very close to this plane. Cu atoms are shown in black, Sb atoms in grey, S atoms in white.

Figure 5. A portion of the structure of chalcostibite in the axial setting of the twin, drawn around the twin plane in the anion-centred description. Bottom: the untwinned structure. Middle: the *Pmnm* twinned model (the portion above the twin plane is obtained from the one below it by an *n*-glide reflection at $z = 0.5$). Top: the *Pbmm* twinned model (the portion above the twin plane is obtained from the one below it by a mirror reflection at $z = 0.5$). In both twinned models, the metal atoms close to the twin plane are shown in the positions corresponding to the two individuals; these positions being very close, the corresponding atoms are almost overlapped in the figure. Whereas in the *Pnmm* model the coordination polyhedra on the opposite sides of the twin plane share their edges, as in the untwinned crystal, in the *Pbmm* model they share their faces, leading to a physically unlikely situation.

Fig. 6. A likely structural adjustment at the composition plane, obtained by taking the arithmetic average of the fractional atomic coordinates of the metal atoms quasi-overlapped in Fig. 5. The S-metal coordination appears very similar to that in the untwinned crystal but actually some of the polyhedra have unphysically small volumes, indicating that the structural adjustment likely extends for a few atomic planes in order to minimize the structural strain occurring when the twin forms.

Figure 7. A portion of the structure of chalcostibite in the axial setting of the twin, drawn around the twin plane in the cation-centred description. Bottom: the untwinned structure; middle: the *Pmnm* twinned model; top: the *Pbmm* twinned model (same conventions as in Fig. 5). The positions of the Cu and Sb atoms on the twin plane are the arithmetic average of the positions in the two individuals; no other structural adjustment is introduced. In the *Pnmm* model, the coordination polyhedra are essentially the same as in the untwinned crystal, with the exception of one of the Cu sites; in the *Pbmm* model, instead, the coordination around the twin plane is severely affected. A structural adjustment of the S atoms close to the twin plane can restore the normal coordination in the *Pmnm* model but not in the *Pbmm* model.

Table 1. Fractional atomic coordinates in the asymmetric unit of chalcostibite, setting *Pnma*. All atoms are in Wyckoff position 4c. Data from Ramzara *et al* (1997).

Cu	0.7463(6)	$\frac{3}{4}$	0.1721(2)
Sb	0.2245(2)	$\frac{1}{4}$	0.0636(1)
S1	0.624(1)	$\frac{1}{4}$	0.0960(4)
S2	0.131(2)	$\frac{3}{4}$	0.1787(5)

Table 3. Fractional atomic coordinates of metal atoms around $z = 0.5$ (label without ') and after application of a mirror reflection about $z = 0.5$ label with '), in the two models *Pmmn* and *Pbmm*. The difference is expressed both in terms of fractional atomic coordinated and in Å ($|\Delta|$).

<i>Pmmn</i>											
Atom	<i>x</i>	<i>y</i>	<i>z</i>	Atom	<i>x</i>	<i>y</i>	<i>z</i>	Δx	Δy	Δz	$ \Delta $
Sb11	0.93256	0.25	0.49808	Sb18'	0.94184	0.25	0.49728	0.00928	0	0.0008	0.2625
Sb18	0.44184	0.75	0.50272	Sb11'	0.43256	0.75	0.50192	0.00928	0	0.0008	0.2625
Cu20	0.68263	0.75	0.50526	Cu20'	0.68397	0.75	0.49406	0.00134	0	0.0112	0.3849
Cu2	0.18397	0.25	0.50594	Cu2'	0.18263	0.25	0.49474	0.00134	0	0.0112	0.3849
<i>Pbmm</i>											
Atom	<i>x</i>	<i>y</i>	<i>z</i>	Atom	<i>x</i>	<i>y</i>	<i>z</i>	Δx	Δy	Δz	$ \Delta $
Sb11	0.93256	0.25	0.49808	Sb11'	0.93256	0.25	0.50192	0	0	0.0008	0.2732
Sb18	0.44184	0.75	0.50272	Sb18'	0.44184	0.75	0.49728	0	0	0.0008	0.2732
Cu20	0.68263	0.75	0.50526	Cu2'	0.68263	0.75	0.49474	0	0	0.0112	0.3825
Cu2	0.18397	0.25	0.50594	Cu02'	0.18397	0.25	0.49406	0	0	0.0112	0.3825