



**HAL**  
open science

## Suppression of all-optical switching in He $\pm$ -irradiated Co/Pt multilayers: influence of the domain-wall energy

Mohammed Salah El Hadri, Michel Hehn, Grégory Malinowski, Cyrille Beigne, Eric E. Fullerton, Dafine Ravelosona, Stéphane Mangin

### ► To cite this version:

Mohammed Salah El Hadri, Michel Hehn, Grégory Malinowski, Cyrille Beigne, Eric E. Fullerton, et al.. Suppression of all-optical switching in He  $\pm$ -irradiated Co/Pt multilayers: influence of the domain-wall energy. *Journal of Physics D: Applied Physics*, 2018, 51 (21), pp.215004. 10.1088/1361-6463/aabf2b . hal-01950851

**HAL Id: hal-01950851**

**<https://hal.univ-lorraine.fr/hal-01950851>**

Submitted on 23 Apr 2019

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Suppression of all-optical switching in He<sup>+</sup>-irradiated Co/Pt multilayers: influence of the domain-wall energy

**Mohammed Salah El Hadri**<sup>1,2</sup>

<sup>1</sup>Institut Jean Lamour, UMR CNRS 7198, Université de Lorraine, BP 70239, F-54506, Vandoeuvre-lès-Nancy, France

<sup>2</sup>Center for Memory and Recording Research, University of California San Diego, La Jolla, California, 92093-0401, USA

E-mail: melhadri@ucsd.edu

**Michel Hehn**<sup>1</sup>

<sup>1</sup>Institut Jean Lamour, UMR CNRS 7198, Université de Lorraine, BP 70239, F-54506, Vandoeuvre-lès-Nancy, France

**Grégory Malinowski**<sup>1</sup>

<sup>2</sup>Institut Jean Lamour, UMR CNRS 7198, Université de Lorraine, BP 70239, F-54506, Vandoeuvre-lès-Nancy, France

**Cyrille Beigné**<sup>3</sup>

<sup>3</sup>Univ. Grenoble Alpes - CNRS - CEA, INAC-SPINTEC, F-38054 Grenoble Cedex 9, France

**Eric E. Fullerton**<sup>2</sup>

<sup>2</sup>Center for Memory and Recording Research, University of California San Diego, La Jolla, California, 92093-0401, USA

**Dafiné Ravelosona**<sup>4</sup>

<sup>4</sup>Centre de Nanosciences et de Nanotechnologies, CNRS, Univ. Paris-Sud, F-91405 Orsay, France

**Stéphane Mangin**<sup>1</sup>

<sup>1</sup>Institut Jean Lamour, UMR CNRS 7198, Université de Lorraine, BP 70239, F-54506, Vandoeuvre-lès-Nancy, France

**Abstract.** The observation of all-optical helicity-dependent switching (AO-HDS) in ferri- and ferro-magnetic materials depends not only on the saturation magnetization, but on the magnetic domain size which takes into account the competition between the demagnetizing energy and the domain wall (DW) energy. In this paper, we study

the optical response of Co/Pt multilayers for which perpendicular magnetic anisotropy can be tuned using He<sup>+</sup>-irradiation. This allows us to correlate the observation of AO-HDS with the magnetic properties of the He<sup>+</sup>-irradiated multilayer. These results give direct evidence of the crucial role of the DW energy in the laser-induced switching process.

*Keywords:* Paper Submitted to: *J. Phys. D: Appl. Phys.*

The manipulation of magnetization using ultrashort laser pulses and without any other stimuli has triggered huge interest as an emergent field of research [1, 2]. This all-optical switching (AOS) of magnetization was initially demonstrated in ferrimagnetic GdFeCo alloy films using single femtosecond (fs) laser pulses [3]. This laser-induced switching in GdFeCo alloys was shown to be purely thermal [4] and ultrafast, taking place on a picosecond timescale [5]. A helicity-dependent switching was also obtained in these ferrimagnetic alloys but only for a narrow range of fluence [6], and its microscopic origin is still heavily debated [6, 7]. Later, AOS was also demonstrated in a much larger variety of ferrimagnetic alloy films and multilayers [8, 9] and also in ferromagnetic materials and spintronic devices [10, 11, 12, 13]. In contrast to GdFeCo alloy films, AOS in these materials was shown to be helicity-dependent independently on the laser fluence [9], cumulative and only achieved after a helicity-independent multiple-domain formation [14].

Furthermore, recent studies have investigated the magnetic parameters ruling the observation of all-optical helicity-dependent switching (AO-HDS) in these material classes [15, 17, 16, 18]. Indeed, El Hadri *et al* [18] performed a comprehensive investigation on ferrimagnetic TbCo alloy films and ferromagnetic Co/Ni and Co/Pt multilayers for a wide range of composition and thickness. By taking into account the competition between the demagnetizing energy and the domain wall (DW) energy, they showed that the large magnetic domain size is a criterion for the observation of AO-HDS, which is common for both studied ferri- and ferro-magnets [18]. More importantly, such investigation reconciles the contradictions between the reported low remanence criterion for ferrimagnetic materials [16, 15, 17] and the observation of AO-HDS in ferromagnets with a high saturation magnetization [10]. However, this investigation has mainly elucidated material classes where both the demagnetizing energy and the DW energy change [18], which makes it impossible to reveal the direct role of the DW energy in the AO-HDS process.


To elucidate the direct role of the DW energy in the observation of AO-HDS, we present in this paper an experimental investigation of the AO-HDS ability in a new material class, namely  $He^+$ -irradiated Co/Pt multilayers with perpendicular magnetic anisotropy (PMA). Indeed, it has already been shown by Chappert *et al* in their pioneering work [19] that the PMA in ferromagnetic Co/Pt multilayers can be decreased in a controlled way via  $He^+$ -ion irradiation. The irradiation process induces intermixing at the Co/Pt interfaces, which results in a strong decrease of the interface anisotropy and thus of the PMA and the DW energy [19, 21, 20, 22]. On the other hand, the saturation magnetization of the  $He^+$ -irradiated Co/Pt multilayers remains constant [23]. Therefore, the change of the demagnetizing energy is negligible compared to the one of the DW energy in  $He^+$ -irradiated Co/Pt multilayers. Hence, investigating the AO-HDS ability in  $He^+$ -irradiated Co/Pt multilayers will enable to reveal the direct role of the DW energy in the AO-HDS process. In this context, we investigate the optical response

of He<sup>+</sup>-irradiated Co/Pt multilayers under the action of fs laser pulses. We demonstrate that a behavior change from AO-HDS to thermal demagnetization takes place by gradually increasing the irradiation dose. These findings highlight the direct role of the DW energy in the AO-HDS process, and confirm the requirement of a large domain size for the observation of AO-HDS.

In this paper, we decided to investigate the effect of He<sup>+</sup>-irradiation on the all-optical switching ability in Co/Pt multilayers which show whether pure AO-HDS or pure TD. On the other hand, it was previously demonstrated that as-deposited [Co (0.6 nm)/Pt (0.7 nm)]<sub>2</sub> and [Co (0.6 nm)/Pt (0.7 nm)]<sub>4</sub> multilayers show pure AO-HDS and pure TD, respectively [18]. Therefore, the investigated ferromagnetic samples are multilayer thin films of Glass/Ta(3 nm)/Pt(3 nm)/ [Pt(0.7 nm)/Co(0.6 nm)]<sub>N</sub>/Pt(3 nm) grown by DC magnetron sputtering, where the number of repeats  $N = 2$  or 4. The top Pt layer prevents sample oxidation. The studied films were subsequently irradiated with He<sup>+</sup> ions at irradiation dose ( $ID$ ) ranging from  $5 \cdot 10^{14}$  He<sup>+</sup>/cm<sup>2</sup> to  $5 \cdot 10^{15}$  He<sup>+</sup>/cm<sup>2</sup>. The irradiation procedure was carried out at room temperature (RT) and at a constant energy of 15 keV. The changes in magnetic properties of He<sup>+</sup>-irradiated Co/Pt multilayers were measured by SQUID magnetometry. For none-irradiated [Co/Pt]<sub>N</sub> multilayers, a saturation magnetization  $M_s = 1619$  emu/cm<sup>3</sup> (resp.  $1982$  emu/cm<sup>3</sup>) and a uniaxial anisotropy constant  $K_u = 2.41 \cdot 10^7$  erg/cm<sup>3</sup> (resp.  $3.15 \cdot 10^7$  erg/cm<sup>3</sup>) were measured for  $N = 2$  (resp.  $N = 4$ ). Thus, the effective perpendicular anisotropy  $K_{\text{eff}} = K_u - 2\pi M_s^2$  is positive for none-irradiated [Co/Pt]<sub>N</sub> multilayers, which leads to a magnetization perpendicular to the film plane at zero fields. The increase of the saturation magnetization ( $M_s$ ) with the number of repeats  $N$  is attributed to the spin polarization of Pt atoms by the adjacent Co layers [24]. The thickness of the spin-polarized Pt is not taken into account for the calculation of the  $M_s$ , and thus of the anisotropy constant ( $K_u$ ).

For irradiated [Co/Pt]<sub>2</sub> multilayers, Fig. 1(a) shows that irradiation up to  $ID$ s of  $5 \cdot 10^{15}$  He<sup>+</sup>/cm<sup>2</sup> results in square hysteresis at RT with the field oriented out-of-plane compared to the sample, indicating that all irradiated samples remain perpendicularly magnetized. The coercive field decreases from  $H_c = 170$  Oe for the none-irradiated film to  $H_c = 110$  Oe for films irradiated at  $ID = 5 \cdot 10^{15}$  He<sup>+</sup>/cm<sup>2</sup>. Moreover, Fig. 1(b) shows that irradiation up to  $ID$ s of  $5 \cdot 10^{15}$  He<sup>+</sup>/cm<sup>2</sup> results also in a gradual decrease of the anisotropy field  $H_K$ . For irradiated [Co/Pt]<sub>4</sub> multilayers, Fig. 2(a) shows that irradiation up to  $10^{15}$  He<sup>+</sup>/cm<sup>2</sup> also results in square hysteresis at RT with the field oriented out-of-plane compared to the sample. However, the magnetization easy axis is rotated towards the in-plane orientation for [Co/Pt]<sub>4</sub> multilayers irradiated at  $ID > 10^{15}$  He<sup>+</sup>/cm<sup>2</sup>, as depicted in Fig.2(b).

Fig. 3(a) shows that the anisotropy constant  $K_u$  decreases strongly down to  $K_u = 2.41 \cdot 10^7$  erg/cm<sup>3</sup> at a high  $ID = 5 \cdot 10^{15}$  He<sup>+</sup>/cm<sup>2</sup>, while the saturation magnetization remains almost constant. These findings are in agreement with previous studies on Co/Pt




**Figure 1.** Room temperature SQUID hysteresis loops of the studied  $[\text{Co}(0.6 \text{ nm})/\text{Pt}(0.7 \text{ nm})]_2$  multilayers as deposited, and after irradiation with 15 keV  $\text{He}^+$ -ions at irradiation doses up to  $5 \cdot 10^{15} \text{ He}^+/\text{cm}^2$ . (a) (resp. (b)) The applied magnetic field is oriented out-of-plane (resp. in plane) compared to the sample. Lines are guides to the eyes.

multilayers [23, 25]. A similar trend is measured for irradiated  $[\text{Co}/\text{Pt}]_4$  multilayers. As depicted in Fig. 3(b),  $K_u$  strongly decreases down to  $2.17 \cdot 10^7 \text{ erg}/\text{cm}^3$  at  $ID = 10^{15} \text{ He}^+/\text{cm}^2$ , while  $M_s$  slightly decreases down to  $1710 \text{ emu}/\text{cm}^3$ .

On the basis of our previous study on the domain size criterion for AO-HDS [18], we estimate the magnetic domain size  $D$  for the  $\text{He}^+$ -irradiated Co/Pt multilayers using the model proposed by Kooy and Unz [26] of periodic stripe domains with a strong uniaxial anisotropy in an infinite plate. We make the approximation that the domain wall size is negligible compared to the magnetic domain size and that the magnetization is perpendicular to the film plane within the domains. Therefore, the magnetic domain size  $D$  corresponding to the minimization of the total energy is expressed by:

$$D = t \exp \left[ \frac{\pi D_0}{2t} + \ln \pi - 1 + \mu \left( \frac{1}{2} - \ln 2 \right) \right] \quad (1)$$

Where  $D_0 = \frac{\sigma}{E_d}$  is the dipolar length and  $\mu = 1 + \frac{E_d}{K_u}$  is the magnetic susceptibility.  $E_d = 2\pi M_s^2$  is the magnetizing energy per unit volume,  $t$  the magnetic thickness, while  $A_{\text{ex}}$  is the exchange constant and  $\sigma = 4\sqrt{A_{\text{ex}}K_u}$  is the DW energy per unit surface area. According to Eq. (1), the strong reduction of  $K_u$  for  $\text{He}^+$ -irradiated Co/Pt multilayers




**Figure 2.** Room temperature SQUID hysteresis loops of the studied  $[\text{Co}(0.6 \text{ nm})/\text{Pt}(0.7 \text{ nm})]_4$  multilayers as deposited, and after irradiation with 15 keV  $\text{He}^+$ -ions at irradiation doses up to  $2 \cdot 10^{15} \text{ He}^+/\text{cm}^2$ . (a) (resp. (b)) The applied magnetic field is oriented out-of-plane (resp. in plane) compared to the sample. Lines are guides to the eyes.

at high  $ID$ s leads to a decrease of the DW energy, and thus of the domain size  $D$ . In a first approximation, we suppose that  $M_s$  and  $A_{ex}$  change only weakly with the irradiation dose. Therefore, we use the values of  $A_{ex}$  and  $M_s$  for none-irradiated samples in order to calculate the domain size for the  $\text{He}^+$ -irradiated ones. The value of  $A_{ex}$  for none-irradiated Co/Pt samples is estimated using data from literature,  $A_{ex}(\text{Co/Pt}) = A_{ex}(ID = 0) = 1.2 \cdot 10^{-6} \text{ erg/cm}$  [27]. We define a domain size threshold  $D_{th} = 50 \mu\text{m}$  corresponding to the size of the fs laser spot used in the all-optical switching experiment (FWHM =  $50 \mu\text{m}$ ).

Fig. 4(a) and Fig. 4(b) show the evolution of  $D$  as a function of the total magnetic thickness  $t$  for  $[\text{Co}(\frac{t}{2})/\text{Pt}(0.7 \text{ nm})]_2$  and  $[\text{Co}(\frac{t}{4})/\text{Pt}(0.7 \text{ nm})]_4$  multilayers, respectively. For  $[\text{Co/Pt}]_2$  irradiated at  $ID = 5 \cdot 10^{15} \text{ He}^+/\text{cm}^2$ , we measured an anisotropy constant  $K_u$  ( $ID = 5 \cdot 10^{15} \text{ He}^+/\text{cm}^2$ ) =  $1.25 \cdot 10^7 \text{ erg/cm}^3$ . As depicted in Fig. 4(a), the estimated domain size  $D$  for  $[\text{Co}(0.6 \text{ nm})/\text{Pt}(0.7 \text{ nm})]_2$  multilayers with  $K_u$  ( $ID = 5 \cdot 10^{15} \text{ He}^+/\text{cm}^2$ ) =  $1.25 \cdot 10^7 \text{ erg/cm}^3$  decreases and coincides with the laser spot size  $D_{th}$ .

Note that it was shown in previous experimental investigations that  $\text{He}^+$ -irradiated of Co/Pt multilayers results in a strong reduction of the Curie temperature ( $T_c$ ) [20, 21],




**Figure 3.**  $M_s$  and  $K_u$  dependence on the irradiation dose  $ID$  for the studied  $[\text{Co}(0.6 \text{ nm})/\text{Pt}(0.7 \text{ nm})]_N$  multilayers with (a)  $N = 2$  and (b)  $N = 4$ . Lines are guides to the eyes.

which is a hint that a decrease of  $A_{ex}$  might also take place. By taking into account a decrease of  $A_{ex}$  due to  $\text{He}^+$ -irradiation, it can be understood from Eq.(1) that the domain size for  $[\text{Co}(0.6 \text{ nm})/\text{Pt}(0.7 \text{ nm})]_2$  irradiated at  $ID = 5 \times 10^{15} \text{ He}^+/\text{cm}^2$  will be smaller than the laser spot size  $D_{th}$ . On the other hand, recent experimental investigation showed that annealing can increase the exchange stiffness of ferromagnetic CoFeB films by 10% [28]. Hence, the  $\text{He}^+$ -irradiation might lead to an increase of  $A_{ex}$ . To investigate the effect of an eventual increase  $A_{ex}$ , we estimated the domain size for  $[\text{Co}(0.6 \text{ nm})/\text{Pt}(0.7 \text{ nm})]_2$  multilayers with  $K_u$  ( $ID = 5 \times 10^{15} \text{ He}^+/\text{cm}^2$ ) =  $1.25 \times 10^7 \text{ erg}/\text{cm}^3$  and with 10% and 20% increase of  $A_{ex}$ . Fig. 4(a) shows that the change in magnetic domain size with increasing  $A_{ex}$  by 10% is negligible.

According to the previously demonstrated domain size criterion for the observation of AO-HDS [18],  $[\text{Co}(0.6 \text{ nm})/\text{Pt}(0.7 \text{ nm})]_2$  irradiated at  $ID = 5 \times 10^{15} \text{ He}^+/\text{cm}^2$  are expected to exhibit thermal demagnetization (TD) and thus are different from non-irradiated  $[\text{Co}(0.6 \text{ nm})/\text{Pt}(0.7 \text{ nm})]_2$  samples showing AO-HDS [10, 18]. Moreover, Fig. 4(b) shows that the domain size  $D$  for  $[\text{Co}(0.6 \text{ nm})/\text{Pt}(0.7 \text{ nm})]_4$  calculated with  $K_u$  ( $ID = 10^{15} \text{ He}^+/\text{cm}^2$ ) =  $3.14 \times 10^7 \text{ erg}/\text{cm}^3$  is smaller than the laser spot laser. Therefore, irradiated  $[\text{Co}(0.6 \text{ nm})/\text{Pt}(0.7 \text{ nm})]_4$  multilayers are also expected to exhibit TD.





**Figure 4.** (a) Estimation of the magnetic domain size  $D$  as a function of the magnetic thickness  $t$  in  $[\text{Co}(\frac{t}{2})/\text{Pt}(0.7 \text{ nm})]_2$  multilayers: for  $K_u (ID = 0) = 2.41 \cdot 10^7 \text{ erg/cm}^3$  and  $A_{ex}(ID = 0) = 1.2 \cdot 10^{-6} \text{ erg/cm}$ ; and for  $K_u (ID = 5 \cdot 10^{15} \text{ He}^+/\text{cm}^2) = 1.25 \cdot 10^7 \text{ erg/cm}^3$  and three different values of  $A_{ex}$  [ $A_{ex}(ID = 0)$ ,  $1.1 A_{ex}(ID = 0)$  and  $1.2 A_{ex}(ID = 0)$ ]. (b) Estimation of the magnetic domain size  $D$  as a function of the magnetic thickness  $t$  in  $[\text{Co}(\frac{t}{4})/\text{Pt}(0.7 \text{ nm})]_4$  multilayers: for  $K_u (ID = 0) = 3.14 \cdot 10^7 \text{ erg/cm}^3$  and  $A_{ex}(ID = 0) = 1.2 \cdot 10^{-6} \text{ erg/cm}$ ; and for  $K_u (ID = 10^{15} \text{ He}^+/\text{cm}^2) = 2.17 \cdot 10^7 \text{ erg/cm}^3$  and three different values of  $A_{ex}$  [ $A_{ex}(ID = 0)$ ,  $1.1 A_{ex}(ID = 0)$  and  $1.2 A_{ex}(ID = 0)$ ].  $D$  is calculated with  $M_s$  measured for the none-irradiated samples. The filled symbols indicate the magnetic thickness of the studied  $[\text{Co}(0.6 \text{ nm})/\text{Pt}(0.7 \text{ nm})]_N$  multilayers.

In order to verify the expected behavior of  $\text{He}^+$ -irradiated Co/Pt multilayers due to the action of fs laser beam, we used a Ti:sapphire fs laser with a 5-kHz laser pulse frequency, a wavelength of 800 nm, and a pulse duration of 35 fs. The Gaussian beam spot is focused with a FWHM of approximately  $50 \mu\text{m}$ . The studied  $[\text{Co}/\text{Pt}]_N$  samples are excited through the glass substrate with laser powers ranging from 0.75 mW for films with  $N = 2$  up to 2.5 mW for films with  $N = 4$ . The response of the investigated magnetic films is probed using static Faraday microscopy in order to image the magnetic domains in transmission. Prior to being optically excited, the irradiated films are saturated with an external magnetic field. During the optical excitation, no magnetic field is applied and the 35-fs laser beam is swept from right to left for both circular polarizations with a low sweeping speed of approximately  $10 \mu\text{m/s}$ .


We have first investigated the optical response of irradiated  $[\text{Co}/\text{Pt}]_2$  multilayers

at  $ID$  ranging from  $5 \cdot 10^{14} \text{ He}^+/\text{cm}^2$  to  $5 \cdot 10^{15} \text{ He}^+/\text{cm}^2$ . As depicted in Fig. 5, the none-irradiated ( $ID = 0$ ) [Co/Pt]<sub>2</sub> multilayers exhibit AO-HDS, in agreement with the previous studies [10, 18]. By increasing  $ID$  from  $5 \cdot 10^{14} \text{ He}^+/\text{cm}^2$  to  $2 \cdot 10^{15} \text{ He}^+/\text{cm}^2$ , the effect of the helicity on the irradiated [Co/Pt]<sub>2</sub> multilayers disappears gradually. Indeed, multiple domains start appearing in the scanned region and are stretched towards to the center of the beam spot. This behavior is attributed to thermal-induced DW motion [29, 30]. More importantly, Fig. 5 shows that only TD is obtained are for the [Co/Pt]<sub>2</sub> sample irradiated at  $ID = 5 \cdot 10^{15} \text{ He}^+/\text{cm}^2$  and with a domain size  $D$  smaller than  $D_{th}$  (see Fig. 4(a)). Moreover, the multiple domains in the scanned region get smaller for  $ID = 5 \cdot 10^{15} \text{ He}^+/\text{cm}^2$ , thus confirming the reduction of the domain size due to the He<sup>+</sup>-irradiation. These findings confirm the large domain size criterion for the observation of AO-HDS [18], and give direct evidence that the DW energy plays a crucial role in the AO-HDS process. Furthermore, the lateral size of the laser-affected area for the studied [Co/Pt]<sub>2</sub> samples is expected to increase with the irradiation dose, since the He<sup>+</sup>-irradiation of [Co/Pt]<sub>2</sub> leads to a decrease of the Curie temperature [20, 21]. Hence, it can be seen from Fig. 5 that this lateral size increases by 28% for the [Co/Pt]<sub>2</sub> irradiated at  $ID = 5 \cdot 10^{15} \text{ He}^+/\text{cm}^2$  compared to the none-irradiated [Co/Pt]<sub>2</sub> sample.

We have also verified the TD behavior of irradiated [Co/Pt]<sub>4</sub> multilayers under the optical excitation. As depicted in Fig. 6 the none-irradiated [Co/Pt]<sub>4</sub> multilayers show TD, which in agreement with the previous studies [10]. Moreover, Fig. 6 shows that the irradiated [Co/Pt]<sub>4</sub> multilayers with an estimated domain size  $D < D_{th}$  exhibit also TD, as expected from the large domain size criterion [18]. Furthermore, the multiple domains in the scanned area of irradiated [Co/Pt]<sub>4</sub> multilayers become too small to be optically resolved, which also confirms the reduction of the domain size due to the He<sup>+</sup>-irradiation.

Recently, many experimental investigations and theoretical models have highlighted the microscopic origins of the symmetry breaking mechanism leading to AO-HDS in ferromagnetic materials. These origins can be divided into pure thermal origins such as the magnetic circular dichroism (MCD) [31, 32], and non-thermal origins such as the inverse Faraday effect (IFE)[33]. Our experimental investigation on He<sup>+</sup>-irradiated Co/Pt multilayers does not explain the symmetry breaking mechanism, but gives insights into the material-related conditions for the observation of AO-HDS. Indeed, the DW energy plays a crucial role in the AO-HDS process by impacting the magnetic domain size. The smaller is the DW energy, the smaller is the domain size. During the AO-HDS process, the initial effect of the laser pulses' helicity is suppressed in magnetic films with small DW energies via the formation of small magnetic domains during the cooling process.


On the other hand, it was previously reported in the literature that He<sup>+</sup>-irradiation influences the domain wall motion properties in ferromagnets, which could also explain the transition from AO-HDS to pure TD for the investigated He<sup>+</sup>-irradiated Co/Pt



**Figure 5.** Optical response for  $[\text{Co}(0.6 \text{ nm})/\text{Pt}(0.7 \text{ nm})]_2$  multilayers as a function of the irradiation dose  $ID$  under the action of swept 35-fs circularly polarized laser beam. A gradual transition from AO-HDS to pure TD is obtained by increasing  $ID$  up to  $5 \cdot 10^{15} \text{ He}^+/\text{cm}^2$ . For each sample, right- and left-circularly polarized laser beam were swept over the sample from right to left. The initial magnetization saturation up is exemplarily shown. The dark contrast corresponds to a reversal to down. The measurements were performed using a constant laser power of 0.75 mW.

multilayers. Indeed, Hererra Diez *et al* showed that the  $\text{He}^+$ -irradiation of ferromagnetic CoFeB/MgO films with PMA leads to an increase of their depinning field in the creep regime [34]. Moreover, it was recently shown that the AO-HDS in ferromagnetic Co/Pt films is governed by a helicity-dependent domain wall motion-like mechanism [14, 32, 35]. Therefore, the  $\text{He}^+$ -irradiation of ferromagnetic Co/Pt multilayers might also influence the helicity-dependent domain wall motion mechanism via the increase of the depinning field, thus canceling the helicity effect and leading to a transition from AO-HDS to TD regime.

In conclusion, we have experimentally investigated the AO-HDS ability in ferromagnetic  $\text{He}^+$ -irradiated Co/Pt multilayers. We showed that increasing the irradiation dose leads to a strong decrease of the magnetic anisotropy, and thus of the magnetic domain size. More importantly, we demonstrated that a gradual change of behavior from AO-HDS to TD is observed in irradiated Co/Pt multilayers by gradually increas-




**Figure 6.** Optical response for  $[Co(0.6 \text{ nm})/Pt(0.7 \text{ nm})]_4$  multilayers as a function of the irradiation dose  $ID$  under the action of swept 35-fs circularly polarized laser beam. A pure TD is obtained and the domain size in the laser excited decreases by increasing  $ID$  up to  $10^{15} \text{ He}^+/\text{cm}^2$ . For each sample, right- and left-circularly polarized laser beam were swept over the sample from right to left. The initial magnetization saturation up is exemplarily shown. The dark contrast corresponds to a reversal to down. The measurements were performed using a constant laser power of 2.5 mW.

ing the irradiation dose. Only TD is obtained for Co/Pt multilayers irradiated at high irradiation doses and with an estimated magnetic domain size smaller than the laser spot size. These findings confirm the large domain size criterion for the observation of AO-HDS and highlight the direct role of the DW energy in the AO-HDS process. Indeed, the initial effect of the laser pulses' helicity during AO-HDS process is suppressed in magnetic films with small DW energies via the formation of small magnetic domains during the cooling process. From a technological point of view, these findings elucidate the effect of the manipulation of PMA on the observation of AO-HDS in materials that are superior for data storage applications.

This work was supported partly by the french PIA project “Lorraine Université d’Excellence”, reference ANR-15-IDEX-04-LUE, by the ANR-NSF Project, ANR-13-IS04-0008-01, “COMAG” by the ANR-Labcom Project LSTNM. Experiments were carried out on IJL-TUBE Daum equipments funded by FEDER(EU), PIA, Region Grand Est, Metropole Grand Nancy and ICEEL.

## References

- [1] Kirilyuk A, Kimel A V and Rasing Th 2013 Laser-induced magnetization dynamics and reversal in ferrimagnetic alloys *Rep. Prog. Phys.* 7 (2), 026501
- [2] El Hadri M S, Hehn M, Malinowski G and Mangin S 2017 Materials and devices all-optical helicity-dependent switching *J. Phys. D: Appl. Phys.* 50 (13), 133002
- [3] Stanciu C D, Hansteen F, Kimel A V, Kirilyuk A, Tsukamoto A, Itoh A and Rasing T 2007 All-optical magnetic recording with circularly polarized light *Phys. Rev. Lett.* 99, 047601
- [4] Ostler T A *et al* 2012 Ultrafast heating as a sufficient stimulus for magnetization reversal in a ferrimagnet *Nat. Commun.* 3, 666
- [5] Radu I *et al* 2011 Transient ferromagnetic-like state mediating ultrafast reversal of antiferromagnetically coupled spins *Nature* 472, 205-208
- [6] Khorsand A R, Savoini M, Kirilyuk A, Kimel A V, Tsukamoto A, Itoh A and Rasing Th 2012 Role of magnetic circular dichroism in all-optical magnetic recording *Phys. Rev. Lett.* 108, 127205
- [7] Vahaplar K *et al* 2012 All-optical magnetization reversal by circularly polarized laser pulses: Experiment and multiscale modeling *Phys. Rev. B* 85,104402
- [8] Alebrand S, Gottwald M, Hehn M, Steil D, Cinchetti M, Lacour D, Fullerton E E, Aeschlimann M and Mangin S 2012 Light-induced magnetization reversal of high-anisotropy TbCo alloy films *Appl. Phys. Lett.* 101, 162408
- [9] Mangin S *et al* Engineered materials for all-optical helicity-dependent magnetic switching *Nat. Mater.* 13, 286-292
- [10] Lambert C H *et al* 2014 All-optical control of ferromagnetic thin films and nanostructures *Science* 345, 1337-1340
- [11] El Hadri M S *et al* 2016 Electrical characterization of all-optical helicity-dependent switching in ferromagnetic Hall crosses *Appl. Phys. Lett.* 108, 092405
- [12] Takahashi Y K, Medapalli R, Kasai S, Wang J, Ishioka K, Wee S H, Hellwig O, Hono K and Fullerton E E 2016 Accumulative magnetic switching of ultra-high-density recording media by circularly polarized light *Phys. Rev. Applied* 6, 054004
- [13] Chen J Y, He L, Wang J P and Li M 2017 All-optical switching of magnetic tunnel junctions with single subpicosecond laser pulses *Phys. Rev. Applied* 7, 021001
- [14] El Hadri M S, Pirro P, Lambert C-H, Petit-Watelot S, Quessab Y, Hehn M, Montaigne F, Malinowski G and Mangin S 2016 Two types of all-optical magnetization switching mechanisms using femtosecond laser pulses *Phys. Rev. B* 94, 064412
- [15] Schubert C, Hassdenteufel A, Matthes P, Schmidt J, Helm M, Bratschitsch R and Albrecht M 2014 All-optical helicity dependent magnetic switching in an artificial zero moment magnet *Appl. Phys. Lett.* 104, 082406
- [16] Hassdenteufel A, Schmidt J, Schubert C, Hebler B, Helm M, Albrecht M and Bratschitsch R 2015 Low remanence criterion for helicity-dependent all-optical magnetic switching in ferrimagnets and heterostructures *Phys. Rev. B* 91, 104331
- [17] Hebler B, Hassdenteufel A, Reinhardt P, Karl H and Albrecht M 2016 Ferrimagnetic Tb-Fe Alloy Thin Films: Composition and thickness dependence of magnetic properties and all-optical switching *Front. Mater.* 3, 8
- [18] El Hadri M S, Hehn M, Pirro P, Lambert C-H, Malinowski G, Fullerton E E and Mangin S 2016 Domain size criterion for the observation of all-optical helicity-dependent switching in magnetic thin films *Phys. Rev. B* 94, 064419
- [19] Chappert C *et al* 1998 Planar patterned magnetic media obtained by ion irradiation *Science* 280, 1919
- [20] Devolder T 2000 Light ion irradiation of Co/Pt systems: Structural origin of the decrease in magnetic anisotropy *Phys. Rev. B* 62, 5794
- [21] J. Ferré *et al* 1999 Irradiation induced effects on magnetic properties of Pt/Co/Pt ultrathin films *J. Magn. Magn. Mater.* 198-199, 191

- [22] Fassbender J, Ravelosona D and Samson Y 2004 Tailoring magnetism by light-ion irradiation *J. Phys. D: Appl. Phys.* 37, 16
- [23] Devolder T, Chappert C, Chen Y, Cambril E, Launois H, Bernas H, Ferré J and Jamet J P 1999 Patterning of planar magnetic nanostructures by ion irradiation *J. Vac. Sci. Technol. B* 17, 3177
- [24] Knepper J W and Yang F Y 2005 Oscillatory interlayer coupling in Co/Pt multilayers with perpendicular anisotropy *Phys. Rev. B* 71, 224403
- [25] Devolder *et al* 2001 Beam-induced magnetic property modifications: basics, nanostructure fabrication and potential applications *Nucl. Instrum. Methods B* 175, 375-381
- [26] Kooy C and Enz U 1960 Experimental and theoretical study of the domain configuration in thin layers of BaFe<sub>12</sub>O<sub>19</sub> *Philips Res. Rep.* 15, 7
- [27] Eyrich C *et al* 2012 Exchange stiffness in thin film Co alloys *J. Appl. Phys.* 111, 07C919
- [28] Cho J, Jung J, Cho S Y and You C Y *et al* 2015 Effect of annealing temperature on exchange stiffness of CoFeB thin films *J. Magn. Magn. Mater.* 395, 18
- [29] Mimura Y, Imamura N and Kobayashi T 1978 Thermomagnetic writing on Gd-Fe and Gd-Fe-Y amorphous films *Jpn. J. Appl. Phys.* 17, 1365
- [30] Hassdenteufel A, Hebler B, Schubert C, Liebig A, Teich M, Helm M, Aeschlimann M, Albrecht M, and Bratschitsch R 2013 Thermally assisted all-optical helicity dependent magnetic switching in amorphous Fe<sub>100-x</sub>Tb<sub>x</sub> alloy films *Adv. Mat.* 25, no. 22, 3122-3128
- [31] Gorchon J, Yang Y and Bokor J 2016 Model for multishot all-thermal all-optical switching in ferromagnets *Phys. Rev. B* 94, 020409(R)
- [32] Medapalli R, Afanasiev D, Kim D, Quessab Y, Monotoya S A, Kirilyuk A, Rasing Th, Kimel A V and Fullerton E E 2017 Multiscale dynamics of helicity-dependent all-optical magnetization reversal in ferromagnetic Co/Pt multilayers *Phys. Rev. B* 96 (22), 224421 
- [33] John R *et al* 2017 Magnetisation switching of FePt nanoparticle recording medium by femtosecond laser pulses *Sci. Rep.* 7, 4114
- [34] Herrera Diez L *et al* 2015 Controlling magnetic domain wall motion in the creep regime in He<sup>+</sup>-irradiated CoFeB/MgO films with perpendicular anisotropy *Appl. Phys. Lett.* 107, 032401
- [35] Quessab Y, Medapalli R, El Hadri M S, Hehn M, Malinowski G, Fullerton E E and Mangin S 2018 Helicity-dependent all-optical domain wall motion in ferromagnetic thin films *Phys. Rev. B* 97 (5), 054419 