



HAL
open science

Microwave-assisted extraction of high-molecular-weight hemicelluloses from spruce wood

Morad Chadni, Olivier Bals, Isabelle Ziegler-Devin, Nicolas Brosse, N. Grimi

► **To cite this version:**

Morad Chadni, Olivier Bals, Isabelle Ziegler-Devin, Nicolas Brosse, N. Grimi. Microwave-assisted extraction of high-molecular-weight hemicelluloses from spruce wood. *Comptes Rendus. Chimie*, 2019, 22 (8), pp.574-584. 10.1016/j.crci.2019.07.002 . hal-02290562

HAL Id: hal-02290562

<https://hal.univ-lorraine.fr/hal-02290562v1>

Submitted on 20 Jul 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial 4.0 International License

1 **MICROWAVE ASSISTED EXTRACTION OF HIGH MOLECULAR WEIGHT**
2 **HEMICELLULOSES FROM SPRUCE WOOD**
3 **EXTRACTION ASSISTEE PAR MICRO-ONDES DES HEMICELLULOSES DE HAUTS**
4 **POIDS MOLECULAIRES A PARTIR D'EPICEA DE BOIS**

5 **Morad Chadni^{a,b*}, Olivier Bals^a, Isabelle Ziegler-Devin^c, Nicolas Brosse^c, Nabil Grimi^{a,*}**

6 ^aSorbonne Université, Université de Technologie de Compiègne, Laboratoire Transformations
7 Intégrées de la Matière Renouvelable (UTC/ESCOM, EA 4297 TIMR), Centre de recherches
8 Royallieu, CS 60 319, 60 203 Compiègne cedex, France

9 ^bSOFREN, 336 Bureaux de la Coline, Bâtiment A - 7ème étage ; 92213 Saint-Cloud Cedex France

10 ^cUniversité de Lorraine – Faculté des Sciences et Technologies, Laboratoire d'Etudes et de Recherche
11 sur le Matériau Bois – EA 4370, Boulevard des Aiguillettes, BP 70239, 54506 Vandœuvre-Lès-Nancy
12 Cedex, France

13 **Corresponding author:**

14 **Morad Chadni**

15 Sorbonne Université, Université de Technologie de Compiègne, Laboratoire Transformations
16 Intégrées de la Matière Renouvelable (UTC/ESCOM, EA 4297 TIMR), Centre de recherches
17 Royallieu, CS 60 319, 60 203 Compiègne cedex, France

18 E-mail : morad.chadni@utc.fr (M. Chadni) ;

19 Telephone: +33 (0)3 44 23 44 42

20 **Nabil Grimi**

21 Sorbonne Université, Université de Technologie de Compiègne, Laboratoire Transformations
22 Intégrées de la Matière Renouvelable (UTC/ESCOM, EA 4297 TIMR), Centre de recherches
23 Royallieu, CS 60 319, 60 203 Compiègne cedex, France

24 nabil.grimi@utc.fr (N. Grimi)

25 Telephone: +33 (0)3 44 23 44 42

26

27 **Abbreviations**

28	Ac-GGM	Acetyl-Galactoglucomannan
29	ARX	Arabinoglucoronoxylan
30	DW	Dry wood
31	kDa	kilo Dalton
32	FTIR	Fourier Transform InfraRed
33	GGM	Galactoglucomannans
34	HMF	Hydroxymethylfurfural
35	HPLC	High performance liquid chromatography
36	M	Mole
37	MAE	Microwave Assisted Extraction
38	Mw	Molecular weight average
39	NREL/TP	National Renewable Energy Laboratory/ Technical Report
40	PD	Polymerization degree
41	W	Watts
42	PDI	Polydispersity index

43

44

45

46

47

48 **Abstract**

49 Microwave assisted extraction (MAE) at atmospheric pressure has been demonstrated as an efficient
50 technology for the extraction of polymeric hemicelluloses from spruce sawdust. This technology was
51 shown to be more efficient than conventional extraction. MAE leads to a high solubilization of wood
52 and a selective extraction of hemicelluloses polymers with high molecular weights. To optimize MAE,
53 different treatments power (125-573W) for a period of 60 min of a pre-soaked spruce sawdust in water
54 and 1M sodium hydroxide solution were tested. The yield of hemicellulose extraction increased with
55 the microwave power in both mediums, but with a clear advantage for pre-soaked samples in basic
56 medium. The characterization of extracted hemicelluloses has shown a high extraction selectivity
57 depending on the medium of impregnation of sawdust before MAE: high molecular mass acetylated
58 galactoglucomannans ($M_w \sim 41$ kDa) were isolated after a pre-soaking in water and higher molecular
59 mass arabinoglucoronoxylans ($M_w \sim 66$ kDa) in basic medium.

60 **Key words:** Wood, spruce, microwave-assisted extraction, hemicelluloses, polymers

61

62

63

64

65

66

67

68

69

70

71

72 **Résumé**

73 Le traitement par microondes (MAE) à pression atmosphérique a montré son efficacité pour
74 l'extraction des polymères d'hémicelluloses à partir de la sciure du bois d'épicéa. Cette technologie de
75 traitement s'est avérée plus efficace qu'un traitement thermique conventionnel. Le traitement
76 microondes a conduit à une solubilisation élevée du bois et une extraction sélective des polymères
77 d'hémicelluloses de poids moléculaires élevés. Pour optimiser le traitement MAE, différentes
78 puissances de traitements (125-573W pendant 60 minutes) ont été testées sur la sciure de bois
79 imprégnée soit dans de l'eau, soit dans une solution de NaOH à 1 mol/L. Les résultats ont montré que
80 le rendement d'extraction d'hémicelluloses augmentait avec l'augmentation de la puissance des micro-
81 ondes dans les deux milieux étudiés, avec un avantage pour la sciure imprégnée dans la solution
82 basique. La caractérisation des hémicelluloses extraites a montré une sélectivité d'extraction
83 importante en fonction du milieu d'imprégnation de la sciure de bois avant MAE: des
84 Galactoglucomannanes de masse moléculaire élevée ($M_w \sim 41$ kDa) ont été obtenus après
85 imprégnation dans l'eau et des arabinoglucoronoxylyanes de masse moléculaire élevée ($M_w \sim 66$ kDa)
86 en milieu de basique.

87

88 **Mots clés :** Bois, épicéa, extraction assistée par micro-ondes, hémicelluloses, polymères

89

90

91

92

93

94

95

1. Introduction

98 Non cellulosic wood polysaccharides are of great interest because of their structural diversity and
99 functionality. The potential for application of polymeric hemicelluloses has been demonstrated by
100 several authors [1–5]. As a result, new utilizations of hemicellulosic polysaccharides are emerging in
101 the fields of bioactive polymers, hydrocolloids, papermaking additive, or coating films [6,7].
102 Softwood hemicelluloses are mainly constituted of galactoglucomannans (GGM), approximately 14–
103 20% of the wood [8] and arabinoglucuronoxylans (7–10% of the wood). Softwood xylans are not
104 acetylated, but the xylan backbone is substituted at carbon 2 and 3 with 4-*O*-methyl- α -D-glucuronic
105 acid and α -L-arabinofuranosyl residues, respectively. Softwood xylan has a relatively low DP of about
106 100 [9]. GGM have been described to have an approximate degree of polymerisation of 100–150,
107 matching to a molar mass of 16–24 kDa [9]. The potential applications of spruce GGM in biomaterials
108 and hydrocolloids, such as barriers in food packaging, bioactive polysaccharides, hydrogels and fibers,
109 and health-promoting agents, have been studied [3,5,10–14].

110 The extraction of polymeric hemicelluloses has been investigated for years. Extraction of softwood
111 hemicelluloses has been studied by hydrothermal treatment at high temperatures (≥ 170 °C) [15,16], by
112 chemical extraction (alkaline) [17–20] and ionic liquids [21], by pressured hot water [22,23], and by
113 microwave heat-fractionation (> 180 °C) ([24–26].

114 The fractionation of wood at high temperatures leads to high solubilization of all macromolecules,
115 including hemicelluloses. However, the extraction at high temperatures for long reaction times led to a
116 low pH level, causing hydrolytic cleavages. As a result, GGMs extracted using these conditions are
117 generally highly deacylated and exhibit low molecular mass. Chemical treatments, especially alkaline
118 extractions are described to produce higher molecular weight hemicelluloses. Nevertheless, alkaline
119 extraction of hemicelluloses has some disadvantages. In addition to causing saponification of
120 polysaccharides, extraction with high concentrated alkaline solutions for long times can lead to peeling
121 reactions [27].

122 Nowadays, new process of extraction have been developed in order to reduce the amount of chemical
123 solvents, treatment time and temperature as well as energy consumption, hence improving the
124 recovery of valuable compounds with lower costs [28]. Microwave-assisted extraction is one of the
125 advantageous green extraction methods based on electromagnetic radiations with a frequency from 0.3
126 to 300 GHz. In this process, microwave irradiations are used to extract biomolecules. Unlike
127 conventional heat treatment where the energy is transferred to the material by convection, conduction
128 or radiation from the surface of the material, microwave energy is delivered directly to the material
129 through a molecular interaction with the electromagnetic field [29]. This interaction allows the heating
130 of the material and a transfer of energy from the inside to the outside of the cell [30].

131 Several studies have been carried out on the effect of microwaves on the extraction of hemicelluloses
132 from lignocellulosic materials. Microwave heating was shown to be efficient for the extraction of
133 softwood hemicelluloses [26,31,32]. In 2014, Panthapulakkal has observed a slightly higher xylans
134 extraction yield from wood fibers using microwave-assisted extraction (58 % of xylans) compared to
135 conventional extraction (54 %) [33]. Similar results have been reported in pretreatment of maize cane
136 using water and acid [34], alkaline pretreatment of *Panicum virgatum* [35]. Free sugars are generally
137 released from the degradation of polysaccharides during the extraction process [36]. Most of the
138 published works are carried out at temperature above 100 °C and at pressure above atmospheric
139 pressure, these conditions leading to a degradation and a depolymerization of hemicellulose chains.

140 In the current work, microwave heating at atmospheric pressure was carried out for the extraction of
141 polymeric hemicelluloses in mild conditions (temperature < 100 °C) in order to limit any possible
142 degradation and depolymerization. The effect of MAE was compared with a conventional treatment at
143 the same temperature. The effect of different conditions (power and/or temperature, pH of extraction)
144 on the yield and the physicochemical properties of extracted hemicelluloses was assessed.

145 **2. Material and method**

146 **2.1. Raw material**

147 Spruce sawdust was produced from a spruce tree from the Lorraine region of France with a particle
148 size of (1-5 mm) and stored at room temperature in a sealed polyethylene bags in the dark until use.

149 The average moisture content of the raw material was 10% w/w. The hemicelluloses content of the
150 sawdust was approximately 30 % w/w dry biomass. Carbohydrate composition of sawdust includes 72
151 % glucan, 7.5 % xylan, and 16.3 % of mannan and other sugars.

152 **2.2. Impregnation**

153 For each experiment, a mass of 20 g of spruce sawdust was soaked with a solution of 1M sodium
154 hydroxide (ratio solid/liquid = 1:7) or water (ratio solid/liquid = 1:7). The sawdust was left for 15
155 hours before treatment at room temperature.

156 **2.3. Experimental methodology of extraction**

157 **2.3.1. Microwave activation**

158 The microwave assisted extraction (MAE) experiments for the extraction of hemicelluloses from
159 spruce sawdust were carried out using a microwave laboratory system (230V-50 Hz, NEOS-GR,
160 Milestone, Italy). This mono-mode apparatus operates at 2.45 GHz with maximum delivered power of
161 900 W regulated in 10 Watt increments with a temperature and power feedback/control. This
162 instrument is equipped with time controller. The experiments were performed at atmospheric pressure
163 and time, power were controlled and followed by the software. The MAE experiments were conducted
164 in a glass extraction vessel. The samples were treated for 1h using different selected powers. Indeed,
165 the effect of microwave irradiation, nature of solvent and consumed energy were studied. The liquid-
166 to-solid ratio was fixed at 7 during microwave treatment.

167 The power values presented in all figures correspond to the effective power received by the sample
168 ($P_{effective}$) which was calculated by the following equations:

$$169 \quad P_{effective} = P_{input} \times Y_{MW}$$

170 (1)

$$171 \quad Y_{MW} = \frac{m \times C_p \times \Delta T(373 K - T_i)}{P_{input} \times t}$$

172 (2)

173 with P_{input} is the power immitted by microwave apparatus (Watts), Y_{MW} is the yield of microwave,
174 m is the weight of water (kg), T_i is the initial temperature of water (K), t is the necessary time of
175 treatment to increase temperature from T_i to T_f , C_p is the specific heat of water (4181.3 J/kg/K)

176 **2.3.2. Diffusion**

177 After microwave treatment, supplementary diffusion step was done by a heating under reflux at low
178 temperature to avoid degradation of polymeric chains (70 °C for 3 h). The liquid-to-solid ratio was
179 fixed at 15 (w/w).

180 For comparison, conventional extraction, without microwave treatment, from impregnated spruce
181 sawdust was treated in similar extraction vessel heated with a water bath at 100 °C for one hour (to
182 highlight the effect of microwave, the time to reach 100 °C for conventional extraction is not included)
183 and then followed by 3 hours of extraction at 70 °C.

184 **2.3.3. Separation of extracted hemicelluloses**

185 After each experiment, the extract was filtered on qualitative filter paper with retention particle size of
186 5–13 μm (VWR International, Fontenay-sous-Bois, France). The volume and end-pH of the extract
187 solutions were measured at room temperature shortly after the extraction. The liquid fraction from 1M
188 NaOH impregnated sawdust was neutralized to a pH of 5.5-6 by a solution of 72% H_2SO_4 . 10 mL
189 were taken from the filtered extract for analyses. The extract solution was concentrated by vacuum
190 evaporation (BUCHI, France) using a water bath at 50 °C. To precipitate high-molecular weight
191 hemicelluloses, four volumes of 95% ethanol were added to the liquid extracts. The liquid phase was
192 separated from the precipitated hemicelluloses by settling at room temperature and decantation.
193 Hemicelluloses were further separated from the remaining liquid by centrifugation at 4000 rpm for 10
194 min at room temperature. The precipitated hemicelluloses were re-dissolved in distilled water and
195 dialyzed with a dialysis membrane with a cut-off of 3.4 kDa (Spectrum Laboratories, USA). Finally,
196 dialyzed hemicelluloses solutions were freeze-dried. Fig.1. shows the experimental procedure of
197 extraction and separation from spruce sawdust.

198 **Fig. 1.** Scheme for extraction and separation of hemicelluloses from spruce sawdust using microwave
199 assisted extraction and conventional extraction.

200 **2.4. Measurement of monosaccharides and uronic acids using HAPE-PAD**

201 The monosaccharide content of the soluble fraction was analyzed according to [37] method. The sugar
202 concentrations were measured by HAPE-PAD (ICS-3000 Dionex, Dionex Corp., Sunnyvale, USA)
203 equipped with a Dionex CarboPac™ PA-20 (3 × 150 mm) analytical column. Filtered samples (20 µL)
204 were eluted at 35 °C and at 0.4 mL/min with the following composition: pure water 99.2%/250 mM
205 NaOH 0.8%: 0–20 min; pure water 75%/250 mM NaOH 20%/ NaOCOCH₃(1 M)- NaOH (20 mM) 5%
206 20–37 min; and pure water 40%/250 mM NaOH 20%/NaOCOCH₃ (1 M)- NaOH (20 mM) 40% 37–41
207 min. Each elution was followed by a wash and subsequent equilibration step. External sugar and
208 uronic acid standards were used for calibration (7 points per curve). The reagents and standards are
209 provided by Sigma-Aldrich and Fisher Scientific.

210 **2.5. Degradation products**

211 Degradation products of hemicelluloses (furfural, HMF, formic acid and levulinic acid) are analyzed
212 according to [38] procedure. All the products are quantified with an Ultimate 3000 HPLC system. The
213 components are separated in 45 min on a Agilent Hi-Plex H column at 55° C with an isocratic flow
214 rate of 0.4 mL·min⁻¹ of sulfuric acid (5. 10⁻³ M). Acids were detected by UV at 210 nm, while HMF
215 and furfural are detected by UV at 280 nm. An external calibration is performed with six calibration
216 points per standard. Reagents and standards are provided by Sigma-Aldrich.

217 **2.6. Acetyl content**

218 Acetyl content of extracted hemicelluloses was calculated by measuring the acetic acid concentration
219 of hemicelluloses after a saponification reaction. Acid acetic was measured following the same
220 procedure as degradation products with an UV detection at 210 nm instead of 280 nm.

221 **2.7. Size-exclusion chromatography (SEC)**

222 A Shimadzu Prominence HPLC system is used to determine molecular weight distribution of
223 hemicelluloses by gel filtration chromatography. The stationary phase is a Phenomenex Polysep GFC-
224 P guard column (7.8 x 35 mm), Phenomenex Polysep GFC-P3000 and GFC-P2000 analytical

225 columns (7.8 x 300 mm). The mobile phase is 0.25 M aqueous NaNO₃. Samples are filtered with a
226 0.45 μm membrane and 20 μL are injected. Samples are separated at 30 °C with a 0.5 mL min⁻¹ flow
227 and detection is done with a Refractive Index Detector (Shimadzu RID-20A). Each analysis runs for
228 70 min. aqueous solutions (1 mg/mL) of dextran standards with molecular weights of 1000–80,000
229 were used to prepare the calibration curve.

230 **2.8. FTIR**

231 FTIR analysis for extracted hemicelluloses were performed by a FTIR spectrophotometer (Thermo
232 Scientific iD3ZnSe ATR—Nicolet iS 5 FTIR Spectrometer unit). Hemicelluloses powder was placed
233 on a ZnSe crystal plate. Each IR spectrum was obtained over the wave number range of 400–4000
234 cm⁻¹ with eight scans at resolution of 4 cm⁻¹. The spectra were analyzed using ThermoScientific
235 OMNIC software

236 **2.9. 2D 13C–1H HSQC NMR spectroscopy**

237 ¹H NMR and ¹H-¹³C correlation 2D NMR (HSQC) spectra were recorded on a Bruker III 400 MHz
238 spectrometer equipped with a 5-mm BBFO probe. Experiment was conducted with 20 mg sample
239 dissolved in 1 ml D₂O. The number of collected complex points was 1024 for the ¹H-dimension with a
240 relaxation of 1.5- and 256-time increments were recorded in ¹³C-dimension. HSQC spectra were
241 taken at room temperature.

242

243 **2.10. Soluble lignin**

244 The acid-soluble lignin (ASL) content was determined from absorbance values at 205 nm according to
245 the laboratory analytical procedure (LAP) provided by the National Renewable Energy Laboratory
246 [37].

$$247 \quad \% \text{ ASL} = \frac{(Abs_{205 \text{ nm}} * V_t * 100)}{(DM_i)} \quad (3)$$

248 where V_t is the total volume of sample (L); DM_i is the initial dry matter (g).

249 **2.11. Wood solubilization**

250 Wood solubilization (WS) was presented as the ratio of the wood dissolved to the weight of the wood
251 used for extraction as expressed in the Eq. (4):

$$252 \quad WS = \frac{\textit{Weight of DW before extraction} - \textit{Weight of DW after extraction}}{\textit{Weight of DW before extraction}} \quad (4)$$

253 where DW stand for the term dry wood.

254

255 **3. Results and discussion**

256 **3.1 Wood solubilization**

257 Prior to microwave activation, spruce sawdust was impregnated in a solution of distilled water (neutral
258 medium) or 1 M NaOH (basic medium) for one night. The aim of the impregnation step is to open the
259 wood structure and to enhance the accessibility of hemicelluloses during the microwave extraction
260 [39–41]. After microwave treatment, a diffusion step was carried out during 3h at 70°C. The effect of
261 impregnation and diffusion steps on hemicelluloses yields in neutral medium (+ 19 % and 2.5 %
262 respectively) and (+ 16.4 % and +30 % respectively) in basic medium. See (**Fig. S1**) in SD section.
263 The temperature profiles for conventional extraction and for MAE at different power are also given in
264 SD section (**Fig. S2**).

265 Solubilization of wood was calculated using Eq.(3). As expected, the solubilization of wood is
266 significantly higher in basic medium (**Fig.3**). The microwave assisted extraction increase notably the
267 effect of sodium hydroxide (+81% for 573W). The advantage of MAE over conventional extraction
268 could be explained by the rapid and the selective heating of wood that lead to destabilization and
269 structural damage of wood matrix, thus improving biomolecules extraction, and also the heat and mass
270 transfer which act in the same direction. Furthermore, the effect of MAE is not only related to the fast
271 increase of temperature, but also to the power transmitted to the wood matrix which destabilizes and
272 weakens structural linkages between lignin and carbohydrates. In conventional extraction, heat
273 transfer and mass transfer had opposite directions [42].

274 Wood solubilization steadily increased with the increase of microwave power. The solubilization of
275 sawdust is mainly affected by microwave power which is the main parameter affecting the irradiation

276 strength and the rate of temperature increase (**Fig.2**). For basic impregnation, alkaline solutions
277 increase the water absorption capacity, swell up cellulosic fibers and decrease their crystallinity, and
278 thus increase the specific surface area [43]. Based on previous reports, the mechanism of action is due
279 to the decrease of intermolecular hydrogen bonds by solvation [44] as well as lignin- hemicelluloses
280 bonds scissions.

281 **Fig.2.** Solubilization of wood after MAE and conventional extractions (1 h under
282 MW, 3h diffusion)

283 3.2 Hemicellulose extraction

284 Polymeric hemicelluloses extracted in the liquid fraction were quantified by subtracting the amount of
285 monomeric sugars (determined by ionic chromatography) from the total sugars content in the liquid
286 fraction obtained after extraction. As expected, **Fig.3 (A and B)** shows that the extraction of
287 hemicelluloses highly depends on the pH of the impregnation step, as it affects the hydrolysis of the
288 hemicelluloses-lignin linkages. In fact, at maximum power (573 Watts) when sodium hydroxide was
289 used as solvent, the effect of microwave on the extraction yield was higher as compared to the
290 conventional extraction (32.3 and 22.5 mg/ g of dry wood respectively). On the other hand, lower
291 extraction yields were observed using water as solvent. To explain the effect of MAE on wood,
292 **Panthapulakkal et al., (2015)** have suggested that the disruption of wood structure and the rupture of
293 wood fibers are due to the selective interaction of the microwaves with the inhomogeneous
294 lignocellulosic materials [35, 45] have found that microwave treatment improves surface disruption
295 and breaking of lignin structures in alkaline treated switch grass, while in conventional heating, the
296 fibers remain intact.

297 The composition of the liquid fraction in terms of monomeric sugars (after acid hydrolysis) at different
298 conditions of microwave extraction are also given in the **Fig.3 (A and B)**. Polysaccharides extracted in
299 neutral medium are mainly composed of mannose (33%), glucose (18%) and galactose (20%). As a
300 result we can assume that the hemicellulosic extract is mainly composed of galactoglucomannans [9].
301 On the other hand, in the basic medium the high contents in xylose (57%) and arabinose (10%)
302 suggests the dominant extraction of arabinoxylans. This selectivity of extraction as a function of the

303 pH of the medium is in accordance with previous reports. It has been described that in neutral or mild
304 acid medium (pH \approx 5), hemicelluloses extracted from softwood are rich in mannose, acetyled
305 glucomannans exhibiting a relatively high water solubility [9,32]. In basic medium, the high xylose
306 content can be rationalized by the dominant extraction of arabinoglucuronoxylans. In fact,
307 arabinoglucuronoxylans are substituted with methyl-glucuronic acid and arabinose moiety which
308 affect their solubility [46]. Thornton **et al., (1994)** have found from the Norway spruce wood that at
309 pH values greater than 10, the concentration of extracted arabinose and xylose units increase,
310 suggesting the release of arabino-(4-*O*-methylglucurono)xylans [47].

311 **Fig.3.** Yield and sugar composition of extracted hemicelluloses polymers in neutral medium (A) and
312 basic medium (B)

313 The oligo- and polymeric fraction of the extracted hemicelluloses were calculated by subtracting the
314 amount of monomeric sugars from the total sugars content in the extracts. The monomer proportion is
315 very low (< 2%) whatever the extraction conditions, the mild conditions used in this study (T<100°C,
316 pH>5) limiting the hydrolytic cleavage of hemicelluloses. Based on literature data, the hydrolysis of
317 hemicellulose into monomeric sugars is promoted by extraction at higher temperatures for longer
318 times and lower pH level [48].

319 Solubilization of lignin during the extraction of hemicelluloses is expected especially in basic medium.
320 As shown in (**Fig.4.B**) the amount of soluble lignin increased after MW sawdust irradiation. A
321 significant difference was observed for MAE at high power input (4.8% and 0.49% at 573 W for 1h
322 compared to 3.3 % and 0.3 % at 100 °C for 1h at basic and neutral medium respectively). Acetic,
323 uronic, formic and levulinic acids have also been detected in the liquid effluents. The carboxylic acids
324 contents were relatively important in basic medium (**Fig.4. A**). Acetic and formic acids are the major
325 carboxylic acids formed (6 and 1.7 g/l respectively). Levulinic acid present the lowest concentration
326 accounting for 0.3 g/l. The peeling reactions occurring during alkaline treatments lead to endwise
327 degradation of polysaccharides with formation of formic acid and different dihydroxy and
328 dicarboxylic acid [49]. Acetic acid is released from the hemicellulosic backbone by saponification of
329 acetate groups.

330 **Fig.4.** Degradation products in the liquid fraction in basic medium (A) and ASL (%) (B)

331 **3.3 composition of the recovered hemicelluloses powder**

332 The sugar composition of polymeric hemicelluloses recovered after precipitation and dialyze is similar
333 to the sugar composition of the liquid fraction (**Fig.5**). Galactoglucomannans and arabinoxylans are
334 the main polysaccharides extracted in neutral and basic medium respectively. In neutral medium,
335 MAE promotes the extraction of arabinose and galactose compared to conventional extraction. In fact,
336 hemicelluloses obtained from neutral medium are accounting for 24% and 19.5 % of galactose, for
337 10.5 % and 5% of arabinose for MW (573W) and conventional extraction respectively. The advantage
338 of MAE seems to be not only due to the temperature, but also owed to the physicochemical
339 interactions induced by microwave heating of the wood matrix.

340 **Fig.5.** Sugar composition of recovered hemicelluloses by MAE and conventional extraction

341 In native softwood, mannopyranosyl units are acetylated at C-2 or C-3 with a degree of acetylation of
342 about 0.5 [17,9]. In our study, the precipitated hemicelluloses recovered from a neutral medium had a
343 lower degree of acetylation, in the range of 0.10-0.15. In basic medium, the acetyl groups have been
344 totally released from the hemicellulosic backbone by saponification.

345 These results have been confirmed by a FTIR study. In the **Fig. 6** two weak absorbances at 1735 and
346 1247 cm^{-1} due to acetyl groups attached to the hemicelluloses chains were observed for the fractions
347 extracted in neutral media but not for the basic extracts. Moreover, the absorption at 1515 cm^{-1}
348 observed in all the hemicellulosic fractions was assigned to lignin's aromatic skeletal vibrations [50].
349 The higher intensity of this signal for the fractions isolated from basic media confirms the higher
350 lignin contamination for hemicelluloses obtained in basic medium compared to those obtained in
351 neutral medium previously observed (**Fig. 4.B**).

352 **Fig.6.** FTIR spectra of extracted hemicelluloses

353 2D ^1H - ^{13}C HSQC spectra clearly shows the typical signal spots expected for the hemicellulosic
354 moieties. In basic medium (**Fig 7. B**), β -D-xylopyranoside units are specified by these signals at
355 $\delta\text{C}/\delta\text{H}$ 60/3.4; 62/4; 72/4.3; 72.5/3.2; 74/3.5; 72.5/3.7. The signals at 72/ 3.5 is assigned to α -D-

356 xylopyranoside of xylans reducing end and at 62/3.3 and 71/3.5 for β -D-xylopyranoside of xylans non
357 reducing end. In neutral medium (**Fig 7. A**), the signals at 3.4/74; 3.5/74; 3.8/76; 4.2/70 are attributed
358 to β -D-mannopyranoside. The same results were found by [51]. The signal in neutral medium at
359 5.45/72 was assigned to 6-*O*-acetyl β -D-mannopyranoside. In fact, as confirmed by the FTIR analysis,
360 the extraction in neutral medium preserved some of the acetyl groups of the backbone units of GGM.
361 These results are in close agreement to those obtained by [47] who found that deacetylation of the *O*-
362 acetyl-galactoglucomannans appeared to begin at pH values above 8. The presence of acetyl residues
363 is critical for the water-solubility of GGM. The acetyl moieties are generally cleaved during the
364 extraction at high temperatures leading to the release of acetic acid. The signals at 98/5.25 and 82/3.1
365 are assigned to 4-*O*-methyl- α -D-glucuronic acids that are spotted only in basic medium which
366 confirms the extraction of arabinoglucuronoxylans in these conditions.

367 **Fig.7.** HSQC spectra of extracted hemicelluloses (A) in neutral medium; (B) in basic medium

368 Weight-average (M_w) and number-average (M_n) molecular weights, as well as the polydispersity index
369 (PDI) were determined by gel-permeation chromatography. The results in Table 2 show that
370 hemicellulose fractions isolated from microwave irradiation display higher molecular mass as
371 compared to the conventionally extracted fractions (for conventional extraction, M_w ~38000 and
372 ~56000 g.mol⁻¹ in neutral and basic medium respectively and ~42000 and ~67000 g mol⁻¹ for
373 hemicelluloses extracted with microwave activation in neutral and basic medium respectively). It can
374 be also observed that the hemicelluloses extracted in neutral medium had much lower molecular
375 weights than those isolated in basic medium. These results were in close agreement to those reported
376 by [52] who found that increasing the alkali concentration during extraction increased the M_w of
377 extracted hemicelluloses by 46%. They suggested that the extraction of high M_w hemicelluloses was
378 owed to the increase of the co-extraction of lignin-carbohydrates complexes. Considering the sugar
379 composition given in **Fig.5**, it can be concluded that the neutral medium released relatively low
380 molecular-weight GGM, while basic extraction allowed the recovery of high molecular mass xylans.

381 **Table 1.** Weight-average (M_w) and number-average (M_n) molecular weights, polydispersity
382 index (PDI) and the polymerization degree (PD) of the hemicellulosic fractions obtained with
383 MAE at 573 W and conventional extraction
384

385
386
387

388 **4. Conclusion**

389
390 In this study the extraction of the hemicelluloses polymers by MAE at atmospheric pressure was
391 investigated. The highest amount of hemicelluloses extracted was 27.5 mg/g of dry wood from pre-
392 soaked wood in 1M NaOH solution using microwave treatment at 573 W for 1 h over. At this
393 condition, the M_w of extracted hemicellulose chains was 66 kDa. At the same conditions, i.e.,
394 temperature and time, the yield and the M_w were lower using a conventional heating than microwave,
395 which highlights the efficacy of MAE for extraction of hemicelluloses chains from spruce sawdust.
396 Pre-soaking in sodium hydroxide improves the solubilization of wood and hence the extraction of high
397 molecular weight hemicelluloses. However, pre-soaking in water preserve acetyl groups in the
398 hemicellulose chains which could be advantageous in various polymer applications. High extraction
399 selectivity was observed as a function of the pre-soaking medium: acetylated galactoglucomannans
400 were isolated after pre-soaking in neutral medium and high molecular mass arabinoglucoronoxylans in
401 basic medium. MAE at atmospheric pressure and mild conditions (temperature < 100°C and pH 5) has
402 shown its effectiveness to extract high molecular weight hemicelluloses chains from spruce wood with
403 less depolymerization and degradation. This technology has a great potential as an alternative method
404 to autohydrolysis and hydrothermal treatments of wood in the aspects of molecular weight of extracted
405 hemicelluloses.

406
407
408

409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447

Conflict of interest

The authors have no conflict of interest.

Acknowledgements

This work was financially supported by SOFREN Company and ANRT “Association National de la Recherche et de la Technologie”. The authors appreciate the financial support from SOFREN and ANRT. LERMAB is supported by the French National Research Agency through the Laboratory of Excellence ARBRE (ANR-12- LABXARBRE-01).

- 449 [1] L. Bai, H. Hu, J. Xu, Influences of configuration and molecular weight of hemicelluloses on
450 their paper-strengthening effects, *Carbohydr. Polym.* 88 (2012) 1258–1263.
451 doi:10.1016/j.carbpol.2012.02.002.
- 452 [2] H. Lindqvist, J. Holmback, A. Rosling, K. Salminen, B. Holmbom, M. Auer, A. Sundberg,
453 Galactoglucomannan Derivatives and Their Application in Papermaking, *BioResources.* 8
454 (2013) 994–1010. doi:10.15376/biores.8.1.994-1010.
- 455 [3] K.S. Mikkonen, M. Tenkanen, Sustainable food-packaging materials based on future biorefinery
456 products: Xylans and mannans, *Trends Food Sci. Technol.* 28 (2012) 90–102.
457 doi:10.1016/j.tifs.2012.06.012.
- 458 [4] P. Alvira, E. Tomás-Pejó, M. Ballesteros, M.J. Negro, Pretreatment technologies for an efficient
459 bioethanol production process based on enzymatic hydrolysis: A review, *Bioresour. Technol.*
460 101 (2010) 4851–4861. doi:10.1016/j.biortech.2009.11.093.
- 461 [5] J. Hartman, A.-C. Albertsson, J. Sjöberg, Surface- and bulk-modified galactoglucomannan
462 hemicellulose films and film laminates for versatile oxygen barriers, *Biomacromolecules.* 7
463 (2006) 1983–1989. doi:10.1021/bm060129m.
- 464 [6] S. Willför, K. Sundberg, M. Tenkanen, B. Holmbom, Spruce-derived mannans – A potential raw
465 material for hydrocolloids and novel advanced natural materials, *Carbohydr. Polym.* 72 (2008)
466 197–210. doi:10.1016/j.carbpol.2007.08.006.
- 467 [7] T. Persson, A.-K. Nordin, G. Zacchi, A.-S. Jönsson, Economic evaluation of isolation of
468 hemicelluloses from process streams from thermomechanical pulping of spruce, *Appl. Biochem.*
469 *Biotechnol.* 137–140 (2007) 741–752. doi:10.1007/s12010-007-9094-7.
- 470 [8] S. Willför, R. Sjöholm, C. Laine, M. Roslund, J. Hemming, B. Holmbom, Characterisation of
471 water-soluble galactoglucomannans from Norway spruce wood and thermomechanical pulp,
472 *Carbohydr. Polym.* 52 (2003) 175–187. doi:10.1016/S0144-8617(02)00288-6.
- 473 [9] T.E. Timell, Recent progress in the chemistry of wood hemicelluloses, *Wood Sci. Technol.* 1
474 (1967) 45–70. doi:10.1007/BF00592255.
- 475 [10] N.M.L. Hansen, D. Plackett, Sustainable Films and Coatings from Hemicelluloses: A Review,
476 *Biomacromolecules.* 9 (2008) 1493–1505. doi:10.1021/bm800053z.
- 477 [11] K.S. Mikkonen, Heikkilä, Mari I, Willför, S.M. R, M. Tenkanen, Films from Glyoxal-
478 Crosslinked Spruce Galactoglucomannans Plasticized with Sorbitol, *Int. J. Polym. Sci.* 2012
479 (2012) e482810. doi:10.1155/2012/482810.
- 480 [12] H.A. Ruiz, M.A. Cerqueira, H.D. Silva, R.M. Rodríguez-Jasso, A.A. Vicente, J.A. Teixeira,
481 Biorefinery valorization of autohydrolysis wheat straw hemicellulose to be applied in a polymer-
482 blend film, *Carbohydr. Polym.* 92 (2013) 2154–2162. doi:10.1016/j.carbpol.2012.11.054.
- 483 [13] C. Peroval, F. Debeaufort, A.-M. Seuvre, P. Cayot, B. Chevet, D. Despré, A. Voilley, Modified
484 arabinoxylan-based films, *J. Membr. Sci.* 233 (2004) 129–139.
485 doi:10.1016/j.memsci.2004.01.009.
- 486 [14] E. Fredon, R. Granet, R. Zerrouki, P. Krausz, L. Saulnier, J.F. Thibault, J. Rosier, C. Petit,
487 Hydrophobic films from maize bran hemicelluloses, *Carbohydr. Polym.* 49 (2002) 1–12.
488 doi:10.1016/S0144-8617(01)00312-5.
- 489 [15] J. Krogell, E. Korotkova, K. Eränen, A. Pranovich, T. Salmi, D. Murzin, S. Willför,
490 Intensification of hemicellulose hot-water extraction from spruce wood in a batch extractor –
491 Effects of wood particle size, *Bioresour. Technol.* 143 (2013) 212–220.
492 doi:10.1016/j.biortech.2013.05.110.
- 493 [16] T. Song, A. Pranovich, B. Holmbom, HOT-WATER EXTRACTION OF GROUND SPRUCE
494 WOOD OF DIFFERENT PARTICLE SIZE, *BioResources.* 7 (2012) 4214–4225.
495 doi:10.15376/biores.7.3.4214-4225.
- 496 [17] P. Capek, M. Kubacková, J. Alföldi, L. Bilisics, D. Lisková, D. Kákoniová,
497 Galactoglucomannan from the secondary cell wall of *Picea abies* L. Karst, *Carbohydr. Res.* 329
498 (2000) 635–645.

- 499 [18] I. Gabrielli, P. Gatenholm, W.G. Glasser, R.K. Jain, L. Kenne, Separation, characterization and
500 hydrogel-formation of hemicellulose from aspen wood, *Carbohydr. Polym.* 43 (2000) 367–374.
501 doi:10.1016/S0144-8617(00)00181-8.
- 502 [19] S.F. Curling, P.A. Fowler, C.A.S. Hill, Development of a method for the production of
503 hemicellulosic gels from Sitka spruce, *Carbohydr. Polym.* 69 (2007) 673–677.
504 doi:10.1016/j.carbpol.2007.02.003.
- 505 [20] C. Alvarez-Vasco, X. Zhang, Alkaline hydrogen peroxide pretreatment of softwood:
506 Hemicellulose degradation pathways, *Bioresour. Technol.* 150 (2013) 321–327.
507 doi:10.1016/j.biortech.2013.10.020.
- 508 [21] I. Anugwom, P. Mäki-Arvela, P. Virtanen, S. Willför, R. Sjöholm, J.-P. Mikkola, Selective
509 extraction of hemicelluloses from spruce using switchable ionic liquids, *Carbohydr. Polym.* 87
510 (2012) 2005–2011. doi:10.1016/j.carbpol.2011.10.006.
- 511 [22] T. Song, A. Pranovich, I. Sumerskiy, B. Holmbom, Extraction of galactoglucomannan from
512 spruce wood with pressurised hot water, *Holzforschung.* 62 (2008) 659–666.
513 doi:10.1515/HF.2008.131.
- 514 [23] G. Gallina, Á. Cabeza, H. Grénman, P. Biasi, J. García-Serna, T. Salmi, Hemicellulose
515 extraction by hot pressurized water pretreatment at 160°C for 10 different woods: Yield and
516 molecular weight, *J. Supercrit. Fluids.* (2017). doi:10.1016/j.supflu.2017.10.001.
- 517 [24] T.A. Gulbrandsen, I.A. Johnsen, M.T. Opedal, K. Toven, K. Øyaas, A. Pranovich, J.-P. Mikkola,
518 B.H. Hoff, Extracting hemicelluloses from softwood and bagasse as oligosaccharides using pure
519 water and microwave heating, *Cell Chem Tech.* 49 (2015) 117–126.
- 520 [25] M. Palm, G. Zacchi, Extraction of hemicellulosic oligosaccharides from spruce using microwave
521 oven or steam treatment, *Biomacromolecules.* 4 (2003) 617–623. doi:10.1021/bm020112d.
- 522 [26] J. Lundqvist, A. Teleman, L. Junel, G. Zacchi, O. Dahlman, F. Tjerneld, H. Stålbrand, Isolation
523 and characterization of galactoglucomannan from spruce (*Picea abies*), *Carbohydr. Polym.* 48
524 (2002) 29–39. doi:10.1016/S0144-8617(01)00210-7.
- 525 [27] J.-Å. Hansson, N. Hartler, Alkaline Degradation of Pine Glucomannan, *Holzforsch. - Int. J. Biol.*
526 *Chem. Phys. Technol. Wood.* 24 (2009) 54–59. doi:10.1515/hfsg.1970.24.2.54.
- 527 [28] B. Kaufmann, P. Christen, Recent extraction techniques for natural products: microwave-assisted
528 extraction and pressurised solvent extraction., (2002).
529 <https://www.ncbi.nlm.nih.gov/pubmed/12018022> (accessed May 2, 2018).
- 530 [29] F. Chemat, M. Abert-Vian, X. Fernandez, Microwave-Assisted Extraction of Essential Oils and
531 Aromas, (2012). https://link.springer.com/chapter/10.1007%2F978-1-4614-4830-3_3 (accessed
532 May 2, 2018).
- 533 [30] F. Chemat, M. Abert Vian, Zill-E-Huma, Microwave assisted - separations: Green chemistry in
534 action, (2009). [https://www.researchgate.net/publication/285912820_Microwave_assisted_-_](https://www.researchgate.net/publication/285912820_Microwave_assisted_-_separations_Green_chemistry_in_action)
535 [_separations_Green_chemistry_in_action](https://www.researchgate.net/publication/285912820_Microwave_assisted_-_separations_Green_chemistry_in_action) (accessed May 2, 2018).
- 536 [31] M. Palm, G. Zacchi, Extraction of Hemicellulosic Oligosaccharides from Spruce Using
537 Microwave Oven or Steam Treatment, *Biomacromolecules.* 4 (2003) 617–623.
538 doi:10.1021/bm020112d.
- 539 [32] T. Song, A. Pranovich, B. Holmbom, Separation of polymeric galactoglucomannans from hot-
540 water extract of spruce wood, *Bioresour. Technol.* 130 (2013) 198–203.
541 doi:10.1016/j.biortech.2012.11.149.
- 542 [33] F.S. Panthapulakkal, Microwave Assisted Extraction of Xylan, University of Toronto, 2014.
543 <https://tspace.library.utoronto.ca/handle/1807/65713> (accessed June 23, 2016).
- 544 [34] J. Shi, Y. Pu, B. Yang, A. Ragauskas, C.E. Wyman, Comparison of microwaves to fluidized
545 sand baths for heating tubular reactors for hydrothermal and dilute acid batch pretreatment of
546 corn stover, *Bioresour. Technol.* 102 (2011) 5952–5961. doi:10.1016/j.biortech.2011.03.027.
- 547 [35] Z. Hu, Z. Wen, Enhancing enzymatic digestibility of switchgrass by microwave-assisted alkali
548 pretreatment, *Biochem. Eng. J.* 38 (2008) 369–378. doi:10.1016/j.bej.2007.08.001.
- 549 [36] C. Liu, C.E. Wyman, The Effect of Flow Rate of Compressed Hot Water on Xylan, Lignin, and
550 Total Mass Removal from Corn Stover, *Ind. Eng. Chem. Res.* 42 (2003) 5409–5416.
551 doi:10.1021/ie030458k.
- 552 [37] NREL/TP-510-42618, B. Hames, R. Ruiz-Peinado, C. Scarlata, W.J. Sluiter, D. Templaton, A.D.
553 Crocker, M.D. Sluiter, Determination of structural carbohydrates and lignin in biomass,

- 554 Technical Report NREL/TP-510-42618, National Renewable Energy Laboratory, Golden, CO,
555 (2010). <https://www.scienceopen.com/document?vid=a3e04a5d-b049-4506-9739-b0c71a39b992>
556 (accessed October 8, 2018).
- 557 [38] A. NREL/TP-510-42623, Determination of Sugars, Byproducts, and Degradation Products in
558 Liquid Fraction Process Samples: Laboratory Analytical Procedure (LAP); Issue Date:
559 12/08/2006, Tech. Rep. (2008) 14.
- 560 [39] V. Pasquet, J.-R. Chérouvrier, F. Farhat, V. Thiéry, J.-M. Piot, J.-B. Bérard, R. Kaas, B. Serive,
561 T. Patrice, J.-P. Cadoret, L. Picot, Study on the microalgal pigments extraction process:
562 Performance of microwave assisted extraction, *Process Biochem.* 46 (2011) 59–67.
563 doi:10.1016/j.procbio.2010.07.009.
- 564 [40] W. Zhang, S. Xu, Microwave-assisted extraction of secoisolariciresinol diglucoside from
565 flaxseed hull, *J. Sci. Food Agric.* 87 (2007) 1455–1462. doi:10.1002/jsfa.2793.
- 566 [41] P.S. Wakte, B.S. Sachin, A.A. Patil, D.M. Mohato, T.H. Band, D.B. Shinde, Optimization of
567 microwave, ultra-sonic and supercritical carbon dioxide assisted extraction techniques for
568 curcumin from *Curcuma longa*, *Sep. Purif. Technol.* 79 (2011) 50–55.
569 doi:10.1016/j.seppur.2011.03.010.
- 570 [42] N. Flórez, E. Conde, H. Domínguez, Microwave assisted water extraction of plant compounds, *J.*
571 *Chem. Technol. Biotechnol.* 90 (2015) 590–607. doi:10.1002/jctb.4519.
- 572 [43] L. f. Wen, K. c. Chang, G. Brown, D. d. Gallaher, Isolation and Characterization of
573 Hemicellulose and Cellulose from Sugar Beet Pulp, *J. Food Sci.* 53 (1988) 826–829.
574 doi:10.1111/j.1365-2621.1988.tb08963.x.
- 575 [44] J.-L. Wen, L.-P. Xiao, Y.-C. Sun, S.-N. Sun, F. Xu, R.-C. Sun, X.-L. Zhang, Comparative study
576 of alkali-soluble hemicelluloses isolated from bamboo (*Bambusa rigida*), *Carbohydr. Res.* 346
577 (2011) 111–120. doi:10.1016/j.carres.2010.10.006.
- 578 [45] S. Panthapulakkal, D. Kirk, M. Sain, Alkaline extraction of xylan from wood using microwave
579 and conventional heating, *J. Appl. Polym. Sci.* 132 (2015) n/a-n/a. doi:10.1002/app.41330.
- 580 [46] A. Svård, E. Brännvall, U. Edlund, Rapeseed straw as a renewable source of hemicelluloses:
581 Extraction, characterization and film formation, *Carbohydr. Polym.* 133 (2015) 179–186.
582 doi:10.1016/j.carbpol.2015.07.023.
- 583 [47] J. Thornton, R. Ekman, B. Holmbom, C. Pettersson, Effects of Alkaline Treatment on Dissolved
584 Carbohydrates in Suspensions of Norway Spruce Thermomechanical Pulp, *J. Wood Chem.*
585 *Technol.* 14 (1994) 177–194. doi:10.1080/02773819408003093.
- 586 [48] T. Song, A. Pranovich, B. Holmbom, Separation of polymeric galactoglucomannans from hot-
587 water extract of spruce wood, *Bioresour. Technol.* 130 (2013) 198–203.
588 doi:10.1016/j.biortech.2012.11.149.
- 589 [49] D. Fengel, G. Wegener, *Wood: chemistry, ultrastructure, reactions*, Walter de Gruyter, 1983.
590 [https://books.google.fr/books?hl=fr&lr=&id=x1B4uITKnt0C&oi=fnd&pg=PA1&dq=Fengel+D](https://books.google.fr/books?hl=fr&lr=&id=x1B4uITKnt0C&oi=fnd&pg=PA1&dq=Fengel+D+%26+Wegener+G,+Wood.+Chemistry,+Ultrastructure,+Reactions+(Walter+de+Gruyter,+Berli n,+New+York&ots=ecb1YbRrXZ&sig=wFyKkHkl2y0XzK5SR0aSJBUymKE)
591 [+%26+Wegener+G,+Wood.+Chemistry,+Ultrastructure,+Reactions+\(Walter+de+Gruyter,+Berli](https://books.google.fr/books?hl=fr&lr=&id=x1B4uITKnt0C&oi=fnd&pg=PA1&dq=Fengel+D+%26+Wegener+G,+Wood.+Chemistry,+Ultrastructure,+Reactions+(Walter+de+Gruyter,+Berli n,+New+York&ots=ecb1YbRrXZ&sig=wFyKkHkl2y0XzK5SR0aSJBUymKE)
592 [n,+New+York&ots=ecb1YbRrXZ&sig=wFyKkHkl2y0XzK5SR0aSJBUymKE](https://books.google.fr/books?hl=fr&lr=&id=x1B4uITKnt0C&oi=fnd&pg=PA1&dq=Fengel+D+%26+Wegener+G,+Wood.+Chemistry,+Ultrastructure,+Reactions+(Walter+de+Gruyter,+Berli n,+New+York&ots=ecb1YbRrXZ&sig=wFyKkHkl2y0XzK5SR0aSJBUymKE) (accessed July
593 21, 2016).
- 594 [50] J.B. Reeves, Infrared spectroscopic studies on forage and by-product fibre fractions and lignin
595 determination residues, *Vib. Spectrosc.* 5 (1993) 303–310. doi:10.1016/0924-2031(93)87006-F.
- 596 [51] N. Giummarella, M. Lawoko, Structural Insights on Recalcitrance during Hydrothermal
597 Hemicellulose Extraction from Wood, *ACS Sustain. Chem. Eng.* 5 (2017) 5156–5165.
598 doi:10.1021/acssuschemeng.7b00511.
- 599 [52] R. Sun, J.M. Lawther, W.B. Banks, Fractional and structural characterization of wheat straw
600 hemicelluloses, *Carbohydr. Polym.* 29 (1996) 325–331. doi:10.1016/S0144-8617(96)00018-5.

601

602

603

604

605

606 **Figure captions:**

607 **Fig. 1.** Scheme for extraction and separation of hemicelluloses from spruce sawdust using microwave
608 assisted extraction and conventional extraction.

609 **Fig.2.** Solubilization of wood after MAE and conventional extractions (1 h under MW, 3h diffusion)

610 **Fig.3.** Yield and sugar composition of extracted hemicelluloses polymers in neutral medium (A) and
611 basic medium (B)

612 **Fig.4.** Degradation products in the liquid fraction in basic medium (A) and ASL (%) (B)

613 **Fig.5.** Sugar composition of recovered hemicelluloses by MAE and conventional extraction

614 **Fig.6.** FTIR spectra of extracted hemicelluloses

615 **Fig.7.** HSQC spectra of extracted hemicelluloses (A) in neutral medium; (B) in basic medium

616

617

618

619

620 **Supplementary data:**

621 **S1.** Effect of the impregnation and the diffusion on the yield of extracted hemicelluloses by MAE at

622 573 Watts in neutral and basic mediums

623 **S2.** Temperature profile during MAE and conventional extraction

624


625 **Table caption:**


626

627 **Table 1.** Weight-average (M_w) and number-average (M_n) molecular weights, polydispersity
628 index (PDI) and the polymerization degree (PD) of the hemicellulosic fractions obtained with
629 MAE at 573 W and conventional extraction


630

631








(A)




(B)












Table 1. Weight-average (M_w) and number-average (M_n) molecular weights, polydispersity index (PDI) and the polymerization degree (PD) of the hemicellulosic fractions obtained with MAE at 573 W and conventional extraction

	Basic medium				Neutral Medium			
	M_n	M_w	PDI	PD	M_n	M_w	PDI	PD
Conventional	27266	56298	2.06	351	20730	37870	1.82	236
MAE 573 W	54227	66564	1.22	416	23875	41589	1.74	259