Condensed tannins from grape pomace: Characterization by FTIR and MALDI TOF and production of environment friendly wood adhesive

Lan Ping, Antonio Pizzi, Zhou Ding Guo, Nicolas Brosse

► To cite this version:

Lan Ping, Antonio Pizzi, Zhou Ding Guo, Nicolas Brosse. Condensed tannins from grape pomace: Characterization by FTIR and MALDI TOF and production of environment friendly wood adhesive. Industrial Crops and Products, 2012, 40, pp.13-20. 10.1016/j.indcrop.2012.02.039 . hal-03140957

HAL Id: hal-03140957

<https://hal.univ-lorraine.fr/hal-03140957>

Submitted on 14 Feb 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Distributed under a Creative Commons Attribution - NonCommercial - NoDerivatives| 4.0
International License

Condensed tannins from grape pomace : characterization by FTIR and MALDI TOF and production of environment friendly wood adhesive

Authors :

Lan Ping^{a,b}, Antonio Pizzi^b, Zhou Ding Guo^a, Nicolas Brosse^{b*}

Affiliations :

^aCollege of Wood Science and Technology, Nanjing Forestry University, Nanjing 210037,
China

^bLaboratoire d'Etude et de Recherche sur le MAteriau Bois, Faculté des Sciences et
Techniques, Nancy-Université, Bld des Aiguillettes, F-54500 Vandoeuvre-lès-Nancy, France

* Corresponding author. E-mail address: Nicolas.Brosse@lermab.uhp-nancy.fr ; tel +333 83 68 48 62 ; fax + 333
83 68 44 98

Abstract

Condensed tannins were extracted from grape pomace using a water medium in presence of
three different bases as catalyst (NaOH, Na₂CO₃ or NaHCO₃) and were characterized by FT-
IR and MALDI-TOF spectrometry. It was demonstrated that the tannin extracts contained
oligomers up to 6 repeating flavonoid units, with dominant procyanidin with a minor amount
of prodelphinidin units. The structure of grape pomace tannin extracted did not present
noticeable discrepancy exception of the ratio of the opening pyran ring which was different as
a function of the catalyst used. Two different formulations (nonfortified tannin adhesive and

1 fortified with addition of 20% of polymeric 4,4'-diphenyl methane diisocyanate (*p*-MDI))
2 were used to press one layer particle board. It has been proved that the extraction processes
3 largely affect the adhesive properties of the extracts obtained from the same raw material.
4 Especially the particleboards prepared from tannins extracted using Na₂CO₃ as catalyst and
5 without *p*-MDI, give a high internal bonding value (IB = 0.45 MPa), which was good enough
6 to pass relevant international standard specifications for interior grade panels. Formaldehyde
7 emission of these panels is very low, well under the European Norm requirements (≤ 6.5 mg/
8 100g panel).

9
10 **Key words:** grape pomace; tannin-based adhesives; MALDI-TOF spectrometry;
11 formaldehyde emission; wood particleboard.

1. Introduction

Phenolic-type compounds obtained from natural resources have been used for the production of wood adhesives since 1970s (Tondi and Pizzi, 2009). Among the possible alternatives of the petroleum-derived phenolic compounds, condensed tannin is an excellent renewable resource (Kim et al., 2003, Sowunmi et al., 1996). It was demonstrated in previous works that condensed tannins can be not only successfully used as substitutes for phenol in the production of phenol-formaldehyde resins (PF), resorcinol-formaldehyde (RF), phenol-resorcinol-formaldehyde (PRF) but also for the preparation of condensed tannins-formaldehyde wood adhesives for interior and exterior wood bonding of products such as particleboard and plywood (Tondi and Pizzi, 2009, Lei et al., 2008, Pichelin et al., 2006, Pizzi, 2003 and 2006). Condensed tannins consist of chains of flavan-3-ol units as oligomeric constituents linked mainly through C4-C8 (or C6) bonds, widely distributed in the plant kingdom including tree bark and grape (Souquet et al., 1996, Kenndy et al., 2001). The industrial extraction of tannins from barks is generally a fairly simple procedure, using water as solvent, in the presence of a base (carbonate, soda) and of sodium sulfite or metabisulfite, at temperature around 80°C (Pizzi, 2003). At present, the commercial and industrial tannin extracts usable for wood adhesives are mainly obtained from mimosa, quebracho and pine barks (Fradinho et al., 2002, Panamgama, 2007, Vazquez et al., 2000).

Grape is one of the world's largest fruit crops and grape pomace is one of wastes generated by grape juice and wine-making processes. This pomace consists of skins, seeds, and in certain case of some stems, with the skins and seeds making up the major part (Zocca et al., 2007). Because of a low extraction during winemaking, the solid residues still retain high levels of condensed tannins. However, the majority of the grape pomace is currently not upgraded, but used for composting or discarded in open areas potentially causing environmental problem (Northup et al., 1998). Only small amounts of these by-products are up-graded by different

1 solvent extraction methods for recovery of the phenolics to use as natural health remedies,
2 food supplements, or as novel nutrifunctional food ingredients (Guerrero et al., 2008, Ruberto
3 et al., 2007, Spigno and De Faveri, 2007, Monrad et al., 2010, Pinelo et al., 2005 and 2007,
4 Vatai et al., 2009). Therefore, grape pomace potentially constitutes a very abundant and
5 relatively inexpensive source for tannin adhesive production.

6 In previous papers, extraction of condensed tannins from grape pomace was described in
7 water medium using NaOH, Na₂CO₃, NaHCO₃ in the presence of Na₂SO₃ (Ping et al 2011a
8 and 2011b). These extracts were characterized by ¹³C NMR and we selected the milder
9 conditions of extraction to prepare the very first grape pomace extract-based particleboards. In
10 the present paper, the grape pomace tannin extracts were characterized by FT-IR, MALDI-
11 TOF spectrometry and thermomechanical analysis (TMA). The effect of the tannins
12 extraction conditions on the chemical structure and the reactivity of the tannins was studied.
13 The addition of a synthetic cross linking agent (polymeric 4,4'-diphenyl methane
14 diisocyanate, pMDI) in the adhesive formulations and the formaldehyde emission of the
15 panels was also examined.

17 **2. Materials and Methods**

18 The samples correspond to mixtures of by-products of the winemaking process of red grape
19 variety (*Vitis vinifera*), growing in south-east of France and were provided by a French
20 distillery. The air-dried grape pomace was composed by grape skin, seeds and stalks manually
21 separated. It was stored at room temperature during the course of this study. Moisture content
22 was determined using KERN MRS 120-3 infrared moisture analyser.

24 **2.1. Tannins extraction**

Grape pomace was treated with an aqueous solution of base (NaOH, Na₂CO₃ or NaHCO₃) and Na₂SO₃ (2.5% or 5% w/w, see Table 4) with a solid-to-liquid ratio of 1:8. The tannins extraction was carried out by heating at 100°C during 120 min in a round bottle flask connected by water condenser. After heating, the pomace was cooled, washed and filtered through filter paper. The washed liquid was evaporated to a moderate concentration (rotary evaporator, temperature: 60°C), then lyophilised to yield tannins. A sample of tannins was stored in a freezer at -5 °C before analysis.

2.2. Characterization of tannin extracts

FT-IR was used to study the functional groups and molecular structure of the tannin extracts. The experiment was determined using Nexus 870 FT-IR instrument. Tannins (0.2 mg) were added into KBr powder (30 mg), mixed and grinded to powder which diameter reached 2 µm, then pressed to a small piece sample in a press machine. Elemental analyses were obtained on a Perkin Elmer 240C micoranalyser. The protein was calculated from the formula: protein (%) = Nitrogen (%) × 6.25. MALDI-TOF spectrometry is a suitable method for examining polyflavonoid tannin oligomers. The spectra were recorded on a KRATOS Kompact MALDI 4 instrument. The irradiation source was a pulsed nitrogen laser with a wavelength of 337 nm. The length of one laser pulse was 3 ns. The experimental conditions used were: mass- high (20 kV acceleration voltage), polarity-positive, flight path -linear 100-150 pulse per spectrum and 200-800 ns time of delayed extraction technique. The best results for tannin analysis were obtained by using the combination of matrix DHB/NaCl (Pash et al., 1996, Hoong et al., 2010). Grape pomace tannin powder (4 mg) was dissolved in 1ml H₂O. 2, 5-Dihydroxy benzoic acid (DHB) was used as the matrix and 10 mg NaCl were added to the matrix solution to enhance the ion formation. The solutions of the sample and the matrix were mixed

in equal amounts and 0.5-1 µl of the resulting solution were placed on the MALDI target. After evaporation of the solvent the MALDI target was introduced into the spectrometer.

2.3. Analysis of modulus of elasticity (MOE)

Modulus of elasticity (MOE) of the tannins formulations were studied using thermal mechanical analyzer with TA controller (Mettler TMA 40), STARE data processing software. TMA is to study the rigidity of the wood-adhesive joint as a function of temperature. The experiments were conducted under the conditions at a heat rate of 10°C/ min from 25 °C to 250 °C, 30 mg of resin, three points bending TMA mode. The maximum of MOE and its increase corresponding to temperature or time for wood-adhesive systems indicated the performance of the adhesive and the strength of the final application.

2.4. Preparation of resin formulation

Two different adhesive formulations were investigated in this paper, the first formulation is nonfortified tannin-formaldehyde adhesive, a certain concentration of tannin solution was prepared, 5 % of powdered *para*formaldehyde, by weight of dry tannin extract, was added. The second Formulation is fortified with a synthetic cross linker: 5 % of powdered *para*formaldehyde, 20% of polymeric 4,4'-diphenyl methane diisocyanate(p-MDI), by weight of dry tannin extract, were added to a certain concentration of tannin solution respectively.

2.5. Particleboard manufacture and testing

Single layer laboratory particleboards of 340 mm × 300 mm × 14 mm dimension were prepared using particles of beech (*Fagus sylvatica*) and Norway spruce (*Picea abies*) at 35.7 kg/cm² maximum pressure, 195 °C press temperature and 7.5 min press time. 10 % (w/w based on dry particles) of adhesive resin solid was loaded. The dry internal bond (IB) strength

of the particleboards was tested according to a relevant international standard European Norm EN 312, wood particleboard-specifications.

2.6. Measurement of formaldehyde emission

The formaldehyde emissions from the particleboards were determined according to the European Norm (EN-717-3) using a 500 ml glass jar. Three test pieces, with dimensions of 25 mm×25 mm×14 mm, which were cut from Single layer laboratory particleboards, are positioned in the jar. The formaldehyde released from the test pieces at 40±1°C, during 180 min is absorbed in 50 ml distilled water and determined from absorbance at 412 nm with spectrophotometer.

3. Results

The tannin extraction experiments from grape pomace were carried out considering previously described studies (Ping et al., 2011b) using 2.5% or 5% (w/w) of NaOH, Na₂CO₃ and NaHCO₃ in the presence of Na₂SO₃ at 100°C during 120 min in an aqueous medium.

3.1. FT-IR study of tannin extracts

The functional groups of the grape pomace extracts using three different basic reagents (NaOH, Na₂CO₃ and NaHCO₃, extraction conditions A, B and C respectively, see Fig. 1) were analysed by FT-IR. The spectra are presented in Fig.1 and the assignments are given in Table 1. The band at 3318 cm⁻¹ was assigned to hydroxyl both contribute to phenolic and sugar content. The bands at 2973 cm⁻¹ and 1743 cm⁻¹ were due to C-H stretching vibration assigned to methyl and methylene groups. A weak signal at 1750 cm⁻¹ is assigned to carbonyl groups. The presence of carbonyl groups could be rationalized by the well known catechinic acid rearrangement occurring during the extraction process. As previously described, the formation

of catechinic acid is to be minimized because it should decrease the reactivity of the extract toward cross linking agent. The bands at 1308 cm^{-1} , 1264 cm^{-1} and 1212 cm^{-1} were assigned to saturated C-C stretching attribute to $\text{CR}_2\text{-CHR-CR}(\text{SO}_3^{2-})$ structure caused by the opening of the pyran ring during sulfitation of flavonoid tannins (Hoong et al., 2009). This reaction has a positive effect because it increases the solubility of tannins and reduces the viscosity of the extracts allowing the use of adhesive solutions of higher resin content. The mechanism of the opening of pyran ring is given in previous papers (Ping et al., 2011b). A comparison of the IR signals for A, B and C and of their relative intensities indicates that the ratio of the heterocyclic C-ring opening of flavonoid unit is function of the nature of the base used for the tannins extraction. It appears from Fig. 1 that the opening of pyran ring during the tannins extraction seems to be more important by using Na_2CO_3 and NaHCO_3 (respectively conditions B and C) than when using NaOH (condition A). This observation is in accordance with the sulfite group contents of the three tannin fractions established based on elemental compositions given in Table 2 (A : 1 sulfitated moiety every 25 residues; B and C : ~ 1 sulfitated flavonoid moiety for approximately every 15 residues). From nitrogen compositions (Table 2), it can also be deduced that the extracts contained about 10 % w/w of proteins.

3.2. MALDI-TOF study of tannin extracts

Fig.2 shows a typical MALDI-TOF analysis of grape pomace tannins extract with the molecular weight ranging from 500 to 3000 Da. It could be concluded that grape pomace extracts contain flavonoid oligomers up to 6 repeating units, based on the largest tannin oligomer detected in the sample which showed a peak at 1924.2 Da. The MALDI-TOF mass spectra showed clear repetitive patterns of peaks that allow the identification of specific oligomer series present in the tannin sample. The major peak-to-peak mass increments observed were 288 Da, 304 Da, 450 Da and 440 Da. These masses corresponded to (I)

procyanidin, (II) prodelphinidin, (III) glucosylated procyanidin, (IV) gallated procyanidin repeating units, respectively (Fig.3). The number of repeating units in each oligomer was calculated using the expression $M + Na^+ = 23.0 (Na) + 2.0 (endgroups, 2 \times H) + 288.3 A + 304.3 B + 450.3 C + 440.4 D$ (table 3) with I, II, III and IV representing the four relevant monomers in the tannin oligomer according the method previously described (Hoong et al., 2010). Table 3 showed the possible combinations of different repeating units and the degree of polymerization corresponding to each of them. These values were obtained based on the m/z value of types I, II, III and IV of tannin structures. The dominant series of peaks at 604.1, 905.1, 1193.4, 1484.6, 1771.5 Da for tannin extracts were dimers, trimers, tetramer, pentamer, hexamer respectively. It could be seen that the main repeating units in each oligomer group were identified as those of procyanidin composing of catechol unit (I).

3.3. TMA study of tannins adhesive

The influence of 3 parameters (i.e., nature of the base for the extraction of tannins, concentration of the chemical reagents and effect of the addition of a cross linking agent (polymeric 4,4'-diphenyl methane diisocyanate, *p*-MDI)) on the properties of the adhesive formulations was examined. The formulations of tannins solution-paraformaldehyde 5% (w/w) (based on oven dry tannin weight) were scanned by thermo mechanical analysis in three points in bending according to a technique already reported (Laigle et al., 1998). The curves of the modulus of elasticity (MOE) as a function of increasing temperature are given in Fig. 4; MOE values at 195 °C are also given in Table 4.

F1, F7 and F11 correspond to the same formulations but using three different bases for the extraction of tannins (respectively NaOH, Na₂CO₃ and NaHCO₃, 2.5% w/w). It clearly appears that grape pomace tannins extracted using NaOH (F1) and NaHCO₃ (F11) gave lower performance (MOE < 2000 MPa) than those extracted with Na₂CO₃ (F7) with a MOE nearly

3500 MPa. The TMA results of the curing of F1 and F2, F11 and F12, F14 and F15 indicated that, in most of the essays, an increase in tannin concentrations used for the preparation of the formulation yielded noticeable improvements in the value of MOE. A comparison of the TMA profiles (given in the Fig.4) of F2 and F3, F4 and F5, F6 and F7, F9 and F10 shows that the addition of *p*MDI did not yield an important increase in the maximum MOE value. On the other hand, concerning F12, it appears that addition of *p*MDI has a positive effect: MOE values of F13 are still higher in the range of temperatures corresponding to industrial wood panel press conditions ($190^{\circ}\text{C} < T < 250^{\circ}\text{C}$).

3.4. Mechanical testing for particle boards

Grape pomace tannins based adhesive were used to press one layer particleboard. The internal bond (IB) strength of a panel is a direct measure of the performance of the adhesive. In this study, two different formulations (the nonfortified tannin adhesive and fortified with diisocyanate adhesive) were analysed. The results are shown in Table 4. The IB strengths demonstrate that the nature of the extraction reagent (NaOH, Na_2CO_3 or NaHCO_3) greatly impacts the value of panel IB strength. It can be seen that formulations F1 to F6 using NaOH for the tannins extraction yielded low panel performances and did not satisfy the IB strength results required (≥ 0.35 MPa) even with addition of *p*MDI in the formulation (F3 and F6). In the same way, the utilization of NaHCO_3 for the tannins extraction (F12) led to an adhesive bearing poor properties; however, with addition of 20% of *p*MDI in the formulation, the adhesive F13 yielded a good internal bond strength ($\text{IB} = 0.36$). These results are in accordance with the TMA experiments previously exposed. The best results were obtained from Na_2CO_3 extracts and it is noteworthy that F7 and F8 yielded very good internal bond strength results ($\text{IB} = 0.45$ and 0.68 respectively). Concerning F7, it is important to note that for the first time a resin formulation composed of 95% of pomace extracts solution, 5%

formaldehyde and without *p*MDI, yielded good internal bond strength which passed relevant international standard specifications for interior-grade panels (IB > 0.35 MPa).

3.5. Formaldehyde emission of particle boards

Formaldehyde emission has become one of the major concerns in wood-based panels industry, especially the interior wood bonding products, such as particle boards used as a major component in the production of decoration and furniture materials. In this study, the best IB value performance particleboards (F7 to F10) were chosen to determine the emission levels of formaldehyde. The results in Table 4 show that the formaldehyde emission of the particleboards was very low, largely below the European Norm requirements (≤ 6.5 mg/ 100g panel).

3.6 Discussion

In this study, it was shown by MADI TOF experiments that grape pomace extracts are mainly composed of flavonoid oligomers up to 6 repeating units, with dominant procyanidin units. This result is in accordance with ^{13}C -NMR and gel times analyses described in a previously study (Ping et al., 2011b). In fact, we described that the grape pomace extracts exhibited gel times below 100 sec at pH 7 and then can be classified under the same group as the faster reacting procyanidin-prodelphinidin tannins such as pine bark and pecan nut pith extracts (Pizzi, 1994). Thus, a ring of grape pomace tannins possess only the phloroglucinol moiety, much more reactive toward formaldehyde than a resorcinol-type structure (10 to 50 times higher than phenol (Kim et al., 2003), with important consequences in the use of these tannins for adhesives. Thus, this high nucleophilicity and reactivity of the tannins can explain the good to very good properties of the extracts isolated in the present study for adhesive applications and also the very low formaldehyde emission of particleboards observed, lower

1 than others wood adhesives, such as phenol-formaldehyde, urea formaldehyde, etc... Based
2 on previous papers (Pizzi, 1994), mechanisms are proposed for formation the grape pomace
3 tannins adhesives (Fig.5). The catechin-formaldehyde condensates are formed through
4 methylene bridges (path a). Concerning adhesives fortified with diisocyanate, the
5 methylolated catechins undergo two reactions of almost equal rate. The first is the standard
6 condensation reaction according the path a (Fig.5); the second is the attack of the *p*MDI on
7 the hydroxyl of the methylol group (-CH₂OH) formed onto the catechin moities (see Fig.5,
8 path b).

9 Sulfitation of tannins is one of the oldest reactions in flavonoid chemistry and can be useful in
10 the preparation of tannin-based adhesives (Pizzi, 1994). In this study, the sulphite group
11 contents were established by elemental analysis and FT-IR spectroscopy. It was observed that
12 using NaOH as extraction reagent, the resulting extracts had a lower sulphite group content
13 and in addition yielded low panel performance than when using carbonate salts as base. This
14 suggests that the introduction of a sulfonic group through sulfitation could increase not only
15 extraction yields and tannin solubility but also the reactivity of the extracts towards a cross
16 linking agent.

17 The grape pomace tannins used in this study are crude extracts, with a considerable proportion
18 of nonphenolic materials, mainly simple sugars and polymeric carbohydrates. Relatively high
19 carbohydrate contents were previously deduced by from ¹³C NMR spectrum and low Stiasny
20 numbers were obtained from the extracts (~0.5-0.6) (Ping et al., 2011b). The presence of non
21 phenolic compounds in the formulations can explained (1) the poor results obtained in terms
22 of mechanical properties of the panels for some of the extracts, (2) the improved performance
23 for some of the adhesive formulations prepared with *p*MDI. In fact, the reactive isocyanate
24 group of *p*MDI can rapidly react with the hydroxyl groups of the monomeric and polymeric

carbohydrates (see Fig.6). The formation of sugar- *p*MDI polyurethane could then enhance the joint performance of grape tannin fortified adhesive.

4. Conclusion

Tannins were extracted from grape pomace using water media in presence of NaOH, Na₂CO₃ or NaHCO₃. The MALDI TOF analysis showed that the crude extracts are composed of oligomers up to 6 repeating units, with dominant procyanidin units with a minor amount of prodelphinidin. The tannin fractions reactivity towards formaldehyde was studied by thermomechanical analysis in bending and through the production of particleboards. Two different formulations (nonfortified tannin adhesive and fortified with addition of 20% of polymeric 4,4'-diphenyl methane diisocyanate (*p*-MDI)) were used to press one layer particle board. It was shown that the nature of the extraction reagent (NaOH, Na₂CO₃ or NaHCO₃) greatly impacts the properties of the resins and the mechanical properties of the panel internal bonding strengths. The particleboards bonded by the tannins extracted using Na₂CO₃ as catalyst give the best performance and were good enough to pass relevant international standard specifications for interior grade panels. Formaldehyde emission of these panels was below the European Norm requirements (≤ 6.5 mg/ 100g panel). Thus, this work proposes an economically valuable utilization of grape pomace, a by-product currently largely underexploited, for the production of an environment friendly adhesive for particleboards production.

Acknowledgements

The authors gratefully acknowledge the financial support of the CPER 2007-2013 “Structuration du Pôle de Compétitivité Fibres Grand’Est” (French Competitiveness Fibre Cluster), through regional (Région Lorraine), national (DRRT and FNADT) and European

(FEDER) funds, the Doctorate Fellowship Foundation of Nanjing Forestry University and the Priority Academic Program Development of Jiangsu Higher Education Institutions. We thank Franck Jolibert (UNGDA) who provided the raw material.

References

- Fradinho, D.M., Neto, C.P., Evtuguin, D., Jorge, F.C., Irle, M.A., Gil, M.H., Pedrosa de Jesus, J., 2002. Chemical characterisation of bark and of alkaline bark extracts from maritime pine grown in Portugal. Ind. Crops Prod. 16, 23-32.
- Guerrero, M. S., Torres, J. S., Nunez, M. J., 2008. Extraction of polyphenols from white distilled grape pomace: Optimization and modelling. Bioresour. Technol. 99, 1311-1318.
- Hoong, Y.B., Paridaha, M.T., Luqman, C.A., Koh, M.P., Loh, Y.F., 2009. Fortification of sulfited tannin from the bark of *Acacia mangium* with phenol-formaldehyde for use as plywood adhesive. Industrial Crops and Products 30, 416-421.
- Hoong, Y.B., Pizzi, A., Tahir, P. Md., Pasch, H., 2010. Characterization of *Acacia Mangium* polyflavonoid tannins by MALDI-TOF mass spectrometry and CP-MAS ¹³ C NMR. European polymer journal 46, 1268-1277.
- Kennedy, J.A., Hayasaka, Y., Vidal, S., Waters, E. J., Jones, G.P., 2001. Composition of grape skin proanthocyanidins at different stages of berry development. J. Agric Food Chem. 49, 5348-5355.
- Kim, S., Lee, Y.K., Kim, H.J., 2003. Physico-mechanical properties of particleboards bonded with pine and wattle tannin-based adhesives. J. Adhesion Sci. Technol. 17 (14), 1863-1875.
- Laigle, Y., Kamoun, C., Pizzi, A., 1998. Particleboard internal bond forecast by TMA bending in UF adhesives curing. Holz Roh Werkstoff. 56 (3), 154.
- Lei, H., Pizzi, A., Du, G.B., 2008. Environmentally friendly mixed tannin /lignin wood resins. J. Appl. Polym. Sci. 107(1), 203-209.
- Monrad, J.K., Howard, L.R., King, J.W., Srinivas, K., 2010. Mauromoustakos, Andy. Subcritical solvent extraction of procyanidins from dried red grape pomace. J. Agric. Food Chem. 58 (7), 4014-4021.

1 Northup, R.R., Dahlgren, R.A., McColl, J.G., 1998. Polyphenols as regulators of plant-litter-soil
2 interactions in northern California's pygmy forest: A positive feedback? *Biogeochem* 42(1-2), 189-
3 220.

4 Panamgama, L.A., 2007. Polyphenolic Extracts of *Pinus radiata* Bark and Networking Mechanisms of
5 Additive-Accelerated Polycondensates. *J. Appl. Polym. Sci.* 103, 2487-2493.

6 Pasch, H., Rode, K., Ghahary, R., Braun, D., 1996. Matrix-assisted laser desorption/ionization mass
7 spectrometry of synthetic polymers. Part 3. Analysis of condensation polymers. *Angew Makromol*
8 *Chem.* 95, 241.

9 Pichelin, F., Nakatani, M., Pizzi, A., Wieland, S., Despres, A., Rigolet, S., 2006. Structural beams from
10 thick wood panels bonded industrially with formaldehyde-free tannin adhesives. *Forest Prod. J.* 56(5),
11 31-36.

12 Pinelo, M., Rubilar, Jerez, M., Sineiro, J., Nunez, M.J., 2005. Effect of solvent, temperature, and solvent-
13 to-solid ratio on the total phenolic content and antiradical activity of extracts from different
14 components of grape pomace. *J. Agric. Food Chem.* 53, 2111-2117.

15 Pinelo, M., Ruiz-Rodríguez, A., Sineiro, J., Senorans, F.J., Reglero, G., Nunez, M.J., 2007. Supercritical
16 fluid and solid-liquid extraction of phenolic antioxidants from grape pomace: a comparative study.
17 *Eur. Food Res. Technol.* 226, 199-205.

18 Ping, L., Brosse, N., Chrusciel, L., Navarrete, P., Pizzi, A., 2011a. Extraction of condensed tannins from
19 grape pomace for use as wood adhesives. *Industrial Crops and Products* 33, 253-257.

20 Ping, L., Pizzi, A., Zhou, D.G., Brosse, N., 2011b. Condensed tannins extraction from grape
21 pomace: characterization and utilization as wood adhesives for wood particleboard. *Industrial*
22 *Crops and Products* 34, 907-914.

23 Pizzi, A., 1994. *Advanced Wood Adhesive Technology*. Marcel Dekker, New York.

24 Pizzi, A., 2003. Natural phenolic adhesives I: Tannin. *Handbook of Adhesive Technology* (2nd Edition,
25 Revised and Expanded), 573-587.

26 Pizzi, A., 2006. Recent developments in eco-efficient bio-based adhesives for wood bonding:
27 opportunities and issues. *J. Adhesion Sci. Technol.* 20 (8), 829-846.

1 Ruberto, G., Renda, A., Daquino, C., Amico, V., Spatafora, C., Tringali, C., De Tommasi, N., 2007.
2 Polyphenol constituents and antioxidant activity of grape pomace extracts from five Sicilian red grape
3 cultivars. *Food Chem.* 100, 203-210.

4 Souquet, J.M., Cheynier, V., Brossaud, F., Moutounet, M., 1996. Polymeric proanthocyanidins from
5 grape skins. *Phytochemistry* 43(2), 509-512.

6 Sowunmi, S., Ebewele, R.O., Conner, A.H., River, B.H., 1996. Fortified mangrove tannin-based plywood
7 adhesive. *Journal of applied polymer science* 62, 577-584.

8 Spigno, G., De Faveri, D.M., 2007. Antioxidants from grape stalks and marc : Influence of extraction
9 procedure on yield, purity and antioxidant power of the extracts. *Journal of Food Engineering.* 78,
10 793-801.

11 Tondi, G., Pizzi, A., 2009. Tannin -based rigid foams: Characterization and modification. *Ind. Crops*
12 *Prod.* , 29(2-3), 356-363.

13 Vatai, T., Skerget, M., Knez, Z., 2009. Extraction of phenolic compounds from elder berry and different
14 grape marc varieties using organic solvents and/or supercritical carbon dioxide. *J. Food Eng.*, 90(2),
15 246-254.

16 Vazquez, G., Freire, S., Gonzalez, J., Antorrena, G., 2000. Characterization of *Pinus pinaster* bark and its
17 alkaline extracts by diffuse reflectance Fourier transform infrared (DRIFT) spectroscopy. *Holz als*
18 *Roh- und Werkstoff.* 58, 57-61

19 Zocca, F., Lomolino, G., Curioni, A., Spettoli, P., Lante, A., 2007. Detection of pectinmethylesterase
20 activity in presence of methanol during grape pomace storage. *Food Chemistry*, 102, 59-65.

21
22
23

Table 1. Assignment of FT-IR spectra of grape pomace tannin extracted by different extraction conditions

Peak cm^{-1}	assignment
3318	-OH stretching vibration
2973,2931	-CH ₃ , -CH ₂ - stretching vibration
1878	C=O stretching vibration
1619,1534,1501	Aromatic squel vibration
1439	CH deformation and aromatic ring vibration
1412	Aromatic vibration
1341	saturated CH in plane bending vibration
1308,1264 , 1212	C-C frame stretching(C-CHR-C)
1111	aromatic CH in plane bending vibration
1066	C-O stretching vibration
921	aromatic CH out of plane bending vibration

Table 2. Elemental analysis of grape pomace tannin extracted using different extraction conditions

extraction conditions	C%	H%	N%	S%
A (NaOH, 5%)	35.92	3.84	1.43	0.01
B (Na ₂ CO ₃ (2.5%)	36.64	3.81	1.48	0.03
C (NaHCO ₃ (2.5%)	36.43	3.80	1.27	0.04

Table 3. Distribution of polyflavonoid oligomer by MALDI-TOF for grape pomace tannin extracts.

	M+Na ⁺ experiment	M+Na ⁺ calculated	Unit type			
			I	II	III	IV
Dimer(2)	604.1	601.6	2	0	0	0
	767.6	763.6	1	0	1	0
Trimer(3)	905.1	905.9	2	1	0	0
	920.8	921.9	1	2	0	0
	1068.0	1067.9	1	1	1	0
Tetramer (4)	1193.4	1194.2	3	1	0	0
	1354.4	1356.2	2	1	1	0
Pentamer (5)	1484.6	1482.5	4	1	0	0
	1635.1	1634.5	3	1	0	1
Hexamer(6)	1771.5	1770.8	5	1	0	0
	1924.2	1922.8	4	1	0	1

Table 4. Adhesive formulation compositions, thermomechanical analysis and particle board testing.

Extraction reagents ^a	Formulation number	Composition Tannin / H ₂ CO/pMDI	Tannin concentration% ^b	TMA		
				MOE ^c at 195°C(MPa)	Density (kg/m ³)	IB ^d
NaOH(2.5%) Na ₂ SO ₃ (2.5%)	F1	20/1/0	30	1937.1	N/A	
	F2	20/1/0	40	2812.5	696.3	0.23
	F3	20/1/5	40	2662.5	693.7	0.28
NaOH(5%) Na ₂ SO ₃ (5%)	F4	20/1/0	30	2846.9	N/A	
	F5	20/1/0	40	2455.1	702	0.28
	F6	20/1/5	40	3062.8	698.4	0.32
Na ₂ CO ₃ (2.5%) Na ₂ SO ₃ (2.5%)	F7	20/1/0	30	3322.9	706.1	0.4
	F8	20/1/5	30	2833.5	710.4	0.6

Na ₂ CO ₃ (5%)	F9	20/1/0	30	2179.4	711.5	0.30
Na ₂ SO ₃ (5%)	F10	20/1/5	30	2605.9	706.9	0.60
NaHCO ₃ (2.5%)	F11	20/1/0	30	1369.7	N/A	
Na ₂ SO ₃ (2.5%)	F12	20/1/0	45	2776.8	692.6	0.20
	F13	20/1/5	45	3520.7	708.5	0.30
	F14	20/1/0	30	2932.9	N/A	
NaHCO ₃ (5%)	F15	20/1/0	45	3878.8	705	0.30
Na ₂ SO ₃ (5%)	F16	20/1/5	45	3589.0	703.4	0.30

- ^a % based on weight of dry pomace
^b in water, % based on weight of dry pomace
^c Modulus of elasticity
^d Internal bond strength

1
2
3
4
5
6
7

Fig.1. FT-IR spectra of grape pomace tannin extracted by different extraction conditions
A: NaOH(2.5%), B: Na₂CO₃(2.5%), C: NaHCO₃(2.5%)

Fig.2. MALDI mass spectrum of grape pomace tannin (conditions A)

Fig.3. Polymer structure of grape pomace tannin repeating unit: (I) procyanidin, (II) prodelphinidin, (III) glucosylated procyanidin, (IV) gallated procyanidin.

I

II

III

IV

Fig.4. TMA measuring MOE as a function of temperature to describe the curing of resins of grape pomace tannins.

Fig.5. Underlying mechanisms proposed for the grape pomace tannins adhesive system.

1

2
3
4
5

Fig.6. The mechanism proposed for *p*MDI reacted with hydroxyl groups of the carbohydrates.