

# Condensed tannins from grape pomace: Characterization by FTIR and MALDI TOF and production of environment friendly wood adhesive

Lan Ping, Antonio Pizzi, Zhou Ding Guo, Nicolas Brosse

## ► To cite this version:

Lan Ping, Antonio Pizzi, Zhou Ding Guo, Nicolas Brosse. Condensed tannins from grape pomace: Characterization by FTIR and MALDI TOF and production of environment friendly wood adhesive. Industrial Crops and Products, 2012, 40, pp.13-20. 10.1016/j.indcrop.2012.02.039. hal-03140957

## HAL Id: hal-03140957 https://hal.univ-lorraine.fr/hal-03140957

Submitted on 14 Feb 2021

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial - NoDerivatives 4.0 International License

1	Condensed tannins from grape pomace : characterization by FTIR and MALDI
2	TOF and production of environment friendly wood adhesive
3	<u>Authors</u> :
4	Lan Ping <sup>a,b</sup> Antonio Pizzi <sup>b</sup> , Zhou Ding Guo <sup>a</sup> , Nicolas Brosse <sup>b</sup> *
5	
6	<u>Affiliations :</u>
7	<sup>a</sup> College of Wood Science and Technology, Nanjing Forestry University, Nanjing 210037,
8	China
9	
10	<sup>b</sup> Laboratoire d'Etude et de Recherche sur le MAteriau Bois, Faculté des Sciences et
11	Techniques, Nancy-Université, Bld des Aiguillettes, F-54500 Vandoeuvre-lès-Nancy, France
12	
13	* Corresponding author. E-mail address: <u>Nicolas.Brosse@lermab.uhp-nancy.fr</u> ; tel +333 83 68 48 62 ; fax + 333
14	83 68 44 98
15	
16	Abstract
17	Condensed tannins were extracted from grape pomace using a water medium in presence of
18	three different bases as catalyst (NaOH, Na <sub>2</sub> CO <sub>3</sub> or NaHCO <sub>3</sub> ) and were characterized by FT-
19	IR and MALDI-TOF spectrometry. It was demonstrated that the tannin extracts contained
20	oligomers up to 6 repeating flavonoid units, with dominant procyanidin with a minor amount
21	of prodelphinidin units. The structure of grape pomace tannin extracted did not present
22	noticeable discrepancy exception of the ratio of the opening pyran ring which was different as
23	a function of the catalyst used. Two different formulations (nonfortified tannin adhesive and

1 fortified with addition of 20% of polymeric 4,4'-diphenyl methane diisocyanate (p-MDI)) 2 were used to press one layer particle board. It has been proved that the extraction processes largely affect the adhesive properties of the extracts obtained from the same raw material. 3 4 Especially the particleboards prepared from tannins extracted using Na<sub>2</sub>CO<sub>3</sub> as catalyst and 5 without *p*-MDI, give a high internal bonding value (IB = 0.45 MPa), which was good enough 6 to pass relevant international standard specifications for interior grade panels. Formaldehyde 7 emission of these panels is very low, well under the European Norm requirements ( $\leq 6.5 \text{ mg}$ / 8 100g panel).

- 9
- 10 **Key words**: grape pomace; tannin-based adhesives; MALDI-TOF spectrometry;
- 11 formaldehyde emission; wood particleboard.

## 1 **1. Introduction**

2 Phenolic-type compounds obtained from natural resources have been used for the 3 production of wood adhesives since 1970s (Tondi and Pizzi, 2009). Among the possible 4 alternatives of the petroleum-derived phenolic compounds, condensed tannin is an excellent 5 renewable resource (Kim et al., 2003, Sowunmi et al., 1996). It was demonstrated in previous 6 works that condensed tannins can be not only successfully used as substitutes for phenol in 7 the production of phenol-formaldehyde resins (PF), resorcinol-formaldehyde (RF), phenol-8 resorcinol-formaldehyde (PRF) but also for the preparation of condensed tannins-9 formaldehyde wood adhesives for interior and exterior wood bonding of products such as 10 particleboard and plywood (Tondi and Pizzi, 2009, Lei et al., 2008, Pichelin et al., 2006, 11 Pizzi, 2003 and 2006). Condensed tannins consist of chains of flavan-3-ol units as oligometric 12 constituents linked mainly through C4-C8 (or C6) bonds, widely distributed in the plant 13 kingdom including tree bark and grape (Souquet et al., 1996, Kenndy et al., 2001). The 14 industrial extraction of tanning from barks is generally a fairly simple procedure, using water 15 as solvent, in the presence of a base (carbonate, soda) and of sodium sulfite or metabisulfite, 16 at temperature around 80°C (Pizzi, 2003). At present, the commercial and industrial tannin 17 extracts usable for wood adhesives are mainly obtained from mimosa, quebracho and pine 18 barks (Fradinho et al., 2002, Panamgama, 2007, Vazquez et al., 2000).

Grape is one of the world's largest fruit crops and grape pomace is one of wastes generated by grape juice and wine-making processes. This pomace consits of skins, seeds, and in certain case of some stems, with the skins and seeds making up the major part (Zocca et al., 2007). Because of a low extraction during winemaking, the solid residues still retain high levels of condensed tannins. However, the majority of the grape pomace is currently not upgraded, but used for composting or discarded in open areas potentially causing environmental problem (Northup et al., 1998). Only small amounts of these by-products are up-graded by different solvent extraction methods for recovery of the phenolics to use as natural health remedies,
food supplements, or as novel nutrifunctional food ingredients (Guerrero et al., 2008, Ruberto
et al., 2007, Spigno and De Faveri, 2007, Monrad et al., 2010, Pinelo et al., 2005 and 2007,
Vatai et al., 2009).Therefore, grape pomace potentially constitutes a very abundant and
relatively inexpensive source for tannin adhesive production.

6 In previous papers, extraction of condensed tannins from grape pomace was described in 7 water medium using NaOH, Na<sub>2</sub>CO<sub>3</sub>, NaHCO<sub>3</sub> in the presence of Na<sub>2</sub>SO<sub>3</sub> (Ping et al 2011a and 2011b). These extracts were characterized by <sup>13</sup>C NMR and we selected the milder 8 9 conditions of extraction to prepare the very first grape pomace extract-based particleboards. In 10 the present paper, the grape pomace tannin extracts were characterized by FT-IR, MALDI-11 TOF spectrometry and thermomechanical analysis (TMA). The effect of the tannins 12 extraction conditions on the chemical structure and the reactivity of the tannins was studied. 13 The addition of a synthetic cross linking agent (polymeric 4,4'-diphenyl methane 14 diisocyanate, pMDI) in the adhesive formulations and the formaldehyde emission of the 15 panels was also examined.

16

## 17 2. Materials and Methods

The samples correspond to mixtures of by-products of the winemaking process of red grape variety (Vitis vinifera), growing in south-east of France and were provided by a French distillery. The air-dried grape pomace was composed by grape skin, seeds and stalks manually separated. It was stored at room temperature during the course of this study. Moisture content was determined using KERN MRS 120-3 infrared moisture analyser.

23

## 24 **2.1. Tannins extraction**

Grape pomace was treated with an aqueous solution of base (NaOH, Na<sub>2</sub>CO<sub>3</sub> or NaHCO<sub>3</sub>) and Na<sub>2</sub>SO<sub>3</sub> (2.5% or 5% w/w, see Table 4) with a solid-to-liquid ratio of 1:8. The tannins extraction was carried out by heating at 100°C during 120 min in a round bottle flask connected by water condenser. After heating, the pomace was cooled, washed and filtered through filter paper. The washed liquid was evaporated to a moderate concentration (rotary evaporator, temperature: 60°C), then lyophilised to yield tannins. A sample of tannins was stored in a freezer at -5 °C before analysis.

8

#### 9 **2.2.** Characterization of tannin extracts

10 FT-IR was used to study the functional groups and molecular structure of the tannin extracts. 11 The experiment was determined using Nexus 870 FT-IR instrument. Tannins (0.2 mg) were 12 added into KBr powder (30 mg), mixed and grinded to powder which diameter reached 2 µm, 13 then pressed to a small piece sample in a press machine. Elemental analyses were obtained on 14 a Perkin Elmer 240C micoranalyser. The protein was calculated from the formula: protein (%) 15 = Nitrogen (%)  $\times$  6.25. MALDI-TOF spectrometry is a suitable method for examining 16 polyflavonoid tannin oligomers. The spectra were recorded on a KRATOS Kompact MALDI 17 4 instrument. The irradiation source was a pulsed nitrogen laser with a wavelength of 337 nm. 18 The length of one laser pulse was 3 ns. The experimental conditions used were: mass- high 19 (20 kV acceleration voltage), polarity-positive, flight path -linear 100-150 pulse per spectrum 20 and 200-800 ns time of delayed extraction technique. The best results for tannin analysis were 21 obtained by using the combination of matrix DHB/NaCl (Pash et al., 1996, Hoong et al., 22 2010). Grape pomace tannin powder (4 mg) was dissolved in 1ml H<sub>2</sub>O. 2, 5-Dihydroxy benzoic acid (DHB) was used as the matrix and 10 mg NaCl were added to the matrix 23 24 solution to enhance the ion formation. The solutions of the sample and the matrix were mixed

1 in equal amounts and 0.5-1 µl of the resulting solution were placed on the MALDI target.

2 After evaporation of the solvent the MALDI target was introduced into the spectrometer.

3

#### 4 **2.3.** Analysis of modulus of elasticity (MOE)

5 Modulus of elasticity (MOE) of the tannins formulations were studied using thermal 6 mechanical analyzer with TA controller (Mettler TMA 40), STARe date processing software. 7 TMA is to study the rigidity of the wood-adhesive joint as a function of temperature. The 8 experiments were conducted under the conditions at a heat rate of 10°C/ min from 25 °C to 9 250 °C, 30 mg of resin, three points bending TMA mode. The maximum of MOE and its 10 increase corresponding to temperature or time for wood-adhesive systems indicated the 11 performance of the adhesive and the strength of the final application.

12

#### 13 **2.4. Preparation of resin formulation**

14 Two different adhesive formulations were investigated in this paper, the first formulation is 15 nonfortified tannin-formaldehyde adhesive, a certain concentration of tannin solution was 16 prepared, 5 % of powdered *para*formaldehyde, by weight of dry tannin extract, was added.

17 The second Formulation is fortified with a synthetic cross linker: 5 % of powdered 18 *para*formaldehyde, 20% of polymeric 4,4'-diphenyl methane diisocyanate(p-MDI), by weight 19 of dry tannin extract, were added to a certain concentration of tannin solution respectively.

20

## 21 **2.5. Particleboard manufacture and testing**

Single layer laboratory particleboards of 340 mm  $\times$  300 mm  $\times$  14 mm dimension were prepared using particles of beech (*Fagus sylvatica*) and Norway spruce (*Picea abies*) at 35.7 kg/cm<sup>2</sup> maximun pressure, 195 °C press temperature and 7.5 min press time. 10 % (w/w based on dry particles) of adhesive resin solid was loaded. The dry internal bond (IB) strength of the particleboards was tested according to a relevant international standard European Norm
 EN 312, wood particleboard-specifications.

3

## 4 **2.6. Measurement of formaldehyde emission**

The formaldehyde emissions from the particleboards were determined according to the European Norm (EN-717-3) using a 500 ml glass jar. Three test pieces, with dimensions of 25 mm×25 mm×14 mm, which were cut from Single layer laboratory particleboards, are positioned in the jar. The formaldehyde released from the test pieces at 40±1°C, during 180 min is absorbed in 50 ml distilled water and determined from absorbance at 412 nm with spectrophotometer.

11

### 12 **3. Results**

13 The tannin extraction experiments from grape pomace were carried out considering 14 previously described studies (Ping et al., 2011b) using 2.5% or 5% (w/w) of NaOH, Na<sub>2</sub>CO<sub>3</sub> 15 and NaHCO<sub>3</sub> in the presence of Na<sub>2</sub>SO<sub>3</sub> at 100°C during 120 min in an aqueous medium.

16

#### 17 **3.1. FT-IR study of tannin extracts**

The functional groups of the grape pomace extracts using three different basic reagents 18 19 (NaOH, Na<sub>2</sub>CO<sub>3</sub> and NaHCO<sub>3</sub>, extraction conditions A, B and C respectively, see Fig. 1) were 20 analysed by FT-IR. The spectra are presented in Fig.1 and the assignments are given in Table 1. The band at 3318 cm<sup>-1</sup> was assigned to hydroxyl both contribute to phenolic and sugar 21 content. The bands at 2973 cm<sup>-1</sup> and 1743 cm<sup>-1</sup> were due to C-H stretching vibration assigned 22 23 to methyl and methylene groups. A weak signal at 1750 cm<sup>-1</sup> is assigned to carbonyl groups. The presence of carbonyl groups could be rationalized by the well known catechinic acid 24 25 rearrangement occuring during the extraction process. As previously described, the formation

1 of catechinic acid is to be minimized because it should decrease the reactivity of the extract toward cross linking agent. The bands at 1308 cm<sup>-1</sup>, 1264cm<sup>-1</sup> and 1212 cm<sup>-1</sup> were assigned to 2 saturated C-C stretching attribute to  $CR_2$ -CHR-CR( $SO_3^{2-}$ ) structure caused by the opening of 3 the pyran ring during sulfitation of flavonoid tannins (Hoong et al., 2009). This reaction has a 4 5 positive effect because it increases the solubility of tannins and reduces the viscosity of the 6 extracts allowing the use of adhesive solutions of higher resin content. The mechanism of the 7 opening of pyran ring is given in previous papers (Ping et al., 2011b). A comparison of the IR 8 signals for A, B and C and of their relative intensities indicates that the ratio of the 9 heterocyclic C-ring opening of flavonoid unit is function of the nature of the base used for the 10 tannins extraction. It appears from Fig. 1 that the opening of pyran ring during the tannins 11 extraction seems to be more important by using Na<sub>2</sub>CO<sub>3</sub> and NaHCO<sub>3</sub> (respectively conditions 12 B and C) than when using NaOH (condition A). This observation is in accordance with the 13 sulfite group contents of the three tannin fractions established based on elemental compositions given in Table 2 (A : 1 sulfitated moiety every 25 residues; B and C : ~1 14 15 sulfitated flavonoid moiety for approximately every 15 residues). From nitrogen compositions (Table 2), it can also be deduced that the extracts contained about 10 % w/w of proteins. 16

17

18

#### **3.2. MALDI-TOF study of tannin extracts**

19 Fig.2 shows a typical MALDI-TOF analysis of grape pomace tannins extract with the 20 molecular weight ranging from 500 to 3000 Da. It could be concluded that grape pomace 21 extracts contain flavonoid oligomers up to 6 repeating units, based on the largest tannin 22 oligomer detected in the sample which showed a peak at 1924.2 Da. The MALDI-TOF mass 23 spectra showed clear repetitive patterns of peaks that allow the identification of specific 24 oligomer series present in the tannin sample. The major peak-to-peak mass increments 25 observed were 288 Da, 304 Da, 450 Da and 440 Da. These masses corresponded to (I)

1 procyanidin, (II) prodelphinidin, (III) glucosylated procyanidin, (IV) gallated procyanidin repeating units, repectively (Fig.3). The number of repeating units in each oligomer was 2 calculated using the expression M + Na<sup>+</sup> = 23.0 (Na) + 2.0 (endgroups,  $2 \times H$ ) + 288.3 A + 3 4 304.3 B + 450.3 C + 440.4 D (table 3) with I, II, III and IV representing the four relevant 5 monomers in the tannin oligomer according the method previously described (Hoong et al., 6 2010). Table 3 showed the possible combinations of different repeating units and the degree 7 of polymerization corresponding to each of them. These values were obtained based on the 8 m/z value of types I, II, III and IV of tannin structures. The dominant series of peaks at 604.1, 9 905.1, 1193.4, 1484.6, 1771.5 Da for tannin extracts were dimers, trimers, tetramer, pentamer, 10 hexamer respectively. It could be seem that the main repeating units in each oligomer group 11 were identified as those of procyanidin composing of catechol unit (I).

12

#### 13 **3.3. TMA study of tannins adhesive**

14 The influence of 3 parameters (i.e., nature of the base for the extraction of tannins, 15 concentration of the chemical reagents and effect of the addition of a cross linking agent (polymeric 4,4'-diphenyl methane diisocyanate, p-MDI)) on the properties of the adhesive 16 17 formulations was examined. The formulations of tannins solution-paraformaldehyde 5% (w/w) 18 (based on oven dry tannin weight) were scanned by thermo mechanical analysis in three 19 points in bending according to a technique already reported (Laigle et al., 1998). The curves 20 of the modulus of elasticity (MOE) as a function of increasing temperature are given in Fig. 4; 21 MOE values at 195 °C are also given in Table 4.

F1, F7 and F11 correspond to the same formulations but using three different bases for the extraction of tannins (respectively NaOH, Na<sub>2</sub>CO<sub>3</sub> and NaHCO<sub>3</sub>, 2.5% w/w). It clearly appears that grape pomace tannins extracted using NaOH (F1) and NaHCO<sub>3</sub> (F11) gave lower performance (MOE < 2000 MPa) than those extracted with Na<sub>2</sub>CO<sub>3</sub> (F7) with a MOE nearly

1 3500 MPa. The TMA results of the curing of F1 and F2, F11 and F12, F14 and F15 indicated 2 that, in most of the essays, an increase in tannin concentrations used for the preparation of the 3 formulation yielded noticeable improvements in the value of MOE. A comparison of the 4 TMA profiles (given in the Fig.4) of F2 and F3, F4 and F5, F6 and F7, F9 and F10 shows that 5 the addition of *p*MDI did not yield an important increase in the maximum MOE value. On the 6 other hand, concerning F12, it appears that addition of pMDI has a positive effect: MOE 7 values of F13 are still higher in the range of temperatures corresponding to industrial wood 8 panel press conditions (190°C < T < 250°C).

9

## 10 **3.4. Mechanical testing for particle boards**

11 Grape pomace tannins based adhesive were used to press one layer particleboard. The 12 internal bond (IB) strength of a panel is a direct measure of the performance of the adhesive. 13 In this study, two different formulations (the nonfortified tannin adhesive and fortified with 14 diisocyanate adhesive) were analysed. The results are shown in Table 4. The IB strengths demonstrate that the nature of the extraction reagent (NaOH, Na<sub>2</sub>CO<sub>3</sub> or NaHCO<sub>3</sub>) greatly 15 16 impacts the value of panel IB strength. It can be seen that formulations F1 to F6 using NaOH 17 for the tannins extraction yielded low panel performances and did not satisfy the IB strength 18 results required (±0.35 MPa) even with addition of pMDI in the formulation (F3 and F6). In 19 the same way, the utilization of NaHCO<sub>3</sub> for the tannins extraction (F12) led to an adhesive 20 bearing poor properties; however, with addition of 20% of pMDI in the formulation, the 21 adhesive F13 yielded a good internal bond strength t (IB = 0.36). These results are in 22 accordance with the TMA experiments previously exposed. The best results were obtained 23 from Na<sub>2</sub>CO<sub>3</sub> extracts and it is noteworthy that F7 and F8 yielded very good internal bond 24 strength results (IB = 0.45 and 0.68 respectively). Concerning F7, it is important to note that 25 for the first time a resin formulation composed of 95% of pomace extracts solution, 5%

1 formaldehyde and without pMDI, yielded good internal bond strength which passed relevant 2 international standard specifications for interior-grade panels (IB > 0.35 MPa).

3

#### 4 **3.5.** Formaldehyde emission of particle boards

Formaldehyde emission has become one of the major concerns in wood-based panels industry, especially the interior wood bonding products, such as particle boards used as a major component in the production of decoration and furniture materials. In this study, the best IB value performance particleboards (F7 to F10) were chosen to determine the emission levels of formaldehyde. The results in Table 4 show that the formaldehyde emission of the particleboards was very low, largely below the European Norm requirements ( $\leq 6.5$  mg/ 100g panel).

12

#### 13 **3.6 Discussion**

14 In this study, it was shown by MADI TOF experiments that grape pomace extracts are mainly 15 composed of flavoinoid oligomers up to 6 repeating units, with dominant procyanidin units. This result is in accordance with <sup>13</sup>C-NMR and gel times analyses described in a previously 16 17 study (Ping et al., 2011b). In fact, we described that the grape pomace extracts exhibited gel 18 times below 100 sec at pH 7 and then can be classified under the same group as the faster 19 reacting procyanidin-prodelphinidin tannins such as pine bark and pecan nut pith extracts 20 (Pizzi, 1994). Thus, a ring of grape pomace tannins possess only the phloroglucinol moity, 21 much more reactive toward formaldehyde than a resorcinol-type structure (10 to 50 times 22 higher than phenol (Kim et al., 2003), with important consequences in the use of these tannins 23 for adhesives. Thus, this high nucleophilicity and reactivity of the tannins can explain the 24 good to very good properties of the extracts isolated in the present study for adhesive 25 applications and also the very low formaldehyde emission of particleboards observed, lower

1 than others wood adhesives, such as phenol-formaldehyde, urea formaldehyde, etc... Based 2 on previous papers (Pizzi, 1994), mechanisms are proposed for formation the grape pomace 3 tannins adhesives (Fig.5). The catechin-formaldehyde condensates are formed through 4 methylene bridges (path a). Concerning adhesives fortified with diisocyanate, the 5 methylolated catechins undergo two reactions of almost equal rate. The first is the standard 6 condensation reaction according the path a (Fig.5); the second is the attack of the *p*MDI on 7 the hydroxyl of the methylol group (-CH<sub>2</sub>OH) formed onto the catechin moities (see Fig.5, 8 path b).

9 Sulfitation of tannins is one of the oldest reactions in flavonoid chemistry and can be useful in 10 the preparation of tannin-based adhesives (Pizzi, 1994). In this study, the sulphite group 11 contents were established by elemental analysis and FT-IR spectroscopy. It was observed that 12 using NaOH as extraction reagent, the resulting extracts had a lower sulphite group content 13 and in addition yielded low panel performance than when using carbonate salts as base. This 14 suggests that the introduction of a sulfonic group through sulfitation could increase not only 15 extraction yields and tannin solubility but also the reactivity of the extracts towards a cross 16 linking agent.

17 The grape pomace tannins used in this study are crude extracts, with a considerable proportion 18 of nonphenolic materials, mainly simple sugars and polymeric carbohydrates. Relatively high carbohydrate contents were previously deduced by from <sup>13</sup>C NMR spectrum and low Stiasny 19 20 numbers were obtained from the extracts (~0.5-0.6) (Ping et al., 2011b). The presence of non 21 phenolic compounds in the formulations can explained (1) the poor results obtained in terms 22 of mechanical properties of the panels for some of the extracts, (2) the improved performance 23 for some of the adhesive formulations prepared with pMDI. In fact, the reactive isocyanate 24 group of *p*MDI can rapidly react with the hydroxyl groups of the monomeric and polymeric

carbohydrates (see Fig.6). The formation of sugar- *p*MDI polyurethane could then enhance
 the joint performance of grape tannin fortified adhesive.

3

## 4 **4. Conclusion**

5 Tannins were extracted from grape pomace using water media in presence of NaOH, 6 Na<sub>2</sub>CO<sub>3</sub> or NaHCO<sub>3</sub>. The MALDI TOF analysis showed that the crude extracts are composed 7 of oligomers up to 6 repeating units, with dominant procyanidin units with a minor amount of 8 prodelphinidin. The tannin fractions reactivity towards formaldehyde was studied by 9 thermomechanical analysis in bending and through the production of particleboards. Two 10 different formulations (nonfortified tannin adhesive and fortified with addition of 20% of 11 polymeric 4.4'-diphenyl methane diisocyanate (p-MDI)) were used to press one layer particle 12 board. It was shown that the nature of the extraction reagent (NaOH, Na<sub>2</sub>CO<sub>3</sub> or NaHCO<sub>3</sub>) 13 greatly impacts the properties of the resins and the mechanical properties of the panel internal 14 bonding strengths. The particleboards bonded by the tannins extracted using  $Na_2CO_3$  as 15 catalyst give the best performance and were good enough to pass relevant international 16 standard specifications for interior grade panels. Formaldehyde emission of these panels was 17 below the European Norm requirements ( $\leq 6.5 \text{ mg}/100 \text{ g panel}$ ). Thus, this work proposes an 18 economically valuable utilization of grape pomace, a by-product currently largely 19 underexploited, for the production of an environment friendly adhesive for particleboards 20 production.

21

## 22 Acknowledgements

The authors gratefully acknowledge the financial support of the CPER 2007-2013
"Structuration du Pôle de Compétitivité Fibres Grand'Est" (French Competitiveness Fibre
Cluster), through regional (Région Lorraine), national (DRRT and FNADT) and European

- 1 (FEDER) funds, the Doctorate Fellowship Foundation of Nanjing Forestry University and the
- 2 Priority Academic Program Development of Jiangsu Higher Education Institutions. We thank
- 3 Franck Jolibert (UNGDA) who provided the raw material.
- 4

## 5 **References**

- 6 Fradinho, D.M., Neto, C.P., Evtuguin, D., Jorge, F.C., Irle, M.A., Gil, M.H., Pedrosa de Jesus, J., 2002.
- 7 Chemical characterisation of bark and of alkaline bark extracts from maritime pine grown in Portugal.8 Ind. Crops Prod. 16, 23-32.
- 9 Guerrero, M. S., Torres, J. S., Nunez, M. J., 2008. Extraction of polyphenols from white distilled grape
  pomace: Optimization and modelling. Bioresour. Technol. 99, 1311-1318.
- 11 Hoong, Y.B., Paridaha, M.T., Luqman, C.A., Koh, M.P., Loh, Y.F., 2009. Fortification of sulfited tannin
- from the bark of Acacia mangium withphenol-formaldehyde for use as plywood adhesive. IndustrialCrops and Products 30, 416-421.
- 14 Hoong, Y.B., Pizzi, A., Tahir, P. Md., Pasch, H., 2010. Characterization of *Acacia Mangium*polyflavonoid tannins by MALDI-TOF mass spectrometry and CP-MAS <sup>13</sup> C NMR. European
  polymer journal 46, 1268-1277.
- 17 Kennedy, J.A., Hayasaka, Y., Vidal, S., Waters, E. J., Jones, G.P., 2001.Composition of grape skin
  proanthocyanidins at different stages of berry development. J.Agric Food Chem. 49, 5348-5355.
- 19 Kim, S., Lee, Y.K., Kim,H.J.,2003. Physico-mechanical properties of particleboards bonded with pine
- 20 and wattle tannin-based adhesives. J.Adhesion Sci. Technol. 17 (14), 1863-1875.
- 21 Laigle, Y., Kamoun, C., Pizzi, A., 1998. Particleboard internal bond forecast by TMA bending in UF
  adhesives curing. Holz Roh Werkstoff. 56 (3), 154.
- 23 Lei, H., Pizzi, A., Du, G.B., 2008. Environmentally friendly mixed tannin /lignin wood resins. J. Appl.
  24 Polym. Sci. 107(1), 203-209.
- 25 Monrad, J.K., Howard, L.R., King, J.W., Srinivas, K., 2010. Mauromoustakos, Andy. Subcritical solvent
- extraction of procyanidins from dried red grape pomace. J. Agric. Food Chem. 58 (7), 4014-4021.

Northup, R.R., Dahlgren, R.A., McColl, J.G., 1998. Polyphenols as regulators of plant-litter-soil
 interactions in northern California's pygmy forest: A positive feedback? Biogeochem 42(1-2), 189 220.

4 Panamgama, L.A., 2007. Polyphenolic Extracts of Pinus radiata Bark and Networking Mechanisms of
5 Additive-Accelerated Polycondensates. J. Appl. Polym. Sci. 103, 2487-2493.

6 Pasch, H., Rode, K., Ghahary, R., Braun, D., 1996. Matrix-assisted laser desorption/ionization mass
7 spectrometry of synthetic polymers. Part 3. Analysis of condensation polymers. Angew Makromol
8 Chem. 95, 241.

9 Pichelin, F., Nakatani, M., Pizzi, A., Wieland, S., Despres, A., Rigolet, S., 2006. Structural beams from
10 thick wood panels bonded industrially with formaldehyde-free tannin adhesives. Forest Prod. J. 56(5),

11 31-36.

12 Pinelo, M., Rubilar, Jerez, M., Sineiro, J., Nunez, M.J., 2005. Effect of solvent, temperature, and solvent13 to-solid ratio on the total phenolic content and antiradical activity of extracts from different
14 components of grape pomace. J. Agric. Food Chem. 53, 2111-2117.

15 Pinelo, M., Ruiz-Rodriguez, A., Sineiro, J., Senorans, F.J., Reglero, G., Nunez, M.J., 2007. Supercritical

16 fluid and solid-liquid extraction of phenolic antioxidants from grape pomace: a comparative study.

17 Eur. Food Res. Technol. 226, 199-205.

18 Ping, L., Brosse, N., Chrusciel, L., Navarrete, P., Pizzi, A., 2011a. Extraction of condensed tannins from
grape pomace for use as wood adhesives. Industrial Crops and Products 33, 253-257.

20 Ping, L., Pizzi, A., Zhou, D.G., Brosse, N., 2011b.Condensed tannins extraction from grape

pomace: characterization and utilization as wood adhesives for wood particleboard. Industrial
Crops and Products 34, 907-914.

23 Pizzi, A., 1994. Advanced Wood Adhesive Technology. Marcel Dekker, New York.

24 Pizzi, A., 2003. Natural phenolic adhesives I: Tannin. Handbook of Adhesive Technology (2nd Edition,
Revised and Expanded), 573-587.

26 Pizzi, A., 2006. Recent developments in eco-efficient bio-based adhesives for wood bonding:
27 opportunities and issues. J. Adhesion Sci. Technol. 20 (8), 829-846.

- Ruberto, G., Renda, A., Daquino, C., Amico, V., Spatafora, C., Tringali, C., De Tommasi, N., 2007.
   Polyphenol constituents and antioxidant activity of grape pomace extracts from five Sicilian red grape
   cultivars. Food Chem. 100, 203-210.
- 4 Souquet, J.M., Cheynier, V., Brossaud, F., Moutounet, M., 1996. Polymeric proanthocyanidins from
  grape skins. Phytochemistry 43(2), 509-512.
- 6 Sowunmi,S., Ebewele, R.O., Conner, A.H., River, B.H., 1996. Fortified mangrove tannin-based plywood
  7 adhesive. Journal of applied polymer science 62, 577-584.
- 8 Spigno, G., De Faveri, D.M., 2007. Antioxidants from grape stalks and marc : Influence of extraction
  9 procedure on yield, purity and antioxidant power of the extracts. Journal of Food Engineering. 78,
  10 793-801.
- 11 Tondi, G., Pizzi, A., 2009. Tannin -based rigid foams: Characterization and modification. Ind. Crops
  Prod., 29(2-3), 356-363.
- 13 Vatai, T., Skerget, M., Knez, Z., 2009. Extraction of phenolic compounds from elder berry and different
  grape marc varieties using organic solvents and/or supercritical carbon dioxide. J. Food Eng., 90(2),
  246-254.
- 16 Vazquez, G., Freire, S., Gonzalez, J., Antorrena, G., 2000. Characterization of Pinus pinaster bark and its
  alkaline extracts by diffuse reflectance Fourier transform infrared (DRIFT) spectroscopy. Holz als
  Roh- und Werkstoff. 58, 57-61
- 19 Zocca, F., Lomolino, G., Curioni, A., Spettoli, P., Lante, A., 2007. Detection of pectinmethylesteraseactivity in presence of methanol during grape pomace storage. Food Chemistry, 102, 59-65.
- 21
- 22
- 23

Table 1. Assignment of FT-IR spectra of grape pomace tannin extracted by different

- extraction conditions

- Peak cm<sup>-1</sup> assignment -OH stretching vibration -CH<sub>3</sub>, -CH<sub>2</sub>- stretching vibration 2973,2931

1878	C=O stretching vibration
1619,1534,1501	Aromatic squel vibration
1439	CH deformation and aromatic ring vibration
1412	Aromatic vibration
1341	saturated CH in plane bending vibration
1308,1264 , 1212	C-C frame stretching(C-CHR-C)
1111	aromatic CH in plane bending vibration
1066	C-O stretching vibration
921	aromatic CH out of plane bending vibration

-

Table 2. Elemental analysis of grape pomace tannin extracted using different extraction

- conditions

extraction conditions	C%	H%	N%	S%
A (NaOH, 5%)	35.92	3.84	1.43	0.01
B (Na <sub>2</sub> CO <sub>3</sub> (2.5%)	36.64	3.81	1.48	0.03
C (NaHCO <sub>3</sub> (2.5%)	36.43	3.80	1.27	0.04

Table 3. Distribution of polyflavonoid oligomer by MALDI-TOF for grape pomace tannin

extracts.

	$M+Na^+$	M+Na <sup>+</sup>	Unit type			
	experiment	calculated	Ι	II	III	IV
Dimer(2)	604.1	601.6	2	0	0	0
	767.6	763.6	1	0	1	0
Trimer(3)	905.1	905.9	2	1	0	0
	920.8	921.9	1	2	0	0
	1068.0	1067.9	1	1	1	0
Tetramer (4)	1193.4	1194.2	3	1	0	0
	1354.4	1356.2	2	1	1	0
Pentamer (5)	1484.6	1482.5	4	1	0	0
	1635.1	1634.5	3	1	0	1
Hexamer(6)	1771.5	1770.8	5	1	0	0
	1924.2	1922.8	4	1	0	1

- 12 13 14 15 16 17 18

Table 4. Adhesive formulation compositions, thermomechanical analysis and particle board testing. 

Extraction reagents	Formulation number	Composition Tannin / H <sub>2</sub> CO/pMDI	Tannin concentration% <sup>b</sup>	TMA MOE <sup>c</sup> at 195°C(MPa)	Density (kg/m <sup>3</sup> )	IB
NaOH(2.5%)	F1	20/1/0	30	1937.1	N/A	
1142003(2.570)	F2	20/1/0	40	2812.5	696.3	0.2
	F3	20/1/5	40	2662.5	693.7	0.2
NaOH(5%)	F4	20/1/0	30	2846.9	N/A	
Na <sub>2</sub> SO <sub>3</sub> (5%)	F5	20/1/0	40	2455.1	702	0.2
	F6	20/1/5	40	3062.8	698.4	0.3
Na <sub>2</sub> CO <sub>3</sub> (2.5%)	F7	20/1/0	30	3322.9	706.1	0.4
Na <sub>2</sub> SO <sub>3</sub> (2.5%)	F8	20/1/5	30	2833.5	710.4	0.6

Na <sub>2</sub> CO <sub>3</sub> (5%)	F9	20/1/0	30	2179.4	711.5	0.3
Na <sub>2</sub> SO <sub>3</sub> (5%)	F10	20/1/5	30	2605.9	706.9	0.60
NaHCO <sub>3</sub> (2.5%)	F11	20/1/0	30	1369.7	N/A	
$Na_2SO_3(2.5\%)$	F12	20/1/0	45	2776.8	692.6	0.20
	F13	20/1/5	45	3520.7	708.5	0.30
	F14	20/1/0	30	2932.9	N/A	
$NaHCO_3(5\%)$ $Na_2SO_2(5\%)$	F15	20/1/0	45	3878.8	705	0.3
Na <u>2</u> 503(570)	F16	20/1/5	45	3589.0	703.4	0.34
<ul> <li><sup>a</sup> % based on weight of d</li> <li><sup>b</sup> in water, % based on w</li> <li><sup>c</sup> Modulus of elasticity</li> <li><sup>d</sup> Internal bond strength</li> </ul>	dry pomace eight of dry pomace					

Fig.1. FT-IR spectra of grape pomace tannin extracted by different extraction conditions
 A: NaOH(2.5%), B: Na<sub>2</sub>CO<sub>3</sub>(2.5%), C: NaHCO<sub>3</sub>(2.5%)







9

Fig.3. Polymer structure of grape pomace tannin repeating unit: (I) procyanidin, (II)

1 2 3 prodelphinidin, (III) glucosylated procyanidin, (IV) gallated procyanidin.





Fig .4. TMA measuring MOE as a function of temperature to describe the curing of resins of grape pomace tannins.





Fig.6. The mechanism proposed for pMDI reacted with hydroxyl groups of the carbohydrates.

