



HAL
open science

Assessment of surface heterogeneity of lime treated kaolinites: Probed by low-pressure argon and nitrogen gas adsorption

Yadeta Chemed, Dimitri Deneele, Angelina Razafitianamaharavo, Frédéric Villieras, Guy Ouvrard

► To cite this version:

Yadeta Chemed, Dimitri Deneele, Angelina Razafitianamaharavo, Frédéric Villieras, Guy Ouvrard. Assessment of surface heterogeneity of lime treated kaolinites: Probed by low-pressure argon and nitrogen gas adsorption. *Applied Clay Science*, 2021, 206, pp.106069. 10.1016/j.clay.2021.106069 . hal-03191228

HAL Id: hal-03191228

<https://hal.univ-lorraine.fr/hal-03191228v1>

Submitted on 23 Mar 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

1 **Assessment of surface heterogeneity of lime treated kaolinites: probed by low-**
2 **pressure argon and nitrogen gas adsorption**

3 Yadeta C. Chemed ^a, Dimitri Deneele ^{b, c,*}, Angelina Razafitianamaharavo ^d, Frédéric Villieras ^d, Guy
4 Ouvrard ^c

5
6 ^a Adama Science and Technology University, School of Applied Natural Science, Department of Applied
7 Geology, P.O.Box 1888, Adama, Ethiopia

8 ^b IFSTTAR, GERS, EE, F-44344 Bouguenais, France

9 ^c Institut des Matériaux Jean Rouxel (IMN), Université de Nantes, CNRS, 2 rue de la Houssinière, BP
10 32229, 44322 Nantes Cedex 3, France

11 ^d Laboratoire Interdisciplinaire des Environnements Continentaux (LIEC), UMR 7569 CNRS, Ecole
12 Nationale Supérieure de Géologie, BP 40, 54501 Vandoeuvre-lés-Nancy, France

13 * Corresponding author

14 **Abstract**

15 It is a common practice to alter the undesirable behavior of clayey soils (i.e. swelling-shrinkage
16 and high plasticity) with lime addition. However, the reaction mechanism involved in the early
17 stage (first minute up to 24 hr after mixing) of lime treatment is still not well explored. In the
18 present work, the surface chemistry of lime ([Ca] = 22 mmol/l and pH=12.63) treated kaolinites
19 (Kaol) was studied using argon and nitrogen gas adsorption. The effect of pH ([Ca] = 22 mmol/l
20 and. pH=12.63 vs. [Ca] = 22 mmol/l and pH=7) was also examined. The derivative low-pressure
21 adsorption isotherms were analyzed using derivative isotherm summation (DIS), focusing on the
22 analysis of surface heterogeneity. After the treatment with lime, the specific surface area and
23 adsorption energy distribution of Kaol were modified. The adsorption of the calcium cation at both

24 investigated pH (i.e. pH 7 and pH 12.63) takes place on the basal and lateral face of Kaol, however,
25 the species of adsorbed calcium cation appeared to be different. The treatment also leads to a
26 decrease in basal surface area due to basal face-basal face particle aggregation. The basal surface
27 of Kaol treated with lime exhibited polar sites when probed with nitrogen molecule. These sites
28 may have promoted linkage and flocculation of Kaol particles, which in turn play a role in the
29 short-term modification of the macroscopic behavior of lime treated kaolins.

30 Keywords: Kaolinite, lime treated, low pressure, argon, nitrogen, surface heterogeneity

31 **1 Introduction**

32 The clayey soils usually exhibit high swelling-shrinkage behavior and compressibility and are
33 generally unsuitable for construction works. These behaviors are mainly governed by the amount
34 and type of clay minerals present in the soil. Hence, it is a common practice to use lime (CaO or
35 Ca(OH)₂) as a chemical additive to alter these undesirable properties and made the clayey soil
36 suitable in construction activities (Bell, 1996; Dang et al., 2016; Emarah and Seleem, 2018, Das
37 et al., 2021). When lime is added to the soil in presence of moisture, the swelling potential and
38 plasticity decrease in the short-term, and mechanical strength increases in the long-term (Bell,
39 1996).

40 The long-term stabilization mechanism (i.e. pozzolanic reaction) has been thoroughly studied and
41 well understood (Bell, 1996; Al-Mukhtar et al., 2010; Pomakhina et al., 2012; Eisazadeh et al.,
42 2012; Vitale et al., 2017). It is related to precipitation of cementitious hydrated gels. On the other
43 hand, the short-term reaction mechanisms, which are mainly controlled by surface phenomena
44 (Bell, 1996; Chemedi et al., 2015; Vitale et al., 2016), are less explored. The reaction at this stage
45 is crucial in soil stabilization as it can affect the mixing ability of the soil with lime (Konan et al.,

46 2009) and retards long-term pozzolanic reaction (Chemedá et al., 2018). Hence, a better
47 understanding of the reaction mechanism is central for the optimization of the technique.

48 The true surface interaction of clay minerals with a solution, which is difficult to look at directly,
49 is usually inferred from adsorption at solid-liquid interface or characterization of surface chemistry
50 of the treated sample. In the previous works (Konan et al., 2009; Chemedá et al., 2018), adsorption
51 at solid-liquid interface were used to assess lime solution-Kaol interfacial phenomenon. Their
52 findings revealed that adsorption of calcium cation mainly takes place on a permanent charge and
53 Si-O⁻ sites at neutral pH, whereas adsorption on pH-dependent charge site is dominant at alkaline
54 pH. In addition, the adsorbed species of calcium cation at pH 7 and pH 12.63 found to be different.
55 However, using this technic, it is impossible to identify the adsorption sites due to difficulty in
56 isolation of the different faces (basal and lateral faces). Thus, a study on surface characteristics
57 with techniques that can distinguish the different crystallographic surfaces is indispensable.

58 The different crystallographic surfaces of clay minerals can be probed using high-resolution gas
59 adsorption coupled with DIS (Michot et al., 1990; Bardot et al., 1998). The technique, particularly
60 low-pressure argon gas adsorption was successfully applied in previous works (Villiéras et al.,
61 1992; 1997; Bardot et al., 1998; Hassan et al., 2005; Mbey et al., 2019) for a quantitative estimation
62 of surface heterogeneity in terms of lateral and basal surfaces of different clay minerals.
63 Furthermore, it has been demonstrated that the presence and nature of surface cation viz. size,
64 electronegativity and polarizability influences the normal interaction energy between the probe
65 gas (argon and nitrogen) and the probed surface (Villiéras et al., 1992; Bardot et al., 1998; Hassan
66 et al., 2005). These advantages can be utilized to indirectly probe the nature (species) of the surface
67 cations and adsorption sites.

68 In the present work, the surface chemistry of four Kaol samples treated with lime ($\text{Ca}(\text{OH})_2$) was
69 characterized using low-pressure quasi-equilibrium argon gas adsorption in order to identify
70 calcium cation adsorption sites. For this purpose, the derivative gas adsorption isotherms of lime
71 treated and Na-exchanged Kaol samples were analyzed using derivative isotherm summation
72 (DIS), focusing on the analysis of surface heterogeneity. The effect of pH value was also
73 investigated by comparing isotherms of lime ($[\text{Ca}] = 22 \text{ mmol/l}$ and $\text{pH}=12.63$) and calcium
74 chloride ($[\text{Ca}] = 22 \text{ mmol/l}$ and $\text{pH}=7$) treated samples. Polar/nonpolar surface characteristics of
75 Kaol samples were examined using nitrogen gas adsorption.

76 **2 Materials and experimental procedures**

77 **2.1 Materials**

78 Four Kaols of different properties and origins, namely KGa-2 (high defect), KGa-1b (low defect),
79 SPwt (low defect) and B24 (high defect), were selected for this investigation. Kaol KGa-1b and
80 KGa-2 were purchased from the Source Clay Repository of the Clay Minerals Society. Kaol SPwt
81 and B24 were collected from Cornwall, UK and Charente basin, France, respectively. Chemical
82 analysis and X-ray diffraction pattern showed the mineralogical purity of the Kaol samples is >
83 95% ([Chemedda et al., 2018](#)). Minor phases in the samples include muscovite (in B24 and SPwt),
84 quartz and anatase. Hydrated lime, $\text{Ca}(\text{OH})_2$ (Merck, analytical grade, purity above 97%) and
85 $\text{CaCl}_2 \cdot 6\text{H}_2\text{O}$ (analytical grade, Merck, Germany) were utilized for preparation of hydrated lime
86 and calcium chloride solution, respectively. High purity argon gas (> 99.9996%) and nitrogen gas
87 (> 99.999%) provided by Alphagas were used for gas adsorption experiment.

88 **2.2 Chemical treatment**

89 The Kaol samples were first purified (i.e. the samples were de-carbonated, organic matters were
90 removed and clay sizes were fractionated) and then exchanged with sodium at pH 7. Na-Kaol was
91 prepared by sodium exchange in 1M NaCl solution. The samples were then washed with distilled
92 water repeatedly until the supernatant was chloride free and had lower conductivity ($< 5 \mu\text{S}/\text{cm}$).
93 Lime and calcium chloride treated Kaol were prepared by suspending Na-exchanged Kaol samples
94 in freshly prepared calcium hydroxide ($[\text{Ca}] = 22 \text{ mmol/l}$ and $\text{pH}=12.63$) and calcium chloride
95 ($[\text{Ca}] = 22 \text{ mmol/l}$ and $\text{pH}=7$) solution, respectively. For this purpose, 6 g sample were kept in
96 contact with calcium chloride and lime solutions (30 ml) in centrifuge tubes and shaken
97 mechanically. This was followed by centrifugation for 15 min at 8000 rpm to separate the solid
98 from solution. The preparations (weighting and mixing) were performed under argon atmosphere
99 in a nitrogen glove box.

100 **2.3 Low-pressure gas adsorption at 77K**

101 The low-pressure adsorption isotherms were recorded with lab-built quasi-equilibrium device (at
102 LIEC (Laboratoire Interdisciplinaire des Environnements Continentaux), Nancy) equipped with
103 three high accuracy differential pressure sensors (0 – 10 Pa, 0 – 103 Pa and 0 – 105 Pa). A full
104 review of the technique and the setup of the apparatus could be found in previous works ([Michot
105 et al., 1990](#); [Bardot, 1998](#)). The principle of the measurement is based on introduction of adsorbate
106 through a calibrated microleak continuously at a constant and slow flow rate ([Michot et al., 1990](#);
107 [Villieras et al., 1992; 1997](#)).

108 About 1 g of samples were put in the adsorption cell and outgassed for 18 hr under a residual
109 pressure of 10^{-4} Pa. The outgassing was carried out at three different temperatures in successive
110 steps (110°C, 150°C and 200°C) on the same sample. More than 3000 data points were obtained
111 from recording of quasi-equilibrium pressures as a function of time. To obtain derivative

112 adsorption isotherm, the data points were plotted as first derivative of adsorbed quantity vs.
113 logarithm of relative pressure ($\ln(P/P_0)$), with P_0 being the saturated vapor pressure (Michot et al.,
114 Villieras et al., 1992; 1997). The derivative adsorption isotherm represents the adsorption
115 energy distribution for the used gaseous probe (Michot et al., 1990; Bardot, 1998). The
116 experimental derivative adsorption isotherms are then modeled with the sum of “local” theoretical
117 isotherms derived from Brunauer, Emmett and Teller (BET) formalism using DIS procedure
118 (Villieras et al. 1992). The lateral interaction parameter (ω) was kept constant (± 0.2) during the
119 modeling of isotherms. For each “local” adsorption isotherm, three parameters were then obtained:
120 the position of the peak ($\ln P/P_0$), which depends on solid-gas and gas-gas interaction energies; the
121 lateral interaction parameter between adjacent adsorbed gas molecules (ω), and a monolayer
122 capacity (V_m). The specific surface area was calculated from monolayer capacity of each domain
123 of local isotherm by applying BET derived formalism.

124 **3. Results and discussion**

125 **3.1. Effect of outgassing temperature**

126 The effect of outgassing temperature on the argon adsorption energy distribution were analysed
127 first to identify cations on charged and neutral surface. An example of experimental derivative
128 argon adsorption isotherm for different outgassing temperatures of Na-KGa-2 (high defect) and
129 Na-KGa-1b (low defect) samples are presented in Figure 1. Irrespective of the outgassing
130 temperature, all the derivative adsorption isotherms show the same shapes with a main peak
131 located at low and medium energy ($\ln(p/p_0) > -5$) representing the adsorption on the basal surfaces.
132 While the shoulder and tail at high energy, located at $\ln(p/p_0) < -6$, attributed to the adsorption on
133 lateral surfaces. At $\ln(p/p_0) > -3$, low energy domain represent adsorption on basal surface and
134 multilayer adsorption (Villieras et al., 1992; 2002; Bardot et al., 1998; Hassan et al., 2005). With

135 increasing outgassing temperature, the major lower energy peak shifted to lower energy and the
136 peak become narrow, i.e. the low energy surfaces become energetically less heterogeneous
137 (Villieras et al., 1992; 2002).

138 The derivative argon adsorption isotherms were modelled using six local isotherms assigned to
139 local derivative adsorption isotherms (Hassan et al., 2005) following DIS techniques. The three
140 highest energy domains (1, 2 and 3) attributed to adsorption on lateral faces whereas the three low
141 energy domains (4, 5 and 6) represent adsorption on basal faces (Bardot et al., 1998; Hassan et al.,
142 2005). The obtained modelling parameters (i.e. $\ln(P/P_0)$ which represents the normal interaction
143 energy of the argon molecule with surface (Villieras et al., 1992;1997;2002), volume adsorbed
144 (V_m) and lateral interaction (ω)) after different outgassing temperature are presented in Table 1,
145 for Na-KGa-2 and Na-KGa-1b. Irrespective of the outgassing temperature, the total specific
146 surface area remains nearly constant. It means that the modification of the derivative adsorption
147 features is mainly related to variation in the argon adsorption energy distribution rather than the
148 variation of amount of gas adsorbed. Concerning local isotherms, the position of domains 1, 2, 3
149 and 4 appeared to be unaffected by outgassing temperature suggesting charged lateral (domain 1,
150 2 and 3) and basal (domain 4) surfaces. On these sites, the surface cations bound tightly (Hassan,
151 2005). On the other hand, domain 5 shows relatively greater sensitivity to outgassing temperature
152 (i.e. the peak position shifts to lower energy after outgassing at 200°C) implying the elimination
153 of physisorbed compounds and/or loosely bound cations from uncharged surface (Hassan, 2005).
154 Since the purpose of using this technique is to identify the calcium adsorbed on charged surface
155 (not neutral compound), domain 3 (charged lateral surface) and 4 (charged basal surface) were
156 considered for further analysis (next section). The isotherms after outgassing at 200°C were also

157 considered to minimize the effect of physisorbed compounds on the gas adsorption energy
158 distribution.

159 **3.2. Effect of chemical treatment**

160 **3.2.1. Derivative adsorption isotherms**

161 The derivative argon adsorption isotherms of the Na-exchanged, lime treated and calcium chloride
162 treated samples are compared in [Figure 2](#), for an outgassing temperature at 200°C. After treatment,
163 major differences are noted in the shape of the derivative adsorption isotherms, particularly for the
164 low energy peak, due to change both in intensity and position of the peak. In both cases, the
165 intensity of the major peak attributed to basal face decreases and becomes wider. However, the
166 change is more pronounced for lime treated sample. This finding is consistent with more calcium
167 adsorption and surface modification in the presence of lime than with calcium chloride solution
168 ([Chemedá et al., 2015](#)). In the case of lateral faces, additional argon molecules are adsorbed at high
169 energy range resulting in a well-developed high energy peak which could corresponds to a new
170 adsorption site generated by flocculated structure ([Bardot et al., 1998](#)). The intensity of the peak
171 is relatively higher for lime treated sample in accordance with higher flocculation in the presence
172 of hydrated lime than calcium chloride solution ([Chemedá et al., 2015](#)). Generally, the major
173 modification on the lower energy peak suggests the interactions of the two solutions (lime and
174 calcium chloride solutions) with Kaol dominantly takes place on the basal surface. However, with
175 this technique, it is impossible to know exactly whether the reaction is on silica or alumina basal
176 faces.

177 An example of the derivative adsorption isotherms together with their decompositions before and
178 after treatment with lime and calcium chloride solutions are presented in [Figure 3](#), for KGa-1b and
179 KGa-2. The numerical DIS results for the four studied Kaol are summarized in [Table 2 & 3](#).

180 **3.2.2. Textural parameters**

181 The total specific surface area deduced from the sum of monolayer capacity of each domain of
182 local isotherm by applying BET derived formalism decreased after lime and calcium chloride
183 treatments as evidenced from the decrease in the intensity of low energy peak. Nevertheless, in
184 some cases (KGa1b, KGa-2), the adsorption of additional argon in high energy region obscured
185 this change ([Table 2](#)). The change is more evident in the low energy peak, particularly for domains
186 4 and 5 ([Figure 4](#)). The extent of the change is different for the four studied Kaol samples, which
187 appears to be depend on the degree of defect and cation exchange capacity. Indeed, there is an
188 approximate linear relationship between the amounts of calcium adsorbed ([Chemedá et al., 2018](#))
189 and the change (decreased) in basal specific surface area derived from domains 4 and 5 ([Figure 5](#)).
190 The more the amount of calcium adsorbed, the more the basal specific surface area decreased. This
191 phenomena can be interpreted in two ways: 1) involvement of exchangeable cation, in the present
192 case calcium, in the first mono-layer adsorption site of argon molecule and/or 2) the aggregation
193 of Kaol particles.

194 The first possibility can be checked by comparing the surface area occupied by the two cations
195 (sodium and calcium) knowing their amount on the surface (from [Chemedá et al., 2018](#)). For this
196 purpose, surface area occupied by Na and Ca-cations were compared for the raw (Na-Kaol) and
197 calcium chloride treated samples ([Table 4](#)). The area occupied by Ca-cation is either equal or lower
198 than the area occupied by Na-cation, which is not surprising as the size of the two cations are
199 nearly the same ($\text{Ca} = 0.99 \text{ \AA}$, $\text{Na} = 0.97 \text{ \AA}$) and the former neutralizes two charge sites per cation.

200 It means that the area should increase when Na-cation is replaced by Ca-cation contrary to our
201 observation. The other possibility is aggregation of Kaol particles. The replacement of monovalent
202 cations by high order valency cations can change the particle arrangement from dispersed to
203 flocculated structure (Mpofu et al., 2003, 2005; Chemedda et al., 2015). The decrease in basal
204 specific surface area could be thus linked to the aggregation (probably basal face-basal face) of the
205 clay particle that makes inaccessible a part of basal surface for argon adsorption. A similar
206 phenomenon between monovalent and divalent cation (Na vs. Ca, Li vs. Mg and K vs. Ba) was
207 observed for illite by Bardot (1998), although the change is more pronounced in the case of illite.
208 However, the observed modification cannot solely accounted to change in texture (aggregation) of
209 Kaol particles as there is also a shift in peak position in addition to decrease in the intensity. The
210 observed difference could also be linked to the effect of the treatments on surface chemistry (this
211 point addressed in next section).

212 **3.2.4. Surface energetic parameters**

213 The energetic parameters ($\ln(P/P_0)$) of domain 3 and 4 varied depending on the nature of the
214 treatment (i.e. shifted to higher energy after lime treatment), revealing the modification of surface
215 chemistry of lateral and basal surfaces (i.e. different surface cations) (Figure 6). This hypothesis
216 is furthermore supported by the fact that the obtained peak position in the case of raw sample (Na-
217 Kaol) and calcium chloride treated sample (Ca-Kaol) compared well with the peak position of Na-
218 illite (for domain 4, $\ln(P/P_0) = -4.53$ and for domain 3, $\ln(P/P_0) = -6.95$) and Ca-illite (for domain
219 4, $\ln(P/P_0) = -4.56$ and for domain 3, $\ln(P/P_0) = -7.05$), respectively (Bardot et al., 1998). On the
220 other hand, the peak positions of both domains in the case of lime treated sample are higher than
221 the calcium chloride treated samples. The only difference between the two solutions (i.e. calcium
222 hydroxide and chloride solution) is the initial pH. The observed difference could be then attributed

223 to the effect of pH on surface charge density and the nature of calcium available for adsorption.
224 However, as it has been demonstrated for the case of synthetic saponites with different layer charge
225 (Michot and Villieras, 2002), the normal adsorption energy of argon on basal face is much more
226 sensitive to the nature of surface cation than to the origin and the density of charge. One can then
227 suppose that the nature of the charge compensating cations in the two cases are different. Indeed,
228 CaOH^+ and Ca^{2+} are the dominant species of calcium available for adsorption at pH= 12.6 and 7,
229 respectively (Mpofu et al., 2005; Chemedda et al., 2015). Hence, in the case of lime treated sample
230 (i.e. CaOH^+ as a surface cation), the argon molecule interacts with OH-ion in addition to calcium
231 and the size is also larger than calcium cation. Therefore, the interaction energy is expected to be
232 higher than the case of the calcium chloride treated sample (i.e. Ca^{2+} as surface cation).

233 3.2.5. Argon vs. nitrogen isotherms

234 Nitrogen and argon have different characteristics: argon molecule gives rise to only non-specific
235 interactions, while due to its inducible quadrupolar momentum, nitrogen molecule interacts also
236 with specific sites (Rouquerol et al., 1989; Villieras et al., 2002; Garnier et al., 2005), provided
237 that the surface of the particle carries localized polar groups or positive charges. For the assessment
238 of polar or non-polar surface characteristics before and after treatment, the adsorption energy
239 distributions of the first monolayer as a function of natural logarithm of pressure ($\ln P$) for nitrogen
240 and argon were compared for selected samples (Figure 7). As usually observed for clay minerals,
241 there is difference between the isotherms of the two gases at the higher energy range for the three
242 samples irrespective of the treatment. It mainly corresponds to specific interaction of nitrogen with
243 surface polar sites (Villieras et al., 1992; 2002; Bardot et al., 1998) and will not be further discussed
244 here as it is not related to the effect of the treatment.

245 Concerning the basal face, the shape of the peak of the argon and nitrogen derivative adsorption
246 isotherms appeared nearly identical (i.e. narrow and sharp) for Na-exchanged and calcium chloride
247 treated sample. Furthermore, the main peak in both cases located at the same position (the values
248 of $\ln P$ around 6 to 7) suggesting non-polar nature of the basal surface. For the case of lime treated
249 sample, the shape of the two gas isotherms are different as the peak of nitrogen isotherm is
250 relatively wider due to additional shoulder at high energy side. The major peak, which located on
251 the same position for the two gases ($\ln P$ around 6) similar to Na-exchanged and calcium chloride
252 treated samples, can be attributed to non-polar surface site. On this site, both nitrogen and argon
253 adsorbed through low energy interaction (Villiéras et al., 2002; Garnier et al., 2005). A shoulder
254 at higher energy side (indicated by arrow) in the case of nitrogen isotherm, could be attributed to
255 the interaction of nitrogen molecules with some polar/ electropositive sites (Villiéras et al., 2002;
256 Garnier et al., 2005) on the basal faces. The chemical nature of this site is not known exactly in
257 the present study, hence, a deeper understanding of the surface chemistry of lime treated sample
258 (at microscopic level) would be necessary to interpret this observation. It is tentatively attributed
259 to CaOH^+ or electropositive sites generated by adsorption of hydrolysis species of calcium as
260 indicated by negative to positive surface charge reversal of Kaol particle in the presence of calcium
261 rich alkaline ($[\text{Ca}] = 22 \text{ mmol/l}$ and $\text{pH}=12.63$) solution (Chemedda et al., 2015). These sites may
262 promote linkage and aggregation of Kaol particles.

263 **4. Conclusion**

264 The results of this work revealed that the adsorption of calcium cation from lime ($[\text{Ca}] = 22 \text{ mmol/l}$
265 and $\text{pH}=12.63$) and calcium chloride ($[\text{Ca}] = 22 \text{ mmol/l}$ and $\text{pH}=7$) solution takes place both on
266 the basal and lateral faces. These sites can be attributed to Si-O^- (lateral face) and local charge
267 defect (i.e. Al^{+3} for Si^{+4} substitution) in tetrahedral sheet at pH 7, and additional charge sites

268 generated by dissociation of Al₂OH and Al-OH functional groups on octahedral basal and lateral
269 faces, respectively, at pH 12.6. The species of calcium cation available for adsorption at the two
270 pH conditions are different as evidenced by the variation of the adsorption energy ($\ln(P/P_0)$)
271 corresponds to charged surface on the basal and lateral faces depending on the source of the cation
272 (calcium chloride or lime solution). The data indirectly validates the results obtained in previous
273 works (i.e. Ca²⁺ and CaOH⁺ at pH 7 and 12.6, respectively) from adsorption at solid-liquid
274 interface (Chemeda et al., 2015) and calculation of pH-dependent calcium cation hydrolysis
275 (Mpofu et al., 2003; 2005). The face-to-face aggregation of Kaol particles, owing to compression
276 of electrical double layer in the presence of calcium cation, mainly accounts for the decrease of
277 basal specific surface area or adsorbed gas volume after lime and calcium chloride treatment. The
278 basal surface of Na-exchanged and calcium chloride treated Kaol samples exhibits mainly non-
279 polar characteristics, whereas lime treatment induces additional polar surface sites. These sites
280 could be CaOH⁺ or electropositive sites emerged on Kaol surface in the presence of calcium rich
281 alkaline solution, which in turn induced particle linkage and short-term modification of
282 macroscopic behavior of kaolins.

283 **Acknowledgment**

284 The authors acknowledge the two anonymous reviewers for their constructive comments and
285 suggestions which greatly improved this paper.

286 **Reference**

287 Al-Mukhtar, M., Lasledj, A., Alcover, J.-F., 2010. [Behaviour and mineralogy changes in lime-](#)
288 [treated expansive soil at 20°C. Appl. Clay Sci. 50, 191–198.](#)

289 Bardot, F., 1998. Les minéraux argileux et leur hétérogénéité superficielle : Influence de la nature
290 des cations compensateurs de l'illite sur les mécanismes d'adsorption de gaz. Thèse de doctorat,
291 Institut National Polytechnique de Lorraine., Nancy, 176 p

292 Bardot, F., Villiéras, F., Michot, L.J., François, M., Gérard, G., Cases, J.M., 1998. High resolution
293 resolution gas adsorption study on illites permuted with various cations assessment of surface
294 energetic properties. *Journals of Dispersion Science and Technology* 19, 739-759

295 Bell, F.G., 1996. Lime stabilisation of clay minerals and soils. *Eng. Geol.* 42, 223–237.

296 Chemedá, Y.C., Deneele, D., G., Ouvrard, G., 2018. Short-term lime solution kaolinite interfacial
297 chemistry and its effect on long-term pozzolanic activity. *Appl. Clay Sci.* 161, 419 – 426

298 Chemedá, Y.C., Deneele, D., Christidis, G., Ouvrard, G., 2015. Influence of hydrated lime on
299 surface properties and interaction of kaolinite particles. *Appl. Clay Sci.* 107, 1 – 13

300 Dang, L.C., Fatahi, B., Khabbaz, H., 2016. Behaviour of Expansive Soils Stabilized with Hydrated
301 Lime and Bagasse Fibres. *Procedia Engineering* 143, 658 – 665.

302 Das, G., Razakamanantsoa, A., Herrier, G., Saussaye, L., Lesueur, D., Deneele, D., 2021.
303 Evaluation of the long-term effect of lime treatment on a silty soil embankment after seven years
304 of atmospheric exposure: Mechanical, physicochemical, and microstructural studies. *Engineering*
305 *Geology* 281, 105986.

306 Eisazadeh, A., Kassim, K.A., Nur, H., 2012. Solid-state NMR and FTIR studies of lime stabilized
307 montmorillonite and lateritic clays. *Appl. Clay Sci.* 67–68, 5–10.

308 Emarah, D.A., and Seleem, S.A. 2018. Swelling soils treatment using lime and sea water for roads
309 construction. *Alexandria Engineering Journal* 57, 2357 – 2365.

310 Garnier, C., Gorner, T., Razafitianamaharavo, A., Villieras, F., 2005. Investigation of Activated
311 Carbon Surface Heterogeneity by Argon and Nitrogen Low-Pressure Quasi-Equilibrium
312 Volumetry. *Langmuir* 21, 2838 – 2846

313 Hassan, M.S., 2005. Etude des hétérogénéités morphologiques et énergétiques superficielles des
314 kaolinites par AFM et adsorption de gas. Thèse de doctorat, Institut National Polytechnique de
315 Lorraine., Nancy, 176 p

316 Hassan, M.S., Villieras, F., Razafitianamaharavo, A., Michot, L.J., 2005. Role of Exchangeable
317 Cations on Geometrical and Energetic Surface Heterogeneity of Kaolinites. *Langmuir* 21, 12283
318 – 12289

319 Konan, K.L., Peyratout, C., Bonnet, J.-P., Rossignol, S., Oyetola, S., 2009. Comparison of surface
320 properties between kaolin and metakaolin in concentrated lime solutions. *Journal of Colloid and*
321 *Interface Science* 339, 103 – 109

322 Mbey, J.A., Thomasb, F., Razafitianamaharavob, A., Cailletb, C., F. Villieras, F., 2019. A
323 comparative study of some kaolinites surface properties. *Appl. Clay Sci.* 172, 135 – 145

324 Michot, L., Francois, M., Cases, J.M., 1990. Surface heterogeneity study by quasi-equilibrium gas
325 adsorption procedure. *Langmuir* 6, 677 – 681

326 Michot, L.J., Villieras, F., 2002. Assessment of surface energetic heterogeneity of synthetic Na-
327 saponites. The role of layer charge. *Clay Minerals* 37, 39 – 57

328 Mpofo, P., Addai-Mensah, J., Ralston, J., 2003. Influence of hydrolyzable metal ions on the
329 interfacial chemistry, particle interactions, and dewatering behavior of kaolinite dispersions.
330 *Journal of Colloid and Interface Science* 261, 349–359

331 Mpofu, P., Addai-Mensah, J., Ralston, J., 2005. [Interfacial chemistry, particle interactions and](#)
332 [improved dewatering behaviour of smectite clay dispersions. International Journal of Mineral](#)
333 [Processing 75, 155–171](#)

334 Pomakhina, E., Deneele, D., Gaillot, A.C., Paris, M., Ouvrard, G., 2012. [²⁹Si solid state NMR](#)
335 [investigation of pozzolanic reaction occurring in lime treated Ca–bentonite. Cem. Concr. Res. 14,](#)
336 [626–632.](#)

337 Rouquerol, J., Rouquerol, F., Grillet, Y., 1989. [Energetical aspects of N₂ and Ar adsorption:](#)
338 [specific adsorption, two-dimensional phase changes and adsorption in micropores. Pure and Appl.](#)
339 [Chem. 61, 1933 - 1936](#)

340 Villieras, F., Cases, J. M., François, M., L. Michot, L.J., Thomas, F., 1992. [Texture and Surface](#)
341 [Energetic Heterogeneity of Solids from Modeling of Low Pressure Gas Adsorption Isotherms.](#)
342 [Langmuir 8, 1789 – 1795](#)

343 Villieras, F., Michot, L.J., Bardot, F., Cases, J. M., François, M., Michot, L.J., Rudzinski, W.,
344 1997. [An improved Derivative Isotherm Summation method to study surface heterogeneity of clay](#)
345 [minerals. Langmuir 13, 1104 – 1117](#)

346 Villieras, F., Michot, L.J., Bardot, F., Chamerois, M., Eypert-Blaison, C., François, M., Gérard,
347 G., Cases, J-M., 2002. [Surface heterogeneity of minerals. C. R. Geoscience 334, 597–609](#)

348 Vitale, E., Deneele, D., Russo, G., Ouvrard, G., 2016. [Short-term effects on physical properties of](#)
349 [lime treated kaolin. Appl. Clay Sci. 132–133.](#)

350 Vitale, E., Deneele, D., Paris, M., Russo, G., 2017. [Multi-scale analysis and time evolution of](#)
351 [pozzolanic activity of lime treated clays. Appl. Clay Sci. 141, 36–45.](#)