Tetracycline removal with activated carbons produced by hydrothermal carbonisation of *Agave americana* fibres and mimosa tannin

Taher Selmi, Angela Sanchez-Sanchez, Philippe Gadonneix, Jacek Jagiello, Mongi Seffen, Habib Sammouda, Alain Celzard, Vanessa Fierro

► To cite this version:

Taher Selmi, Angela Sanchez-Sanchez, Philippe Gadonneix, Jacek Jagiello, Mongi Seffen, et al.. Tetracycline removal with activated carbons produced by hydrothermal carbonisation of *Agave americana* fibres and mimosa tannin. *Industrial Crops and Products*, 2018, 115, pp.146-157. 10.1016/j.indcrop.2018.02.005 . hal-03207566

HAL Id: hal-03207566

<https://hal.univ-lorraine.fr/hal-03207566>

Submitted on 25 Apr 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Tetracycline removal with activated carbons produced by hydrothermal carbonisation of Agave americana fibres and mimosa tannin

Taher Selmi ^a, Angela Sánchez-Sánchez ^b, Philippe Gadonneix ^b, Jacek Jagiello^c,
Mongi Seffen ^a, Habib Sammouda ^a, Alain Celzard ^b, Vanessa Fierro ^{* b}

a. Laboratory of Energy and Materials (LabEM). High School of Sciences and Technology of
Hamam Sousse, BP 4011 Hamam Sousse (Sousse University-Tunisia).

b. Institut Jean Lamour, UMR Université de Lorraine-CNRS 7198, 27 rue Philippe Séguin,
BP 21042, 88051 Epinal Cedex 9, France

c. Micromeritics Instrument Corporation, 4356 Communications Drive, Norcross, GA 30093,
United States

* Corresponding author: (Vanessa Fierro)

Tel: + 33 372 74 96 77 Fax: + 33 372 74 96 38

E-mail address: Vanessa.Fierro@univ-lorraine.fr

Abstract

Two series of carbons were prepared from *Agave americana* fibres (A) mixed with *mimosa* Tannin (T) at different T to A weight ratios $W = 0/4; 1/3; 2/2; 3/1$ and $4/0$. The first series, CTAW, was produced by direct pyrolysis of the precursors (T, A, or blends) and the second one, CHTAW, was produced in two steps, hydrothermal carbonisation (HTC) and then pyrolysis. Materials from the CHTAW series presented higher surface areas, H/C atomic ratios and carbon yields than those of the CTAW series. CHTA2/2 was next activated with CO_2 during 1, 2 or 3h. The appropriate selection of the synthesis conditions allowed obtaining high-surface area activated carbons (ACs) with similar carbon yields and average pore diameters as non-activated, low-surface area, carbon materials. CHTA2/2 activated for 2h was tested for tetracycline (TC) adsorption, and the equilibrium was reached much faster than for a reference commercial AC due to the presence of macropores and mesopores provided by carbonised A. TC adsorption was spontaneous, and adsorption kinetics was adequately fitted by a pseudo-second-order model. TC adsorption essentially depends on surface area, and the results reported herein are in the range of those reported in the open literature.

Keywords: Hydrothermal carbonisation, *Agave americana*, *Mimosa tannin*, Physical activation, Activated carbon, Tetracycline adsorption

1 **Introduction**

2 Activated carbons (ACs) are porous materials characterised by highly developed pore
3 texture, specific area and surface functionalities. ACs are produced from many different
4 precursors, biomass among them, the selection of which being mainly conditioned by
5 availability and cost. Among biomass, coconut shells (Rodríguez-Estupiñan et al., 2013),
6 algae (Altenor et al., 2012), rice straw (Fierro et al., 2010a; Schaefer et al., 2017), lignin
7 (Fierro et al., 2007) or ramboutan (*Nephelium lappaceum*) skin (Njoku et al., 2014) can be
8 mentioned but are just examples. Pore texture, surface area and amount of functional groups
9 in ACs can be enhanced by physical activation in which the precursor is pyrolysed under inert
10 gas, usually nitrogen at high temperature, at least 800°C, and further exposed to an oxidising
11 gas. The latter is usually steam or CO₂, at temperatures within the range from 800 to 1000°C
12 (Ghouma et al., 2015). Physical activation with CO₂ allows obtaining ACs with high surface
13 areas and amount of surface functionalities (Molina-Sabio and Rodríguez-Reinoso, 2004).
14 Activation time and flow of oxidising gas are the main parameters influencing the final AC
15 characteristics (Acosta et al., 2016), and these parameters are sometimes optimised by
16 experimental design (Zhao et al., 2011). Unlike for chemical activation, the resultant ACs
17 doesn't need washing, which is a time-consuming step.

18 In the last decade, the interest for hydrothermal carbonisation (HTC) treatment
19 significantly increased (Braghiroli et al., 2014; Braghiroli et al., 2015; Schaefer et al., 2016),
20 although this process is known since 1913 (Bergius, 1915). HTC indeed allows transforming
21 biomass precursors into hydrochars with a hydrophilic shell and a hydrophobic core
22 (Braghiroli et al., 2015) in a very simple way. In brief, biomass and water are introduced in an
23 autoclave which is then placed in an oven at moderate temperature (150-250°C), and in which
24 the pressure is auto-generated. In these conditions, hydrolysis of the soluble biopolymers
25 takes place, followed by fragmentation (Braghiroli et al., 2015). Next, the resultant monomers

condensate and the as-obtained nuclei grow through a diffusion process, usually leading to carbonaceous microspheres. Different biomasses have been submitted to HTC to produce carbon materials, such as corn stalk and *Tamarix ramosissima* (Ling-Ping et al., (2012)), cellulose (Luca et al., 2014) or tannin (Braghiroli et al., 2015). HTC is also an interesting method for producing carbons doped with heteroatoms such as nitrogen. Thus, nitrogen-rich carbonaceous materials were synthesised from tannin submitted to HTC in concentrated ammonia (Braghiroli et al., 2012). However, hydrochars must be pyrolysed for obtaining true carbon materials, and have to be further activated to enhance their porosity and functionalities and hence to produce activated carbons (ACs).

ACs are widely used as adsorbents and are applied in many fields such as, among others, air purification (Choi et al., 2016), drinking water and wastewater treatment (Zietzschmann et al., 2016), gas storage (Sethia and Sayari, 2016), or purification of pharmaceutical products (Li et al., 2015). The gradual increase of antibiotics presence in natural water and antibiotics bioaccumulation, tetracycline (TC) among them, is a serious threat to the environment. Therefore, antibiotics removal is a scientific and technological challenge, and a matter of public concern. Antibiotics removal can be achieved by membrane filtration (Kovalova et al., 2012), electrochemical treatments (Dirany et al., 2012) or adsorption onto porous materials (Acosta et al., 2016; Ncibi and Mika, 2015).

The main objective of the present study was to remove TC using ACs produced from a low-cost, easily available and highly abundant local biomass in Tunisia: *Agave americana* fibres (A). *Mimosa* tannin (T) was used to increase the carbon yield, and ACs were synthesised by varying several experimental conditions: T/A weight ratio, addition of an HTC step or not, and activation time. We showed that the ACs prepared here had higher performances than a commercial AC in terms of TC adsorption. Traditional studies including basic thermodynamic calculations, pH effect, equilibrium and kinetics aspects were also

carried out. A review of the TC adsorption capacities reported in the open literature was finally provided in order to compare with the performances of the ACs prepared herein.

2. Material and methods

2.1 Raw materials

Agave americana fibres (A) were collected at Ben Salem, in the central Tunisian region of Kairouan. The relevant fibre extraction method was described in the literature (Ben Hamissa et al., 2007). Briefly, *Agave americana* plants were treated in a NaCl-salt solution at 80°C for 8h. Afterwards, they were beaten with a mallet and vigorously thrashed with a scraper in order to separate the fibres (Ben Hamissa et al., 2013). Fibres were washed several times with distilled water to remove non-cellulosic particles, and were dried in an oven at 70°C until constant weight. Then, the fibres were finely cut and sieved using an electric sifter. The particle size used in the experiments was comprised between 1 and 5 mm.

Tannin (T) was extracted from *Mimosa* tree barks (*Acacia mearnsii*, De Wild), and was kindly supplied by the company SilvaChimica (San Michele Mondovi, Italy). This material is commercially available under the name “Fintan OP”, and its extraction protocol has been described in detail elsewhere (Braghiroli et al., 2014). Briefly, fresh barks were subjected to leaching in a diluted sodium bisulphite aqueous solution at 70°C. The resultant solutions were concentrated and then spray-dried to yield a light-brown powder containing 1 wt. % of amino and imino acids, 4-6 wt. % of water, 80-82 wt. % of phenolic flavonoid materials. The remainder consists in monomeric and oligomeric carbohydrates, mainly broken pieces of hemicelluloses (Braghiroli et al., 2014).

A commercial AC, F300 provided by the company Calgon, was used as reference material for Tetracycline (TC) adsorption. TC, 98% pure, was provided by Sigma Aldrich.

2.2 Activated carbon synthesis

Two series of carbons were prepared from 4g of different precursors obtained by mixing *Agave americana* fibre (A) and tannin (T) at several T to A weight ratios (W) and maintaining the final mass to 4g (i.e., $W = 0/4; 1/3; 2/2; 3/1$ and $4/0$). The carbon precursors were labelled TA0/4; TA1/3; TA2/2; TA3/1 and TA4/0, respectively, and this series was called TAW.

The first carbon series was prepared by direct pyrolysis of the aforementioned TAW precursors in a horizontal tubular furnace (Carbolite CTF). 1g of carbon precursor was placed in a quartz boat and transferred into a quartz tube continuously flushed with nitrogen at a flow rate of 100 mL/min. The tube was heated in the furnace at 1°C/min up to 900°C, and such final temperature was held for 1h. Then, the furnace was allowed to cool down to room temperature under nitrogen flow. The resultant samples after pyrolysis and drying at 105°C were labelled CTAW, where “C” means carbon.

The second carbon series was prepared by submitting the TAW precursors to hydrothermal carbonisation (HTC) before pyrolysis at 900°C. In a typical experiment, 4g of TAW were introduced in a glass vial containing 40g of distilled water, and the vial was introduced into a 200 mL Teflon-lined autoclave (Anton Parr). The autoclave was then introduced for 6h in a ventilated oven pre-heated at 180°C. The choice of HTC conditions ensured total HTC conversion (Braghiroli et al., 2014).

After HTC and drying at 105°C, the samples were labelled HTAW, where “H” means HTC, and they were pyrolysed in the same conditions as for the first series. The resultant samples were then labelled CHTAW, where C, H, T, A and W have the same meaning as before.

One of the carbon samples, CHTA2/2, was chosen for physical activation with CO₂ in order to further develop its textural properties. CO₂ activation was carried out in a horizontal tubular furnace. 1g of CHTA2/2 was placed in a quartz boat and transferred into a quartz tube

flushed with high-purity nitrogen at a flow rate 100 mL/min, then heated at 5°C/min up to 900°C. Once the final temperature was reached, N₂ was replaced by CO₂ at a flow rate of 60 mL/min during 1, 2 or 3h. Next, the furnace was allowed to cool under nitrogen flowing at 100 mL/min. ACs were labelled act_CHTA2/2, where “t” stands for the activation time (h), from 1 to 3h, i.e., ac1_CHTA2/2, ac2_CHTA2/2, ac3_CHTA2/2, respectively.

Carbon yield: Y_C , total carbon yield: $Y_{T,C}$, HTC yield: Y_H , HTC total yield: $Y_{T,H}$, carbon yield after HTC: $Y_{C,H}$, and total carbon yield after HTC: $Y_{T,CH}$, were calculated according to equations SI1, SI2, SI3, SI4, SI5, and SI6, respectively, in the supplementary information (SI).

The activation yield, Y_{ac} (%), on dry basis, was calculated as:

$$Y_{ac} (\%) = \left(\frac{act_CHTA2/2(g)}{CHTA2/2(g)} \right)_{db} \times 100 \quad \text{Equation 1}$$

and the total yield of the process after HTC, pyrolysis and activation, Y_{T,act_CH} (%), as:

$$Y_{T,act_CH} (\%) = \frac{Y_{ac} (\%) \times Y_{T,CH} (\%)}{100} = \left(\frac{act_CHTA2/2(g)}{TA2/2(g)} \right)_{db} \times 100 \quad \text{Equation 2}$$

The total yield, Y_T , is thus either Y_H , $Y_{T,C}$, $Y_{T,CH}$ or Y_{T,act_CH} for the series HTAW, CTAW, CHTAW or act_CHTA2/2, respectively, depending on the process considered.

Theoretical yields of processes such as HTC (H), direct pyrolysis (C) or HTC + pyrolysis (CH), for $W = 1/3$, $2/2$ or $3/1$, were calculated by a linear expression taking into account the experimental yields of pure T or pure A submitted to the process considered, and the value of W . For instance, for a TA mixture at $W = 1/3$ submitted to direct pyrolysis, one gets:

$$Y_{C,th}(1/3) = \frac{Y_{C,exp}(T) + Y_{C,exp}(A) \times 3}{4} \quad \text{Equation 3}$$

where the subscripts “exp” and “th” stand for experimental and theoretical, respectively.

2.3 Materials characterisation

Carbon, hydrogen, oxygen, nitrogen and sulphur contents were directly determined using a CHONS elemental analyser (vario EL Cube, Elementar, Germany).

The pH at which the net charge of the surface is zero, named pH_{PZC} (point of zero charge), is affected by the nature and the amount of functional groups existing at the surface of activated carbons. The pH_{PZC} was determined by following the pH drift method (Khan and Sarwar, 2007). 11 aqueous solutions of 0.01 mol/L NaNO_3 were prepared, having pH adjusted to values ranging from 2 and 12 by steps of one pH unit by using either 0.5 mol/L NaOH or 0.5 mol/L HCl. 0.5 g of carbon was added to 25 mL of each solution and left for a 48 h equilibration. The final pH was measured and plotted against the initial pH. The pH at which the curve crossed the $\text{pH}_{\text{initial}} = \text{pH}_{\text{final}}$ line was taken as the pH_{PZC} . The initial pH of the carbons was also determined. For that purpose, 0.1g of carbon was placed in 10 mL of distilled water and equilibrated during 24 hours. Then, the pH of the suspension was measured at room temperature using a pH-meter (Denisa et al., 2009).

The amount of proton-binding groups was also measured, and the total surface charge Q (mmol/L) was calculated. From these quantities, the numbers of groups having pK_a values in selected ranges could be calculated (Jagiello et al., 1995). For that purpose, 0.1g of activated carbon was suspended in 50 mL of NaNO_3 solution (0.01 mol/L) as the supporting electrolyte and was stirred overnight to equilibrate. The suspension was then titrated with NaOH (0.1 mol/L) under N_2 saturation (Jagiello, 1994) using an automatic titrator (905 Titrando, Metrohm commanded with tiamo[®] software V2.2).

The infrared spectra of the hydrochars were obtained by using a Fourier-Transform Infrared (FTIR) spectrometer (Perkin-Elmer Frontier equipped with Perkin-Elmer Spotlight 400 FTIR Microscope) in the wavenumber range 4000-600 cm^{-1} . The experiments were done on powdered samples, without pelletizing.

Secondary electrons were used for observing the topographic contrast of samples using scanning electron microscopy (FET Quanta 600 FEG) under an accelerating voltage of 3 kV. Textural properties of samples were determined from nitrogen adsorption-desorption isotherms at -196°C and CO₂ adsorption at 0°C, using a Micromeritics ASAP 2020 and a Micromeritics ASAP 2420, respectively. The BET (Brunauer-Emmet-Teller) method was used to determine the specific surface area S_{BET} (m²/g) (Brunauer et al., 1938). Particular attention was paid to the C parameter in the BET equation that provides information about the interaction of the adsorbent surface and the adsorbate, and which has to be positive. S_{BET} strongly depends on the range of relative pressures (P/P_0) chosen to fit the BET equation to the nitrogen isotherm, and therefore it cannot be automatically applied between 0.05 and 0.25. We thus plotted $V_{N_2} \times (1 - P/P_0)$, where V_{N_2} is the adsorbed nitrogen volume at a given value of P/P_0 , as a function of P/P_0 and starting at $P/P_0 = 0.01$. The maximum P/P_0 to fit the BET equation will be that where $V_{N_2} \times (1 - P/P_0)$ reaches its maximum. The micropore volume, V_{DR,N_2} (cm³/g), was determined using Dubinin-Raduskevich method (Dubinin, 1989). The total pore volume accessible by adsorption, $V_{0.97}$ (cm³/g), was measured at a relative nitrogen pressure of 0.97. The mesopore volume, V_{mes} (cm³/g), was assumed to be the difference $V_{0.97} - V_{DR,N_2}$. All the data were treated using the MicroActive software from Micromeritics®. Finally, the pore size distribution (PSD) was determined by application of the non-local density functional theory (NLDFT), combining both N₂ and CO₂ adsorption isotherms using the SAIEUS® Software provided by Micromeritics (Jagiello et al., 2015). The PSD was then used to calculate the surface area, S_{NLDFT} , and the micropore volume, $V_{micNLDFT}$. The average pore diameter, $d_{p,av}$, was calculated as:

$$d_{p,av}(nm) = 4 \times \frac{V_{0.97}}{S_{BET}} \times 10^{-6} \quad \text{Equation 4}$$

Mesoporosity (down to 3nm) and macroporosity were assessed by mercury porosimetry using a Micromeritics Autopore IV. The experiments were performed at low pressure (0.001-

0.24 MPa) first, then at high pressure (0.24-414 MPa). The Washburn theory (Washburn, 1921) was used to determine the pore size from the pressure through Equation 5:

$$d = - \frac{4 \sigma_{Hg} \cos \theta}{P} \quad \text{Equation 5}$$

where d is the pore diameter, P is the pressure (MPa), σ_{Hg} is the surface tension of mercury (485 mJ/m² at 20°C), and θ is the contact angle (130°).

2.4 Tetracycline (TC) adsorption

The study of TC adsorption was carried out with one AC, taking into account the total surface area S_{Tot} , introduced elsewhere (Fierro et al., 2010a) and calculated according to:

$$S_{Tot} = S_{BET}(\text{m}^2/\text{g}) \times Y_T(\text{wt. \%}) \quad \text{Equation 6}$$

TC adsorption isotherms were performed in batch experiments as follows: 0.05g of AC adsorbent, with a rod-like form and grain size not exceeding 1 mm, was added to 100 mL of TC solution with the desired TC concentration (0.5-400 mg/L). The initial pH was adjusted by adding a small amount of diluted NaOH solution (0.1 mol/L) and using a pH meter. The suspensions of AC in TC solution were stirred magnetically. TC adsorption thermodynamics was obtained from experiments carried out at three temperatures: 25, 35 and 50°C, using a thermostatic bath regulated at $\pm 1^\circ\text{C}$. After a given time, a sample of 4 mL was withdrawn, the residual TC concentration was always measurable and determined with a UV-Vis spectrophotometer (Perkin-Elmer Lambda 35) at a wavelength of 358 nm. Once the absorbance was measured, the liquid sample was put back into the flask in order to maintain a constant liquid volume. The amount of adsorbed TC at equilibrium, q_e (mg/g), was calculated by:

$$q_e = \frac{(C_0 - C_e) V}{m}$$

Equation 7

where C_0 and C_e (mg/L) are the initial and equilibrium TC concentrations, respectively. V (L) is the volume of solution and m (g) is the AC mass used. TC adsorption kinetics was fitted with pseudo-first-order (PFO) and pseudo-second-order (PSO) models.

2.4.1 Kinetics models

The Pseudo-First-Order (PFO) model proposed by Lagergren (Lagergren, 1898) is generally used to describe solute adsorption in liquid phase for a small interval of time. The variation of the solute concentration with time reads:

$$\frac{dq_t}{dt} = k_1(q_{e1} - q_t) \quad \text{Equation 8}$$

where t is the time (min), k_1 (min^{-1}) is the rate constant of PFO sorption at equilibrium, and q_{e1} and q_t (mg/g) represent the amounts of TC adsorbed at equilibrium and at time t , respectively.

After integration, the following equation is obtained:

$$q_t = q_{e,1}(1 - \exp(-k_1 \cdot t)) \quad \text{Equation 9}$$

The initial adsorption rate, h_1 (mg/(g.min)), is defined as:

$$h_1 = k_1 q_{e,1} \quad \text{Equation 10}$$

The Pseudo-Second-Order (PSO) model, proposed by Ho and McKay (Ho and McKay, 1999), is used for larger time intervals than in the PFO model. The following equation describes the variation of the solute concentration with time by the PSO model:

$$\frac{dq_t}{dt} = k_2(q_{e2} - q_t)^2 \quad \text{Equation 11}$$

After integration the following expression is obtained:

$$q_t = \frac{q_{e,2}^2 \cdot k_2 \cdot t}{1 + q_{e,2} \cdot k_2 \cdot t} \quad \text{Equation 12}$$

where t , $q_{e,2}$ and q_t have the same meaning as in the previous model, and k_2 is the rate constant of PSO sorption at equilibrium ($\text{g}/(\text{mg} \cdot \text{min})$). Then, the initial adsorption rate, h_2 (mg/(g.min)), can be calculated as follows:

$$h_2 = k_2 q_{e,2}^2 \quad \text{Equation 13}$$

2.4.3 Thermodynamic studies

Free energy (ΔG°), entropy (ΔS°), and enthalpy (ΔH°) were determined using TC adsorption at the three selected temperatures. ΔG° was calculated for each temperature according to:

$$\Delta G^\circ = -RT \ln K_C \quad \text{Equation 14}$$

where R is the gas constant (8.314 J/(mol.K)), T is the absolute temperature (K), and K_C (dimensionless) is the apparent equilibrium constant defined according to:

$$K_C = \frac{C_{ad,e}}{C_e} \quad \text{Equation 15}$$

$C_{ad,e}$ (mg/L) is the concentration of adsorbed TC at equilibrium and C_e is the concentration of TC in the aqueous phase at equilibrium (mg/L), considering the plateau of each isotherm at each pH and temperature. Plotting ΔG° as a function of T , a straight line can be obtained with ΔH° as the intercept and ΔS° as the slope:

$$\Delta G^\circ = \Delta H^\circ - T\Delta S^\circ \quad \text{Equation 16}$$

3. Results and discussion

3.1 Materials characterisation

3.1.1 Yields and elemental composition

Figure 1 shows the Van Krevelen diagrams for biomass precursors, T and A, and for hydrochars (Figure 1a), as well as for carbon materials CTAW, CHTAW and act_CHTA2/2 series (Figure 1b). As Van Krevelen diagrams deal with atomic ratios, we calculated atomic percentages by considering 100 g of material and dividing the weight percentage of each element by its atomic weight. The atomic percentages were then calculated by dividing the number of atoms of a given element by the total number of atoms, considering C, H, N and O. Table SI 1 shows the total yields and elemental compositions of the precursors and of the CTAW, HTAW, CHTAW and act_CHTA2/2 series. The carbon content of A and T was

43.87 wt.% (27.68 at.%) and 55.29 wt.% (34.88 at.%), respectively. Tannin is a polyphenolic oligomer, i.e., is of aromatic nature, and hence both oxygen and hydrogen contents were lower than those of Agave fibres, the latter being mainly composed of cellulose and hemicelluloses with a minor content of lignin (Ben Hamissa et al., 2013).

Figure 1: Van Krevelen diagrams of: (a) Agave, Tannin and HTAW series; and (b) CTAW, CHTAW and act_CHTA2/2 series.

In agreement with these results, Agave had higher H/C and O/C atomic ratios than Tannin. After HTC, the carbon content slightly increased in the HTAW series and varied from 45.58 wt. % (28.75 at.%) to 60.39 wt.% (38.09 at.%), corresponding to HTA0/4 (pure agave) and to HTA4/0 (pure tannin), respectively. A and T had the same nitrogen content, 0.22 wt. % (0.12 at.%), which did not vary appreciably after HTC. Increasing *W* increased the carbon content and decreased both hydrogen and oxygen contents of the resultant hydrochars, leading to a remarkably straight line as seen in Figure 1a.

Figure 1b shows that the H/C and O/C atomic ratios decreased after pyrolysis due to the evolution of volatiles mainly in the form of H₂O, CO₂ and CO (Schaefer et al., 2016). For the same O/C atomic ratio, the H/C ratio was higher for CTAW than for the CHTAW series, probably indicating dehydration reaction during HTC and leading to lower hydrogen contents

1 after pyrolysis. H/C and O/C atomic ratios decreased when increasing *W* for the two series of
2 carbons. The nitrogen content was 0.28 wt. % (0.15 at.%) and 0.52 wt. % (0.28 at.%), on
3 average, for CHTAW and CTAW series, respectively (see Table SI 1). Therefore, when
4 biomass was directly pyrolysed, it maintained a lower content of heteroatoms (78.78 wt. %
5 (49.70 at.%) to 91.04 wt. % (57.43 at.%%)) compared to carbons of the CHTAW series (87.83
6 wt. % (55.41 at.%) – 94.58 wt. % (59.67 at.%%)). CO₂ activation of CHTA2/2 produced a
7 considerable reduction of both H/C and O/C atomic ratios as early as 1h activation time, and
8 higher activation times further decreased those ratios. H/C atomic ratios were between 0.05
9 and 0.04 for ac1_CHTA2/2 and ac3_CHTA2/2, respectively, while O/C atomic ratios were
10 around 0.02.

11 Figure 2a shows the yields to hydrochars (HTAW series), carbons (CTAW and
12 CHTAW series) and activated carbons (act_CHTA2/2 series) from the initial TAW series.
13 The HTC yield of Tannin to hydrochar was lower, 58.2 %, than that of Agave, 63.3 %, but an
14 interesting finding is that mixing A with T and submitting the blend to HTC produced a
15 higher hydrochar yield with respect to the theoretical values calculated from the individual
16 hydrochar yields of A and T. Figure 2a indeed shows that the yield to hydrochar did not
17 change linearly when increasing *W*, meaning that the addition of a phenolic molecule to a
18 lignocellulosic material increased the hydrochar yield, in agreement with previous results.
19 Thus, some authors (Braghiroli, 2014; Brun et al., 2013; Ryu et al., 2010) showed that
20 phloroglucinol acts as a crosslinking agent, promoting sugar nucleation mechanism and
21 increasing the final HTC carbon yield by 20%.

Figure 2 : (a) Total yield to hydrochar (HTAW), carbon (CHTAW and CTAW) or activated carbon (act_CHTA2/2); and (b) Experimental (full symbols) and theoretical (empty symbols) carbon yield: CTAW and CHTAW as a function of W .

The highest difference was found when HTA2/2 was submitted to HTC. The theoretical yield was 60.78 % whereas the experimental value was 67.29 %. This difference was maintained after pyrolysis. The yield to CTAW series varied from 21.43 to 46.77 % and was higher than that of CHTAW series, which ranged from 10.30 to 28.82 %. In both series, the yield increased with W due to the higher carbon yield of tannin. We could observe that there was no linear increase of yield with W for the CHTAW series, unlike what was seen for the HTAW series. In order to better show this effect, Figure 2b presents the theoretical and experimental carbon yields for both CTAW and CHTAW series. For direct pyrolysis, the experimental and theoretical yields were equal, but important differences were observed when materials were submitted together to HTC beforehand, especially at $W = 2/2$.

3.1.2 Textural properties

Figure 3 shows the adsorption-desorption isotherms of N_2 at -196°C for series CTAW, CHTAW and act_CHTA2/2. The CO_2 adsorption isotherms for the same materials are given as supplementary information (Figure SI 1).

All materials presented a steep increase in the N₂ volume adsorbed at very low relative pressure ($P/P_0 < 0.01$), indicating the existence of narrow micropores (Szczurek et al., 2011). According to the IUPAC classification, the CTAW samples exhibit N₂ adsorption isotherms of type Ia (Thommes et al., 2015), characteristic of microporous materials with narrow micropores. A nearly horizontal plateau, above $P/P_0 = 0.1$, was observed together with the presence of mesopores, indicated by the small hysteresis loop closing at $P/P_0 = 0.2$. Increasing the amount of Tannin, i.e., increasing W from 0 at 4, produced a higher micropore volume, from 0.12 cm³/g to 0.21 cm³/g, and a higher S_{BET} from 321 m²/g to 546 m²/g (see Table SI 2), indicating the development of the porosity. This result was confirmed by the isotherms of CO₂ of Figure SI 1, and the corresponding pore texture parameters are gathered in Table SI 2.

CHTAW and act_CHTA2/2 exhibited N₂ adsorption isotherms of type Ib (Thommes et al., 2015), characteristic of developed pore texture with a wider supermicroporosity than before and the existence of pores between 0.7 and 2 nm wherein cooperative filling is possible. For the CHTAW series, we observed an increase of the amount of adsorbed nitrogen in the micropores, from 0.15 to 0.26 cm³/g, and an increase of S_{BET} from 406 to 683 m²/g, with the addition of Tannin at a weight ratio $W = 1/3$. A further increase of W reduced the mesopore volume, but the micropore volume and S_{BET} remained essentially unchanged. Comparing the pore texture parameters of CTAW and CHTAW (Figure 3a and Figure 3c), we can conclude that a preliminary hydrothermal step allowed an enhanced development of the microporosity during pyrolysis, which produced higher surface areas. The PSD calculated by the NLDFT model were not very different for CTAW and CHTAW series, since the micropore volume generally controls the value of S_{BET} .

The sample CHTA2/2, having the highest yield increase when compared to the theoretical one, was chosen to further develop its textural properties by CO₂ activation. Figure

3e shows the N₂ adsorption-desorption isotherms of CHTA2/2 after activation at 1, 2 and 3 hours, compared to those of the non-activated sample. The micropore volume increased with the activation time from 0.25 to 0.48 cm³/g, and the shoulder of the isotherm widened, showing an increase of the amount of wider micropores. At $P/P_0 > 0.1$, a plateau was not reached and the slope of the curve increased with the activation time, suggesting a progressive development of the porosity as shown by the PSDs in Figure 3f. The micropore volume, V_{DR,N_2} determined by DR method applied to N₂ isotherm, was lower than the one determined by CO₂ isotherm, V_{DR,CO_2} : 0.25 and 0.29 cm³/g, respectively, for CHTA2/2. The difference between V_{DR,N_2} and V_{DR,CO_2} increased for act1_CHTA2/2, meaning that CHTA2/2 had an important fraction of narrow microporosity, i.e., inaccessible to N₂ at -196°C, and the material obtained after 1h activation developed a microporosity even narrower (Braghiroli et al., 2017). After 2h activation, V_{DR,N_2} was higher than V_{DR,CO_2} , meaning a widening of the microporosity. All the carbon materials prepared, activated or not, had S_{NLDFT} higher than S_{BET} , indicating the existence of narrow pores wherein only a monolayer of nitrogen between two pore walls can be adsorbed (Braghiroli et al., 2017). Increasing the activation time from 1 to 3 hours made the specific surface area S_{BET} increase from 621 to 1250 m²/g, and so did the surface area determined by the NLDFT method, S_{NLDFT} , which varied from 934 to 1431 m²/g (Table SI 2). The PSDs of the non-activated sample, CHTA2/2, and of the series act_CHTA2/2, obtained by application of the NLDFT model to both N₂ and CO₂ isotherms, are shown in Figure 3f.

Figure 3: (a, c, e) N_2 adsorption-desorption isotherms at -196°C ; and (b, d, f) corresponding PSDs.

Figure 4a and 4b show the changes of $V_{0.97}$ and S_{BET} as a function of the total yield of the process for synthesising the considered materials, Y_T . First, we can observe that $V_{0.97}$ and S_{BET} followed similar trends due to the fact that most of the pore volume in all the materials was mainly constituted of micropores (< 2 nm), and the value of S_{BET} is essentially due to microporosity.

Figure 4: Correlation between total yields, Y_T , and: (a) total pore volume, $V_{0.97}$; (b) specific surface area, S_{BET} ; (c) % of micropore volume from NLDFT, $\Phi_{mic,NLDFT}$ (%); and (d) average pore diameter of CTAW, CHTAW and act_CHTA2/2 series.

Figure 4c shows the percentage of microporosity calculated by the NLDFT model, $\Phi_{mic,NLDFT} (\%) = V_{mic,NLDFT} / V_{0.97}$. The highest $\Phi_{mic,NLDFT}$ was found for materials submitted to direct pyrolysis, especially when Tannin was present in the blend. Agave provided macro- and mesoporosity to all materials, as confirmed by SEM observations (see below), but all materials were essentially microporous, with $\Phi_{mic,NLDFT}$ higher than 75%. This fact can be also observed in Figure 4d when representing the average pore diameter, $d_{p,av}$, as a function of Y_T . As a general trend, $d_{p,av}$ decreased when Y_T increased, but ACs produced from CHTA2/2 had similar values of $d_{p,av}$ as those of some materials of the CHTAW series. However, these ACs had much higher surface areas due to activation. Therefore, the appropriate selection of the

synthesis conditions allowed obtaining activated carbons with high surface area but with similar carbon yields and average pore diameters as those of non-activated, low-surface area, carbon materials.

Figure 5a shows mercury intrusion curves for the act_CHTA2/2 series. At low pressure (0.003 MPa) the mercury surrounds particles but does not enter the pores, whereas it penetrates into all pores wider than 3 nm when increasing progressively the pressure up to 400 MPa.

Figure 5: (a) Cumulative intrusion/extrusion of mercury; and (b) corresponding pore size distributions of the act_CHTA2/2 series.

The total volume penetrated by mercury increased from 3.69 to 5.55 cm³/g when the activation time increased from 1 to 3 hours (see Table SI 3). Figure 5b shows the PSDs calculated by applying Washburn's equation (Equation 5) to the data of Figure 5a. The PSDs become broader when increasing the activation time, although only little difference was noticed between ac2_CHTA2/2 and ac3_CHTA2/2.

Figure 6 shows the results of the potentiometric titration for the hydrochar HTA2/2, and its pyrolysed and activated derivatives: CHTA2/2 and act_CHTA2/2 series, respectively. Pyrolysis after HTC decreased the density of functional groups from 8.15 to 1.16 mmol/g (see

Table 1), in good agreement with the decrease of O and H contents observed by elemental analysis. The nature of the functional groups also changed. The increase of the activation time progressively increased the amount of functional groups: 0.43, 0.89 and 4.92 mmol/g for ac1_CHTA2/2, ac2_CHTA2/2 and ac3_CHTA2/2, respectively. The number of peaks, representing different types of functional groups, were 3 and 4 for ac1_CHTA2/2 and ac3_CHTA2/2, respectively, and the most acidic sites ($3 < pK_a < 5$) progressively vanished when the activation time increased. However, the AC prepared with 2h activation time, ac2_CHTA2/2, still presented 5 types of functional groups, with 2 acidic ones centred at $pK_a = 3.97$ and 5.24. Upon increasing the activation time to 3h, the groups at $pK_a = 3.97$ disappeared. The pK_a distributions showed the predominance of strongly basic species such as lactol- or hydroxyl-containing functional groups with $pK_a > 8$ (Seredych et al., 2016). The basicity of ACs was confirmed by the high value of $pH_{initial}$ and pH_{PZC} , around 10 (Table 1).

Figure 6: Density of functional groups as a function of pK_a , for carbonaceous materials derived from TA2/2 sample: a) after HTC on one hand, and after HTC followed by carbonisation on the other hand; b) after activation of the CHTA 2/2 sample.

Table 1: Results of pH_{PZC} , $pH_{initial}$ and potentiometric titration measurements: peak position and numbers of groups (in parentheses: (mmol/g)).

Samples	$pH_{initial}$	pK_a 3-5	pK_a 5-7	pK_a 7-8	pK_a 8-10	pK_a 10-12	All	pH_{PZC}
HTA2/2	n.d.	4.92 (0.298)	-	7.32 (0.536)	-	10.02 (7.313)	8.15	n.d.
CHTA2/2	n.d.	-	5.04 (0.030)	-	9.72 (0.315)	11.19 (0.810)	1.16	n.d.
ac1_CHTA2/2	10.6	4.96 (0.036)	-	7.38 (0.091)	9.76 (0.302)	-	0.43	n.d.
ac2_CHCTA2/2	9.7	3.97 (0.031)	5.24 (0.078)	7.79 (0.085)	9.10 (0.212)	10.93 (0.480)	0.89	9.31
ac3_CHCTA2/2	10.7	-	5.23 (0.146)	7.54 (0.309)	8.98 (0.468)	11.21 (3.997)	4.92	n.d.

n.d. non determined because not relevant for the objectives of this study

3.1.3 Scanning Electron microscopy (SEM) studies

Figure 7 shows SEM images of the material CHTA2/2 at different magnifications. The morphology of the sample did not change with activation time, see Figure SI 2 for images of ac2_CHTA2/2 and ac3_CHTA2/2. The initial structure of agave was preserved, giving rise to tubular carbon pores where carbon microspheres, probably produced by HTC of tannin and/or dissolved (poly)saccharides (Braghiroli et al., 2015; Sanchez-Sanchez et al., 2016) were attached.

Figure 7: SEM images obtained with secondary electrons of CHTA2/2 at different magnifications: (a) 1000 ×; and (b) 5000 ×.

1 In order to get more insight into these materials, the five produced hydrochars were
2 investigated by FTIR. Figure 8a shows the spectra of HTA4/0 (pure tannin submitted to HTC)
3 at the top and that of HTA0/4 (pure agave submitted to HTC) at the bottom. In between are
4 the spectra of the three hydrochars produced from T and A at different values of W . All the
5 samples showed a broad band centred on around 3300 cm^{-1} and attributed to hydroxyl groups
6 (Mahmoudi et al., 2012). The diminution of intensity of the band around 2900 cm^{-1} from
7 HTA0/4 to HTA4/0 is due to the diminution of aliphatic C-H stretching functions because
8 HTA0/4 was richer in hydrogen. Contrariwise, the addition of tannin made the band around
9 1500 cm^{-1} become more intense, indicating that tannin tends to enrich the surface in hydroxyl
10 and carboxyl functional groups ($-\text{OH}$, $\text{C}=\text{O}$ and $\text{C}-\text{O}$ stretching). This was confirmed by the
11 results of elemental analysis. Finally, the addition of tannin decreased slightly the stretching
12 C-C vibration corresponding to the series of peaks between 1350 and 850 cm^{-1} . This broad
13 band, becoming wider with W , confirms the enrichment of the surface with C-O groups. Other
14 hydrochars (HTA1/3, HTA2/2 and HTA3/1) had intermediary characteristics.

15 Figure 8b shows a fibre present in hydrochar HTA2/2: it came from agave and a
16 squared area was chosen for studying its chemical composition. Figure 8c shows the resultant
17 chemical mapping wherein the red colour corresponds to the composition of the *Agave*
18 *americana* hydrochar (HTA0/4), and the green colour corresponds to that of the Tannin
19 hydrochar (HTA4/0). 35.2 % of the analysed area was thus ascribed to agave hydrochar
20 whereas 61.9% was attributed to tannin hydrochar. Only a residual 2.9% could not be fitted
21 with these two main components, which was assumed to occur from experimental error or to
22 parallel reactions produced by the combination of tannin and agave during the hydrothermal
23 treatment. The higher amount of tannin hydrochar found here supports the morphological
24 observations. Therefore, we can confirm that when T was submitted to HTC with A, the latter

remained in the form of hydrochar microspheres covering the surface, thus providing microporous volume to the resultant carbon materials.

Figure 8: (a) FTIR spectra of HTAW materials; (b) optical microscopy image of a fibre of HTA2/2; and (c) chemical mapping of the area selected in (b) (■: *agave americana* hydrochar (HTA0/4), ■: *mimosa* tannin hydrochar (HTA4/0), ■: insignificant component).

3.2 Tetracycline adsorption

TC adsorption was investigated in aqueous phase on ac2_CHTA2/2, since this AC had the highest S_{Tot} : 152 m²/g. This AC had a S_{BET} of 1068 m²/g and a S_{NLDFT} of 1292 m²/g. Figure 9 shows the effect of pH and temperature on the TC adsorption capacity, q_e , onto ac2_CHTA2/2. pH slightly influenced the adsorption capacity at 35 and 50°C, but had a significant influence at 25°C. The pH_{PZC} of this AC was 9.3, consequently the adsorbent surface was negatively charged (attracting cations) at pH 10, and positively charged (attracting anions) at pH 4.5 or 7. According to Zhang et al. (Zhang et al., 2015), TC molecule can be charged either positively (pH < 3.32), neutrally (3.3 < pH < 7.8), or negatively (pH > 7.8), due to the existence of three functional groups. At pH 10, the AC surface and TC were both negatively charged, so electrostatic repulsion between them probably caused the decrease of the amount of adsorbed TC at 25°C. At pH 4.5 or 7, the AC surface was positively charged while the TC molecule was neutral. TC adsorption capacities clearly increased with temperature from 25 to 50°C, and this fact was confirmed at the 3 pH tested, especially when increasing the basicity. This experimental observation might appear against the thermodynamic principles because adsorption usually decreases when the temperature increases. However, adsorption in aqueous solution is a much more complex process than in the gas phase. ΔG° depends on ΔH° and ΔS° , which were both positives as can be seen in Table 2. Positive values of ΔH° and ΔS° have also been reported by other authors for TC adsorption (Acosta et al., 2016; Erşan et al., 2013), using different adsorbents and initial concentrations. ΔH° should be negative for an adsorption process but TC adsorption on ac2_CHCTA2/2 might include an endothermic process (break of hydrogen bonds) and an exothermic process (adsorption), the former predominating over the latter. Increasing the adsorption temperature weakens the hydrogen bonds formed between water molecules on one hand, and between water molecules and solute or adsorbent on the other hand and also

enhances the diffusion into the pores. This was already observed by other authors (Fontecha-Cámara et al., 2006) who pointed out that the formation of hydrogen bonds between solute and solvent, favored at low temperatures, can modify the shape and size of solute molecules so that they can no more access the micropores of the adsorbent. Thus, temperature increase may possibly weaken the hydrogen bonds and favor solute uptake on the adsorbent. ΔS° was also positive, which suggests higher randomness at the adsorbate-solution interface when compared to the concentrated liquid phase.

Figure 9: Effect of pH and temperature on the adsorption of TC on ac2_CHTA2/2 at equilibrium ($C_0 = 10$ mg/L, $m = 0.05$ g, $V = 100$ mL).

Table 2: Thermodynamic parameters for the adsorption of TC onto ac2_CHTA2/2 activated carbon at different temperatures (initial TC concentration of 10 mg/L).

Sample	pH	ΔH° (kJ/mol)	ΔS° (J/mol/K)	ΔG° (kJ/mol)		
				25°C	35°C	50°C
ac2_CHTA2/2	4	12.7	56.5	-4.2	-4.7	-5.6
	7	22.3	87.8	-3.8	-5.1	-6.0
	10	37.7	135.1	-2.0	-5.0	-5.5

3.3 Kinetic studies

Figure 10a shows the adsorption of TC onto ac2_CHTA2/2 and F300 as a function time at 25°C and at pH 4. The F300 commercial activated carbon was used for the sake of comparison, and its characterisation was detailed elsewhere (Selmi et al., 2017). In brief, F300 has the following pore texture parameters: $S_{BET} = 884 \text{ m}^2/\text{g}$, $S_{NLDFT} = 1003 \text{ m}^2/\text{g}$, $V_{mic,NLDFT} = 0.34 \text{ cm}^3/\text{g}$. The maximum adsorption was obtained after 4h for ac2_CHTA2/2 and after 7h for F300. The latter presented a lower TC adsorption capacity because of its lower S_{BET} , and the time needed for equilibrium was also higher because F300 has essentially a narrow microporosity whereas ac2_CHTA2/2 has supermicropores and some mesoporosity. Figure 10b shows the adsorption of TC at different initial concentrations onto ac2_CHTA2/2 as a function time. When the concentration increased, the sorption rate of TC increased, as well as the amount adsorbed at equilibrium. The increase of TC concentration from 0.5 to 100 mg/L also increased the time needed to reach equilibrium, from 25 to 200 min; this might be due to diffusional resistance, given the fact that TC molecule size is similar to the ac2_CHTA2/2 micropore size (Rivera-Utrilla et al., 2013).

Table SI 4 and Table SI 5 show the parameters derived from the nonlinear fits of kinetic models to the experimental data, as well as the calculated and experimental equilibrium sorption capacities, rate constants (k_1 and k_2), error (χ^2), determination coefficient (R^2), and the initial adsorption rates (h_1 and h_2). Table SI 4 presents the corresponding experimental adsorption capacities at equilibrium: 51.35 and 28.58 mg/g for ac2_CTA2/2 and F300, respectively. Generally, q_e calculated by PSO was always closer to the experiment than the value obtained from the PFO model. Moreover, determination coefficients obtained by PSO were always higher than those obtained by PFO model, in agreement with previous results on the adsorption of methylene blue onto *Agave americana* fibres (Ben Hamissa et al., 2013). In addition, the values of h_2 were 2.48 and 0.15 mg/(g.min) for ac2_CHTA2/2 and F300,

respectively, demonstrating that TC adsorption onto ac2_CHTA2/2 was much faster than onto F300.

Figure 10: Nonlinear fit to the kinetics of TC adsorption onto: (a) ac2_CHTA2/2 and F300 with PFO and PSO models at pH 4, 25°C and $C_0 = 100$ mg/L; and (b) onto ac2_CHTA2/2 only with PSO model at different initial concentrations for pH 7 at 25°C.

Table SI 5 shows that the determination coefficients, R^2 , for the PFO kinetic models obtained for all studied initial concentrations were sometimes not that high. The best fit was obtained with the PSO kinetic model for all initial concentrations used. Similar results were obtained for the adsorption of Congo red dye onto an activated carbon derived from coir pith (Namasivayam and Kavitha, 2002). The initial adsorption rates increased with TC initial concentration.

3.4 isotherm studies

Figure 11 shows TC adsorption isotherms onto ac2_CHTA2/2. TC adsorption capacity increased with C_0 . Because of their simplicity, Langmuir (Langmuir, 1918) and Freundlich (Freundlich, 1906) models were applied to analyse the experimental data. The parameters of each model, calculated by regression from non-linear forms of Langmuir and Freundlich

isotherms are summarised in Table SI 6. Langmuir model led to the best fit, with determination coefficients between 0.968 and 0.995. Moreover, the monolayer saturation capacity, q_{max} , was relatively close to q_{exp} . As for Freundlich isotherm, the values of R^2 (between 0.773 and 0.943) were much lower with respect to those of the Langmuir model. The values of Freundlich exponent, n , were found to be higher than 1, indicating that TC adsorption onto ac2_CHTA2/2 is favourable.

Figure 11: Adsorption isotherms of TC onto ac2_CHTA2/2, showing the effects of pH and temperature: (a) fit with Langmuir model, and (b) fit with Freundlich model.

In order to have an idea about the efficiency of the tested adsorbents materials for the removal of TC, a comparison was made with other adsorbents reported in the literature as summarised in Table 3. Such comparison was based on the adsorption capacity q_e (mg/g). As can be observed, the ac2_CHTA2/2 material has adsorption capacities in the range of those presented by other materials of similar S_{BET} . The adsorption capacities obtained by Ncibi and Mika (Ncibi and Mika, 2015) were clearly higher, but their materials were carbon nanotubes and, probably, a very narrow microporosity existed inside and between the nanotubes walls not accessible to nitrogen, and/or was underestimated by the BET equation. On the contrary, it is not physically possible to have ACs with areas higher than 2630 m²/g (Fierro et al., 2010b;

Schlapbach and Zuttel, 2001), whereas Zhang et al. (Zhang et al., 2015) reported a surface area of 2900 m²/g.

Table 3: TC removal onto different adsorbents.

S_{BET} (m ² /g)	C_0 (mg/L)	Adsorbent (g/L)	T (°C)	pH	pH_{PZC}	q_e (mg/g)	Reference
56	n.a	n.a	n.a	n.a	n.a	24	(Lian et al., 2013)
61	100	1			7.2	24	
484	300	0.5	25	6.5-7.5	7.8	265	(Acosta et al., 2016)
700	300	0.5			10.7	316.6	
67	80	1	25	7.0	n.a	23.3	(Liao et al., 2013)
158						391	
382	100	0.1	25	7.0	n.a	507	(Ncibi and Mika, 2015)
576						554	
680	100	0.06	Room	7.0	n.a	303.3	(Vu et al., 2010)
1008	450	0.4	25	2.0	n.a	339	(Huang et al., 2013)
1455	400	1	35	5.7	5.86	202	(Güzel and Hasan, 2016)
1463	660	1	25	5.0	n.a	535	(Sun et al., 2013)
2806	100	0.1	25	3.68	n.a	897.6	(Zhang et al., 2015)
>1220	700	1	25	7	7.7	471.1	(Rivera-Utrilla et al., 2013)
1068	400	0.5	25	7.0	9.3	239.4	This study
884	100	1	25	4.5	8.0	28.6	

n.a. (non available)

4. Conclusion

Agave americana fibres (A) and *mimosa* Tannin (T) were used as precursors of activated carbons (ACs). Two carbon series were prepared at several T/A weight ratios (W) (i.e., 0/4; 1/3; 2/2; 3/1 and 4/0). The first series, CTAW, was directly pyrolysed at 900°C and the second one, CHTAW, was made through a hydrothermal carbonisation (HTC) step prior to pyrolysis. These two carbon series were completely different, in terms of both porous texture and chemical composition. Thus, the CTAW series had a less developed pore texture than the CHTAW series. The CHTAW series had higher H/C atomic ratios indicating a lower aromatisation. Submitting a blend of T and A to HTC produced an increase of carbon yield, the highest one being obtained for the sample CHTA2/2, i.e., with $W = 2/2$.

1 The CHTA2/2 sample was activated under CO₂ flowing at 900°C for 1, 2 or 3 hours to
2 produce ACs with S_{BET} as high as 1200 m²/g, and with much more chemical groups on their
3 surface. The appropriate selection of the synthesis conditions thus allowed obtaining high-
4 surface area ACs with similar carbon yields and average pore diameters as those of non-
5 activated, low-surface area carbon materials.

6 The one activated for 2 hours, ac2_CHTA2/2, was tested for tetracycline (TC)
7 adsorption and compared to a commercial activated carbon, F300. Adsorption equilibrium
8 was reached much faster, 4h, for ac2_CHTA2/2 than for F300, 7h, due to the presence of
9 macropores and mesopores provided by Agave giving access to an important microporosity.
10 TC adsorption was spontaneous onto ac2_CHTA2/2, and the corresponding adsorption
11 kinetics was adequately fitted by a pseudo-second-order model. TC adsorption essentially
12 depends on surface area, and the results reported herein are in the range of those reported in
13 the open literature.

15 **Acknowledgements**

16 The authors from Sousse University gratefully acknowledge the financial support from
17 the Tunisian Ministry of Higher Education and Scientific Research, and the EU-METALIC
18 Erasmus Mundus project.

References

- Acosta, R., Fierro, V., Martinez de Yuso, A., Nabarlantz, D., Celzard, A., 2016. Tetracycline adsorption onto activated carbons produced by KOH activation of tyre pyrolysis char. *Chemosphere* 149, 168-176.
- Altenor, S., Ncibi, M.C., Emmanuel, E., Gaspard, S., 2012. Textural characteristics, physiochemical properties and adsorption efficiencies of Caribbean alga *Turbinaria turbinata* and its derived carbonaceous materials for water treatment application. *Biochem Eng J* 67, 35-44.
- Ben Hamissa, A.M., Brouers, F., Borhane, M., Seffen, M., 2007. Adsorption of Textile Dyes Using *Agave Americana* (L.) Fibres: Equilibrium and Kinetics Modelling. *Adsor Sci Technol* 25, 311-325.
- Ben Hamissa, A.M., Brouers, F., Ncibi, M.C., Seffen, M., 2013. Kinetic Modeling Study on Methylene Blue Sorption onto *Agave americana* fibers: Fractal Kinetics and Regeneration Studies. *Sep Sci Technol* 48, 2834-2842.
- Bergius, F., 1915. *Zeitschrift für Komprimierte und Flüssige Gase*. 17.
- Braghiroli, F.L., 2014. Polyphénols végétaux traités par voie humide: synthèse de carbones biosourcés hautement poreux et applications, Département N2EV – Equipe 402. Université de Lorraine, pp. 27-32.
- Braghiroli, F.L., Fierro, V., Izquierdo, M.T., Parmentier, J., Pizzi, A., Celzard, A., 2012. Nitrogen-doped carbon materials produced from hydrothermally treated tannin. *Carbon* 50, 5411-5420.
- Braghiroli, F.L., Fierro, V., Izquierdo, M.T., Parmentier, J., Pizzi, A., Celzard, A., 2014. Kinetics of the hydrothermal treatment of tannin for producing carbonaceous microspheres. *Bioresource Technol.* 151, 271–277.

1 Braghiroli, F.L., Fierro, V., Parmentier, J., Vidal, L., Gadonneix, P., Celzard, A., 2015.
2 Hydrothermal carbons produced from tannin by modification of the reaction medium:
3 Addition of H⁺ and Ag⁺. *Ind Crops Prod* 77, 364-374.

4 Braghiroli, F.L., Fierro, V., Szczurek, A., Gadonneix, P., Ghanbaja, J., Parmentier, J.,
5 Medjahdi, G., Celzard, A., 2017. Hydrothermal Treatment of Tannin: A Route to
6 Porous Metal Oxides and Metal/Carbon Hybrid Materials. *inorganics* 19, 7.

7 Brun, N., Edembe, L., Gounel, S., Mano, N., Titirici, M.M., 2013. Emulsion-Templated
8 Macroporous Carbons Synthesized By Hydrothermal Carbonization and their
9 Application for the Enzymatic Oxidation of Glucose. *ChemSusChem* 6, 701-710.

10 Brunauer, S., Emmet, P.H., Teller, E., 1938. Adsorption of gases in multimolecular layers. *J*
11 *American Chem Society*, 309–319.

12 Choi, Y.-K., Cho, M.-H., Kim, J.-S., 2016. Air gasification of dried sewage sludge in a two-
13 stage gasifier. Part 4: Application of additives including Ni-impregnated activated
14 carbon for the production of a tar-free and H₂-rich producer gas with a low NH₃
15 content. *Internat J Hydr Energ* 41, 1460-1467.

16 Denisa, H.-J., Mykola, S., Gao, G.L., Teresa, J.B., 2009. Combined Effect of Nitrogen- and
17 Oxygen-Containing functional Group of Microporous Activated Carbon on its
18 Electrochemical Performance in Supercapacitors. *Adv Funct Mater* 9, 438-447.

19 Dirany, I., Sirés, I., Oturan, N., Ozcan, A., Oturan, M., 2012. Electrochemical treatment of the
20 antibiotic sulfachloropyridazine: kinetics, reaction pathways, and toxicity evolution.
21 *Environ Sci Technol*, 4074-4082.

22 Dubinin, M.M., 1989. Fundamentals Of The Theory Of Adsorption In Micropores Of Carbon
23 Adsorbents: Characteristics Of Their Adsorption Properties And Microporous
24 Structures. *Carbon* 27, 457-567.

1 Erşan, M., Bağda, E., Bağda, E., 2013. Investigation of kinetic and thermodynamic
2 characteristics of removal of tetracycline with sponge like, tannin based cryogels.
3 Colloids and Surfaces B: Biointerfaces 104, 75-82.

4 Fierro, V., Muñiz, G., Basta, A.H., El-Saied, H., Celzard, A., 2010a. Rice straw as precursor
5 of activated carbons: Activation with ortho-phosphoric acid. J Hazard Mater 181, 27-34.

6 Fierro, V., Szczurek, A., Zlotea, C., Marêché, J.F., Izquierdo, M.T., Albinia, A., Latroche,
7 M., Furdin, G., Celzard, A., 2010b. Experimental evidence of an upper limit for
8 hydrogen storage at 77K on activated carbons. Carbon 48, 1902-1911.

9 Fierro, V., Torné-Fernández, V., Celzard, A., Montané, D., 2007. Influence of the
10 demineralisation on the chemical activation of Kraft lignin with orthophosphoric acid. J
11 Hazard Mater 149, 126-133.

12 Fontecha-Cámara, M.A., López-Ramón, M.V., Álvarez-Merino, M.A., Moreno-Castilla, C.,
13 2006. About the endothermic nature of the adsorption of the herbicide diuron from
14 aqueous solutions on activated carbon fiber. Carbon 44, 2335-2338.

15 Freundlich, H., 1906. Over the adsorption in solution. J Phys Chem 57, 385-471.

16 Ghouma, I., Mejdi, J., Sophie, D., Lionel, L., Camelia, M.G., Abdelmottaleb, O., 2015.
17 Activated carbon prepared by physical activation of olive stones for the removal of NO₂
18 at ambient temperature. Compt Rend Chim 18, 63–74.

19 Güzel, F., Hasan, S., 2016. Adsorptive efficacy analysis of novel carbonaceous sorbent
20 derived from grape industrial processing waste towards tetracycline in aqueous
21 solution. J Taiwan Inst Chem Eng 4, 236-240.

22 Ho, Y.S., McKay, G., 1999. Pseudo-second order model for sorption processes. Process
23 Biochem 34, 451-465.

- 1 Huang, L., Shi, C., Zhang, B., Niu, S., Gao, B., 2013. Characterization of Activated Carbon
2 Fiber by Microwave Heating and the Adsorption of Tetracycline Antibiotics. *Sep Sci*
3 *Technol* 48, 1356-1363.
- 4 Jagiello, J., 1994. Stable Numerical Solution of the Adsorption Integral Equation Using
5 Splines. *Langmuir* 10, 2778-2785.
- 6 Jagiello, J., Ania, C., Parra, J.B., Cook, C., 2015. Dual gas analysis of microporous carbons
7 using 2D-NLDFT heterogeneous surface model and combined adsorption data of N₂
8 and CO₂. *Carbon* 91, 330-337.
- 9 Jagiello, J., Bandosz, T.J., Putyera, K., Schwarz, J.A., 1995. Determination of proton affinity
10 distributions for chemical systems in aqueous environments using a stable numerical
11 solution of the adsorption integral equation *J Colloid Interface Sci* 172, 341-346.
- 12 Khan, M.N., Sarwar, A., 2007. Determination of Points of Zero Charge of Natural and
13 Treated Adsorbents. *Surf Rev Lett* 14, 461-469.
- 14 Kovalova, L., Siegrist, H., Singer, H., Wittmer, A., McArdell, C.S., 2012. Hospital
15 wastewater treatment by membrane bioreactor: performance and efficiency for organic
16 micropollutant elimination. *Environ Sci Technol*, 1536-1545.
- 17 Lagergren, S., 1898. Zur Theorie der Sogenannten Adsorption Gelöster Stoffe, *Kungliga*
18 *Svenska Vetenskapsakademiens Handlingar* 24, 1-39.
- 19 Langmuir, I., 1918. The adsorption of gases on plane surfaces of glass, mica, and platinum. *J*
20 *American Chem Society* 40, 1361.
- 21 Li, Q., Qi, Y., Gao, C., 2015. Chemical regeneration of spent powdered activated carbon used
22 in decolorization of sodium salicylate for the pharmaceutical industry. *J Clean Prod* 86,
23 424-431.

- 1 Lian, F., Song, Z., Liu, Z., Zhu, L., Xing, B., 2013. Mechanistic understanding of tetracycline
2 sorption on waste tire powder and its chars as affected by Cu^{2+} and pH. *Environ Pollu*
3 178, 264-270.
- 4 Liao, P., Zhan, Z., Dai, J., Wu, X., Zhang, W., Wang, K., Yuan, S., 2013. Adsorption of
5 tetracycline and chloramphenicol in aqueous solutions by bamboo charcoal: A batch
6 and fixed-bed column study. *Chem Eng J* 228, 496-505.
- 7 Ling-Ping, X., Zheng-Jun, S., Feng, X., Run-Cang, S., (2012) Hydrothermal carbonization of
8 lignocellulosic biomass. *Bioresource Technol.* 4, 619-623.
- 9 Luca, F., Daniele, B., Daniele, C., Marco, B., 2014. Hydrothermal Carbonization of Biomass:
10 Design of a Batch Reactor and Preliminary Experimental Results. *Chem Eng* 37, 55-60.
- 11 Mahmoudi, K., Hamdi, N., Kriaa, A., Srasra, S., 2012. Adsorption of Methyl Orange Using
12 Activated Carbon Prepared from Lignin by ZnCl_2 Treatment. *Russian J Phys Chem A*
13 86, 1294–1300.
- 14 Molina-Sabio, M., Rodríguez-Reinoso, F., 2004. Role of chemical activation in the
15 development of carbon porosity. *Colloid Surf A: Physchem Eng Asp* 241, 15-25.
- 16 Namasivayam, C., Kavitha, D., 2002. Removal of Congo Red from water by adsorption onto
17 activated carbon prepared from coir pith, an agricultural solid waste. *Dyes Pigments*, 47.
- 18 Ncibi, M.C., Mika, S., 2015. Optimized removal of antibiotic drugs from aqueous solutions
19 usingsingle, double and multi-walled carbon nanotubes. *J Hazard Mater* 298, 102-110.
- 20 Njoku, V.O., Foo, K.Y., Asif, M., Hameed, B.H., 2014. Preparation of activated carbons from
21 rambutan (*Nephelium lappaceum*) peel by microwave-induced KOH activation for acid
22 yellow 17 dye adsorption. *Chem Eng J* 250, 198-204.
- 23 Rivera-Utrilla, J., Gómez-Pacheco, C.V., Sánchez-Polo, M., López-Peñalver, J.J., Ocampo-
24 Pérez, R., 2013. Tetracycline removal from water by adsorption/bioadsorption on
25 activated carbons and sludge-derived adsorbents. *J Environ Manage* 131, 16-24.

1 Rodríguez-Estupiñan, P., Giraldo, L., Moreno-Piraján, J.C., 2013. Energetic changes in the
2 surface of activated carbons and relationship with Ni(II) adsorption from aqueous
3 solution. *Appl Surf Sci* 286, 351-357.

4 Ryu, J., Suh, Y.-W., Suh, D.J., Ahn, D.J., 2010. Hydrothermal preparation of carbon
5 microspheres from mono-saccharides and phenolic compounds. *Carbon* 48, 1990-1998.

6 Sanchez-Sanchez, A., Martinez de Yuso, A., Braghiroli, F.L., Izquierdo, M.T., Alvarez, E.D.,
7 Perez-Cappe, E., Mosqueda, Y., Fierro, V., Celzard, A., 2016. Sugarcane molasses as a
8 pseudocapacitive material for supercapacitors. *RSC Adv* 6, 88826-88836.

9 Schaefer, S., Fierro, V., Izquierdo, M.T., Celzard, A., 2016. Assessment of hydrogen storage
10 in activated carbons produced from hydrothermally treated organic materials. *Internat J*
11 *Hydr Energ* 41, 12146-12156.

12 Schaefer, S., Muñoz, G., Izquierdo, M.T., Mathieu, S., Ballinas-Casarrubias, M.L., González-
13 Sánchez, G., Celzard, A., Fierro, V., 2017. Rice straw-based activated carbons doped
14 with SiC for enhanced hydrogen adsorption. *Internat J Hydr Energ* 42, 11534-11540.

15 Schlapbach, L., Züttel, A., 2001. Hydrogen-storage materials for mobile applications. *Nature*
16 414, 353-358.

17 Selmi, T., Seffen, M., Sammouda, H., Sandrine, M., Jagiello, J., Celzard, A., Fierro, V., 2017.
18 Physical meaning of the parameters used in fractal kinetic and generalized adsorption
19 models of Brouers-Sotolongo. Submitted to *Adsorption*.

20 Seredych, M., Biggs, M.J., Bandosz, T.J., 2016. Oxygen reduction on chemically
21 heterogeneous iron-containing nanoporous carbon: The effects of specific surface
22 functionalities. *Microporous Mesoporous Mater* 221, 137-149.

23 Sethia, G., Sayari, A., 2016. Activated carbon with optimum pore size distribution for
24 hydrogen storage. *Carbon* 99, 289-294.

- 1 Sun, Y., Yue, Q., Gao, B., Wang, Y., Gao, Y., Li, Q., 2013. Preparation of highly developed
2 mesoporous activated carbon by $H_4P_2O_7$ activation and its adsorption behavior for
3 oxytetracycline. Powder Technol 249, 54-62.
- 4 Szczurek, A., Amaral-Labat, G., Fierro, V., Pizzi, A., Celzard, A., 2011. Bimodal activated
5 carbons derived from resorcinol-formaldehyde cryogels. Sci Technol Adv Mater 12.
- 6 Thommes, M., Kaneto, K., Neimark, A.V., Olivier, J.P., Rodriguez-Reinoso, F., Rouquerol,
7 J., Sing, K.S.W., 2015. Physisorption of gases, with special reference to the evaluation
8 of surface area and pore size distribution (IUPAC Technical Report),. Pure Appl Chem
9 9e10, 1051e1069.
- 10 Vu, B.K., Snisarenko, O., Lee, H.S., Shin, E.W., 2010. Adsorption of tetracycline on
11 La-impregnated MCM-41 materials. Environmental Technology 31, 233-241.
- 12 Washburn, E.W., 1921. The dynamics of capillary flow. Phys Rev 17, 273-283.
- 13 Zhang, D., Yin, J., Zhao, J., Zhu, H., Wang, C., 2015. Adsorption and removal of tetracycline
14 from water by petroleum coke-derived highly porous activated carbon. J Environ Chem
15 Eng 3, 1504-1512.
- 16 Zhao, W., Fierro, V., Zlotea, C., Aylon, E., Izquierdo, M.T., Latroche, M., Celzard, A., 2011.
17 Optimization of activated carbons for hydrogen storage. Internat J Hydr Energ 36,
18 11746-11751.
- 19 Zietzschmann, F., Stützer, C., Jekel, M., 2016 Granular activated carbon adsorption of organic
20 micro-pollutants in drinking water and treated wastewater--Aligning breakthrough curves
21 and capacities. Water Res 7, 180.

1 **List of tables**

2 Table 1: Results of pH_{PZC} , $pH_{Initial}$ and potentiometric titration measurements: peak position
3 and numbers of groups (in parentheses: (mmol/g))

4 Table 2: Thermodynamic parameters for the adsorption of TC onto ac2_CHTA2/2 activated
5 carbon at different temperatures (initial TC concentration of 10 mg/L).

6 Table 3: TC removal onto different adsorbents.

7

8

Figure captions

Figure 1: Van Krevelen diagrams of: (a) Agave, Tannin and HTAW series; and (b) CTAW, CHTAW and act_CHTA2/2 series.

Figure 2 : (a) Total yield to hydrochar (HTAW), carbon (CHTAW and CTAW) or activated carbon (act_CHTA2/2); and (b) Experimental (full symbols) and theoretical (empty symbols) carbon yield: CTAW and CHTAW as a function of W .

Figure 3: (a, c, e) N_2 adsorption-desorption isotherms at -196°C ; and (b, d, f) corresponding PSDs.

Figure 4: Correlation between total yields, Y_T , and: (a) total pore volume, $V_{0.97}$; (b) specific surface area, S_{BET} ; (c) % of micropore volume from NLDFT, $\Phi_{mic,NLDFT}$ (%); and (d) average pore diameter of CTAW, CHTAW and act_CHTA2/2 series.

Figure 5: (a) Cumulative intrusion/extrusion of mercury; and (b) corresponding pore size distributions of the act_CHTA2/2 series.

Figure 12: Density of functional groups as a function of pK_a , for carbonaceous materials derived from TA2/2 sample: a) after HTC on one hand, and after HTC followed by carbonisation on the other hand; b) after activation of the CHTA 2/2 sample.

Figure 7: SEM images obtained with secondary electrons of CHTA2/2 at different magnifications: (a) 1000 $\times$; and (b) 5000 $\times$.

Figure 8: (a) FTIR spectra of HTAW materials; (b) optical microscopy image of a fibre of HTA2/2; and (c) chemical mapping of the area selected in (b) (■: *agave americana* hydrochar (HTA0/4), ■: *mimosa* tannin hydrochar (HTA4/0), ■: insignificant component).

Figure 9: Effect of pH and temperature on the adsorption of TC on ac2_CHTA2/2 at equilibrium ($C_0 = 10 \text{ mg/L}$, $m = 0.05 \text{ g}$, $V = 100 \text{ mL}$).

Figure 10: Nonlinear fit to the kinetics of TC adsorption onto: (a) ac2_CHTA2/2 and F300 with PFO and PSO models at pH 4, 25°C and $C_0 = 100 \text{ mg/L}$; and (b) onto ac2_CHTA2/2 only with PSO model at different initial concentrations for pH 7 at 25°C .

Figure 13: Adsorption isotherms of TC onto ac2_CHTA2/2, showing the effects of pH and temperature: (a) fit with Langmuir model, and (b) fit with Freundlich model.