

# Supporting Information

## Carbon microspheres with tailored texture and surface chemistry as electrode materials for supercapacitors

*Abdelhakim Elmouwahidi<sup>1</sup>, Esther Bailón-García<sup>\*1</sup>, Agustín F. Pérez-Cadenas<sup>1</sup>, Alain Celzard<sup>2</sup>, Vanessa Fierro<sup>2</sup>, Francisco Carrasco-Marín<sup>1</sup>*

<sup>1</sup>Research Group in Carbon Materials, Inorganic Chemistry Department, Faculty of Sciences, University of Granada, Campus Fuente Nueva s/n. 18071, Granada, Spain.

<sup>2</sup>Université de Lorraine, CNRS, IJL, F-88000 Epinal, France.

\*Corresponding author: E. Bailón-García, E-mail: [estherbg@ugr.es](mailto:estherbg@ugr.es)

### Contents

Experimental details

Figure S1. Particle size distribution of carbon microspheres obtained from the analysis of optical microscopy images.

Figure S2. XPS spectra of urea-treated carbon microspheres: N1s and O1s

Number of pages: 4

Number of figures: 2

## Experimental details

Gravimetric capacitances, C (F/g), were obtained from the cyclic voltammetry curves by Eq. S1:<sup>1,2</sup>

$$C = \frac{\sum |I| \times \Delta t}{m \times \Delta V} \quad (\text{Eq. S1})$$

where  $\sum |I| \times \Delta t$  was the area of the current (A) against time (s) curve,  $\Delta t$  the discharge time, m the total mass of the carbon material in the electrodes,  $\Delta V$  the voltage interval after the ohmic drop.

The gravimetric capacitance, C (F/g), was obtained from galvanostatic charge-discharge tests by Eq. S2:<sup>3,4</sup>

$$C = \frac{I_d \times \Delta t}{m \times \Delta V} \quad (\text{Eq. S2})$$

where  $I_d$  is the discharge current,  $\Delta t$  the discharge time, m the total mass of the active material in the electrodes, and  $\Delta V$  the voltage interval after the ohmic drop.


For performance comparisons, the gravimetric capacitances in two-electrodes configuration (2EC) were multiplied by four to obtain the expression per single electrode, ( $C_{CV}$  and  $C_{GD}$ , from cyclic voltammetry and galvanostatic charge-discharge tests, respectively) which is the 3-electrode configuration (3EC) equivalent.<sup>5</sup>

The electrical energy and the power density were calculated by using the Eq. S3 and Eq. S4, respectively for two-electrode cell:<sup>6</sup>


$$E(\text{Wh kg}^{-1}) = \frac{C(F \text{ g}^{-1}) \times \Delta V^2 (V)}{2 \times 3.6} \quad (\text{Eq. S3})$$

$$P(W \text{ kg}^{-1}) = \frac{E}{\Delta t} \quad (\text{Eq. S4})$$

where  $\Delta V$  is the operation voltage taken as  $\Delta V = V_{\max} - IR_{\text{drop}}$ ,  $\Delta t$  is the discharge time (h) and C are the values of the capacitances obtained from Eq. S2.



**Figure S1.** Particle size distribution of carbon microspheres obtained from the analysis of optical microscopy images.



**Figure S2.** XPS spectra of urea-treated carbon microspheres: (a) N<sub>1s</sub> and (b) O<sub>1s</sub>

## REFERENCES

- (1) Moreno-Castilla, C.; García-Rosero, H.; Carrasco-Marín, F. Symmetric Supercapacitor Electrodes from KOH Activation of Pristine, Carbonized, and Hydrothermally Treated Melia Azedarach Stones. *Materials (Basel)*. **2017**, *10* (7). DOI 10.3390/ma10070747.
- (2) Elmouwahidi, A.; Zapata-Benabithe, Z.; Carrasco-Marín, F.; Moreno-Castilla, C. Activated Carbons from KOH-Activation of Argan (*Argania Spinosa*) Seed Shells as Supercapacitor Electrodes. *Bioresour. Technol.* **2012**, *111*, 185–190. DOI 10.1016/j.biortech.2012.02.010.
- (3) Zapata-Benabithe, Z.; Carrasco-Marín, F.; Moreno-Castilla, C. Electrochemical Performance of Cu- and Ag-Doped Carbon Aerogels. *Mater. Chem. Phys.* **2013**, *138* (2–3), 870–876. DOI 10.1016/j.matchemphys.2012.12.076.
- (4) Zapata-Benabithe, Z.; Carrasco-Marín, F.; De Vicente, J.; Moreno-Castilla, C. Carbon Xerogel Microspheres and Monoliths from Resorcinol-Formaldehyde Mixtures with Varying Dilution Ratios: Preparation, Surface Characteristics, and Electrochemical Double-Layer Capacitances. *Langmuir* **2013**, *29* (20), 6166–6173. DOI 10.1021/la4007422.
- (5) Rufford, T. E.; Hulicova-Jurcakova, D.; Fiset, E.; Zhu, Z.; Lu, G. Q. Double-

Layer Capacitance of Waste Coffee Ground Activated Carbons in an Organic Electrolyte. *Electrochim. commun.* **2009**, *11* (5), 974–977. DOI 10.1016/j.elecom.2009.02.038.

- (6) Korenblit, Y.; Rose, M.; Kockrick, E.; Borchardt, L.; Kvít, A.; Kaskel, S.; Yushin, G. High-Rate Electrochemical Capacitors Based on Ordered Mesoporous Silicon Carbide-Derived Carbon. *ACS Nano* **2010**, *4* (3), 1337–1344. DOI 10.1021/nn901825y.