

Hydrogen storage in HKUST-1@Activated Carbon composites obtained by Resonant Acoustic Mixing

L Jimenez-Lopez, R Morales, Jimena Castro-Gutiérrez, A. Celzard, Vanessa

Fierro

► To cite this version:

L Jimenez-Lopez, R Morales, Jimena Castro-Gutiérrez, A. Celzard, Vanessa Fierro. Hydrogen storage in HKUST-1@Activated Carbon composites obtained by Resonant Acoustic Mixing. 18th International Symposium on Metal-Hydrogen Systems, MH2024, May 2024, Saint-Malo, France. hal-04568152

HAL Id: hal-04568152 https://hal.univ-lorraine.fr/hal-04568152

Submitted on 3 May 2024 $\,$

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Hydrogen storage in HKUST-1@Activated Carbon composites obtained by Resonant Acoustic Mixing

L. Jimenez-Lopez¹, R. Morales¹, J. Castro-Gutierrez¹, A. Celzard^{1,2}, V. Fierro^{1,*}

¹ Université de Lorraine, CNRS, IJL, F-88000 Epinal, France ² Institut Universitaire de France (IUF), 75005 Paris, France

vanessa.fierro@univ-lorraine.fr

Metal-organic frameworks (MOFs) are promising adsorbents for hydrogen storage, as they feature adaptable porosities, high surface areas and the potential to be functionalized to suit specific applications [1]. Incorporating carbon materials into the MOF matrix has already proved to be a successful strategy for enhancing the specific surface area of the resulting composite material compared with the original MOF. This, in turn, improves its adsorption capacity [2]. This study focuses on the impact of mixing a commercial, high-surface area activated carbon (AC, MSC 30 from Kansai Coke and Chemicals Co., Ltd.) with a well-known MOF, HKUST-1, on the properties of the composite, including hydrogen storage capacity. Resonant Acoustic Mixing (RAM) was used because it provides exceptional powder mixing. Figure 1 shows a schematic representation of the synthesis method and some relevant results.




Figure 1 a) Schematic representation of the synthesis process. For commercial HKUST-1 and its composites: b) XRD patterns; c) N₂ isotherms at 77 K; d) Amount of H₂O adsorbed at 293 K; e) Total H₂ uptake (kg/m³)

Mixing different weight percents of AC with HKUST-1 increased the mesopore volume, leading to enhanced H_2 uptake at pressures above 20 bars, and the composites exhibited reduced hydrophilic behavior, possibly extending their lifespan. The total H_2 uptake increased from 40.4 kg/m³ for pure HKUST-1 to 48.6 kg/m³ for the composite with 20 wt.% AC, surpassing the H_2 storage capacity of pure AC, 45.07 kg/m³ at 130 bar and 77K.

Aknowledgements The authors acknowledge: (i) SOLHYD project funded by the ANR-22-PEHY-0007 from the Agence Nationale de la Recherche, (ii) FRCR HyPE project (Production et stockage d'Hydrogène décarboné et son utilisation pour la Production d'Energie dans des dispositifs sans métaux nobles) funded by Région Grand-Est and FEDER, and (iii) TALiSMAN and TALiSMAN2 projects funded by FEDER.

References

[1] S. Bordiga et al., *Phys. Chem. Chem. Phys.*, vol. 9, no. 21, pp. 2676–2685.

[2] A. Policicchio et al., *Microporous and Mesoporous Materials*, vol. 309, p. 110571.